


**3M Industrial Adhesives and Tapes** 

Design & Production Guide | June 2024



# 3M<sup>™</sup> Adhesives and Tapes for design, assembly and production.

### **Table of Contents**

Adhesives and Tapes Overview	2
Considerations for Selecting $3M^{\scriptscriptstyleTM}$ Adhesives and Tapes	3
Assembly Solutions	4–16
Adharina and Carlanta	
Adhesives and Sealants	
3M™ Scotch-Weld™ Structural Adhesives	•
3M™ Scotch-Weld™ PUR Adhesive Systems	
3M™ Scotch-Weld™ Instant Adhesives	
3M™ Scotch-Weld™ Anaerobic Adhesives	
3M™ Scotch-Weld™ EPX Applicators and Nozzles	
3M™ Hot Melt Adhesive Selector Guide	45
3M™ Hot Melt Spray Adhesives	
3M™ Hot Melt Adhesives, Applicators and Accessories	
3M™ Solvent and Water Based Adhesives	52–56, 60-63
3M™ Cleaners and Lubricants	57
3M™ Cylinder Spray Adhesives	58–59
3M™ Adhesive Sealants	64–68
3M™ Concrete Repair	69
Bonding Tapes	
3M™ VHB™ Tapes and Primers	72–79
3M™ Extreme Sealing Tapes	80
3M™ Double Coated Foam Tapes	81–82
3M™ Double Coated Tapes	83–85
3M™ Removable/Repositionable Tapes	86
3M™ Adhesive Transfer Tapes	87–91
Scotch® ATG Adhesive Transfer Tapes	92
3M™ Extended Liner Tapes	93
Specialty Technologies	
3M™ Dual Lock™ Reclosable Fasteners	96–97
3M™ Hook and Loop Reclosable Fasteners	98–99
3M™ Single Coated Foam Tapes	100
3M™ Converter Markets Center	101
Numerical Index	102-104
Product Name Index	105–108







### What can 3M™ Adhesives and Tapes do for your product and process?

### Build strong, durable products:

• From repositionable to permanent, 3M has an adhesive or tape that can be readily matched to the substrate and stress characteristics needed in the joint.

#### Improve appearance and aesthetics:

- 3M adhesives and tapes are generally hidden between the bonded substrates, offering nearly invisible fastening.
- Surfaces stay smooth and clean for a more attractive appearance and less surface refinishing.

### Lower production and material costs:


- Reduce process steps such as weld grinding and sealing individual penetrations from screws, nuts and bolts.
- Use thinner, lighter or less expensive materials that cannot be welded or fastened traditionally.
- Potentially lower capital investment. Many adhesives and tapes do not require major capital to use.
- Manage labor costs. Many tape and adhesive technologies require little operator training.

#### Build products with a continuous bond line:

- Adhesives and tapes uniformly distribute stress along the entire joint. Nuts, bolts and other fasteners concentrate stress at a point which can decrease physical properties of the substrates being assembled.
- Bond and seal simultaneously. Many 3M adhesives and tapes will provide a strong bond, but are also an effective seal against dirt, dust, water and other environmental conditions.
- Good fatigue resistance. If your parts are subject to vibration or other movement, the viscoelastic nature of 3M adhesives and tapes will impart flexibility to a joint or bonded area.

#### Wider material selection for assemblies:

- Lighter and thinner materials can be used. Welding and fastening weaken substrates and require a minimum thickness to retain integrity.
- Bond dissimilar materials. 3M adhesives and tapes bond to a wide range of substrates from metals, wood, glass, plastics and ceramics. This includes "hard to bond," low surface energy materials.
- Prevent galvanic corrosion. 3M adhesives and tapes can provide a film barrier to reduce or prevent bimetallic corrosion that can occur when joining to different types of metals.



With uniform stress distribution of adhesives and tapes, lighter, thinner materials can be used without concerns about distortion, splitting, or crazing at the mechanically fastened site. Elimination of holes in metal also reduces the chances for rust and corrosion.

### 3M™ Adhesives and Tapes Product Family



3M™ VHB™ Tapes



3M™ Contact and **Spray Adhesives** 



3M™ Scotch-Weld™ **Gasket Makers** 



3M™ Scotch-Weld™ Structural Adhesives



3M™ Double **Coated Tapes** 



3M™ Scotch-Weld™ **Instant Adhesives** 



3M™ Adhesive **Sealants** 



3M™ Extreme **Sealing Tapes** 



3M™ Scotch-Weld™ **PUR Adhesives** 





3M™ Hot Melt **Adhesives** 



■ 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Retaining Compound



3M™ Adhesive 3M™ Reclosable Transfer Tapes **Fasteners** 



3M™ Scotch-Weld™ **Threadlockers** 

# Considerations when selecting 3M™ Adhesives and Tapes for your product and process.



### **Assembly**

What type of assembly is required? (Refer to 7 common assembly types in the right hand column.)

What are the overall performance needs of the assembly (flexibility, high peel strength, etc.)?





#### **Substrate**

What are the materials that are being bonded together? (Refer to the substrate selectors for each assembly type on pages 4–15.)

Consider the surface condition texture of each material.



#### **Process**

What is the current assembly and manufacturing process?



Does the solution need to fit into the current process/ equipment or can the process/equipment change?

What are the various process steps and how quickly will the assembly be moved to each step?

At any time, might the assembly bond need to be repositioned? If so, why and when?

Are there any environmental, regulatory or workplace safety restrictions?



### **End-Use**

How and where is the final product used?

Will the assembly be exposed to harsh environmental conditions (UV, chemicals, high humidity, very high or low temperatures, etc.)?





#### Cost

Where can improvements be made in the assembly process (labor, reduction of process steps, materials, workflow, etc.)?

Assembly Solutions are made up of these common applications:



Panel to Frame/ Stiffener to Panel pg 4



Small Joint Assembly pg 6



Large Surface Lamination pg 8



Mounting and Trim Attachment pg 10



Gasket Attachment pg 12



Sealing pg 14



Potting and Encapsulating pg 14

# What are Panel to Frame Assemblies? What are Stiffener to Panel Assemblies?



Panels are used in multiple markets, such as transportation, metalworking and construction.

Panel to Frame: Decorative or load bearing panel that is applied to a rigid frame or support. Examples include trailer panels, elevator walls and sign boxes.

**Stiffener to Panel:** Stiffeners are applied to panels to give extra support and rigidity. **Examples include trailer wall panels, traffic signs and large metal enclosures.** 

#### Possible Adhesive or Tape Requirements:

- Dead load holding strength
- Flexibility for dynamic loads and thermal expansion mismatch
- Fill a gap or variation in fit from end to end
- Provide a water seal

### **Best 3M Solutions for Panel to Frame/Stiffener to Panel Assemblies**



### **■ 3M<sup>™</sup> VHB<sup>™</sup> Tapes** (pg 72–79)

These high-strength bonding tapes are a proven alternative to screws, rivets, welds and other mechanical fasteners. 3M™ VHB™ Tape offers instant strength, a high ultimate bond and seals simultaneously. 3M™ VHB™ Tape's viscoelasticity allows relative movement of parts for thermal expansion/contraction. Best for flat to flat applications with a consistent bondline thickness.



### **3M™ Scotch-Weld™ Structural Adhesives** (pg 18–35)

Acrylic, epoxy and urethane structural adhesives that hold over 1,000 psi in overlap shear strength. Best suited for thinner bondlines, irregular shapes and textured surfaces where load-bearing strength is needed. Provides the highest load-bearing strength and environmental resistance.



### 3M™ Adhesive Sealants (pg 64–68)

Acrylic, polyurethane, nitrile and hybrid one-component adhesive technologies with outstanding sealing properties. These products are capable of filling larger and irregular gaps including rough substrates. Highly flexible formulations allow for relative movement for thermal expansion/contraction.



### 3M™ Reclosable Fasteners (pg 96-99)

 $3M^{\mathbb{M}}$  Dual Lock<sup> $\mathbb{M}$ </sup> and  $3M^{\mathbb{M}}$  Hook and Loop Reclosable Fasteners for strong yet easily removable fastening solutions. These products are ideal to allow access for servicing or replacement of a panel. Generally backed with  $3M^{\mathbb{M}}$  VHB $^{\mathbb{M}}$  Tape or other 3M adhesive technologies.

### Performance Factors for Panel to Frame/Stiffener to Panel Assemblies

All 3M technologies in the table below are commonly used in panel applications. Use the table below as a relative comparison of product performance.

Attribute	3M™ VHB™ Tapes	3M™ Scotch-Weld™ Structural Adhesives	3M™ Adhesive Sealants	3M <sup>™</sup> Reclosable Fasteners
Number of Steps to Apply and Ease of Application	Best	Best	Better	Better
Rate of Strength Build	Best	Good	Good	Best
Flexibility and Joint Expansion	Best	Good	Best	Best
Holding Power	Good	Best	Better	Good
Repair/Removal After Cure	Best	Good	Better	Best

### Panel to Frame/Stiffener to Panel Assembly Solutions

Metals + (Aluminum, Steel, Stainless, Galvanized)	Paints (Powder Coat, Painted Metal, Composite Panel)	Glass	Plastics: HSE, MSE (ABS, Acrylic, Polycarbonate, Nylon)	Plastics: LSE (Polypropylene, Polyethylene)
3M" VHB" Tape4941, RP+110GP, 5952 3M" Scotch-Weld" Structural Adhesive LSB60NS 3M" Adhesive Sealant 550FC+ AC63* 3M" Reclosable Fastener SJ3550/51/52, SJ3571/72	■ 3M" VHB" Tape 4941*, RP+110GP*, 5952 ■ 3M" Scotch-Weld" Structural Adhesive LSB60NS ■ 3M" Adhesive Sealant 550FC + AC63* ■ 3M" Reclosable Fastener SJ3540/41/42, SJ3526N/27N	3M" VHB" Tape 4941*, RP+110GP*, 5952* 3M" Scotch-Weld" Structural Adhesive LSB60NS 3M" Adhesive Sealant 590*, 560*, 760* 3M" Reclosable Fastener SJ3560/61/62, SJ3571/72	3M" VHB" Tape 4941*, RP+110GP*, 5952 3M" Scotch-Weld" Structural Adhesive LSB60NS 3M" Adhesive Sealant 560*, 760* 3M" Reclosable Fastener SJ3550/51/52, SJ3571/72	3M" VHB" Tape 4941*, RP+110GP*, 5952*  3M" Scotch-Weld" Structural Adhesive DP8010 Blue  3M" Adhesive Sealant 560*, 760*  3M" Reclosable Fastener SJ3540/41/42, SJ3526N/27N
Paints	■ 3M" VHB" Tape 4941*, RP+110GP*, 5952 ■ 3M" Scotch-Weld" Structural Adhesive DP8810NS ■ 3M" Adhesive Sealant 550*, 560*, 760	■ 3M* VHB* Tape 4941*, RP+110GP*, 5952* ■ 3M* Scotch-Weld* Structural Adhesive LSB60NS ■ 3M* Adhesive Sealant 590*, 560*, 760*	3M" VHB" Tape 4941*, RP+110GP*, 5952 3M" Scotch-Weld" Structural Adhesive DP8810NS 3M" Adhesive Sealant 560*, 760*	3M" VHB" Tape 4941*, RP+110GP*, 5952* 3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Adhesive Sealant 560*, 760*
Glass		■ 3M* VHB* Tape 4941*, RP+110GP*, 5952* ■ 3M* Scotch-Weld* Structural Adhesive DP460 ■ 3M* Adhesive Sealant 590*	3M" VHB" Tape 4941*, RP+110GP*, 5952 3M" Scotch-Weld" Structural Adhesive DP100 Plus Clear 3M" Adhesive Sealant 560*, 760*	3M" VHB" Tape 4941*, RP+110GP*, 5952* 3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Adhesive Sealant 560*, 760*
Plastics: HSE, MSE			■ 3M* VHB* Tape 4941*, RP+110GP*, 5952 ■ 3M* Scotch-Weld* Structural Adhesive DP8405NS ■ 3M* Adhesive Sealant 560*, 760*	■3M" VHB" Tape 4941*, RP+110GP*, 5952* ■3M" Scotch-Weld" Structural Adhesive DP8010 Blue ■3M" Adhesive Sealant 560*, 760*
Plastics: LSE				3M" VHB" Tape 4941*, RP+110GP*, 5952* 3M" Scotch-Weld" Structural Adhesive D8010 Blue 3M" Adhesive Sealant 560*, 760*


<sup>\*</sup>Primers may also be required in some cases. See specific product pages for primer details.

# For 3M™ VHB™ Tape applications in the Commercial Vehicle market, refer to page 76 for a selection of products.









This guide lists products that are commonly used for this specific application. It is important that the customer evaluates these suggested products in their specific application.

### What are Small Joint Assemblies?

Small joint assemblies exist in multiple markets, such as sporting goods, electronics, furniture, motors and electrical.



Small Joint: Small joints are typically irregularly shaped but only a few inches of overlap area. They may be insertion joints or overlap joints, or some combination. Examples include sporting goods (e.g., golf club heads to shaft), plastic casings, lens mounting for instrumentation, mortise and tenon furniture joints, thread locking or shaft retailing, magnet bonding and jewelry making.

# Possible Adhesive or Tape Requirements:

- Low viscosity for tight fitting parts
- Vibration resistance
- Very high strength
- Bond dissimilar materials

### **Best 3M Solutions for Small Joint Assemblies**



### **3M™ Scotch-Weld™ Structural Adhesives** (pg 18–35)

Acrylic, epoxy and urethane structural adhesives that hold over 1000 psi in overlap shear strength. Best choice for highest strength, fatigue and environmental resistance especially for metal to metal bonds.



### 3M™ Scotch-Weld™ Instant Adhesives (pg 38-39)

One part solvent-free adhesive that reaches handling strength in 5–10 seconds. Best for small bondlines (<10cm2). Commonly used on rubbers and plastics. Very tight bondlines are achievable with near instant strength.



### 3M™ Hot Melt Adhesives (pg 45-51)

100% solid, thermoplastic resins that reach bond strength in seconds. Best for wood and plastic.



One component, hot applied thermosetting adhesive with immediate strength and holding power. Final cured strength over 1,000 psi. Best for wood and plastic.



### ■ 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Retaining Compounds

One-part anaerobic adhesives cure between metal surfaces. Permanent and removable grades are available.



### 3M™ Scotch-Weld™ Threadlockers (pg 41)

One-part anaerobic adhesives cure between metal surfaces. Permanent and removable grades are available.

### **Performance Factors for Small Joint Assemblies**

All 3M technologies in the table below are commonly used in small joint applications.


Use the table below as a relative comparison of product performance.

Attribute	3M™ Scotch-Weld™ Structural Adhesives	3M™ Scotch-Weld™ Instant Adhesives	3M™ Hot Melt Adhesives	3M™ Scotch-Weld™ PUR Adhesives	3M™ Scotch-Weld™ Threadlockers
Shear and Peel Strength	Best	Better	Good	Best	Better
Temperature and Solvent Resistance	Best	Good	Better	Best	Better
Aesthetics	Good	Best	Better	Better	Better
Rate of Strength Build	Good	Best	Best	Better	Better
Rework	Good	Better	Better	Good	Best

### **Small Joint Assembly Solutions**

+ Metal (Unpainted)	Metal (Painted)	Glass, Ceramic, Stones	Rubber, Elastomers	Plastics: HSE, MSE (ABS, Acrylic, Polycarbonate, Nylon)	Plastics: LSE (Polypropylene, Polyethylene)	Wood
3M" Scotch-Weld" Structural Adhesive DP420NS 3M" Hot Melt Adhesive 3747, 3789 3M" Scotch-Weld" Retaining Compound RT09 3M" Scotch-Weld" Threadlockers TL62	3M° Scotch-Weld° Structural Adhesive DP8805NS 33M° Hot Melt Adhesive 3747, 3764	■ 3M" Scotch-Weld" Structural Adhesive DP420NS ■ 3M" Hot Melt Adhesive 3747, 3789	■ 3M <sup>™</sup> Scotch-Weld <sup>™</sup> Structural Adhesive 2216	■ 3M* Scotch-Weld* Structural Adhesive DP8805NS ■ 3M* Hot Melt Adhesive 3764, 3747 ■ 3M* Scotch-Weld* PUR Adhesive TE040, EZ250150	■ 3M" Scotch-Weld" Structural Adhesive DP8010 Blue ■ 3M" Hot Melt Adhesive 3748, 3764 ■ 3M" Scotch-Weld" PUR Adhesive TE040, EZ250150	3M" Scotch-Weld" Structural Adhesive DP100 Plus 3M" Hot Melt Adhesive 3792 3M" Scotch-Weld" PUR Adhesive EZZ5150
Metal (Painted)	3M" Scotch-Weld" Structural Adhesive DP8805NS 3M" Scotch-Weld" Instant Adhesive PR100 3M" Hot Melt Adhesive 3747, 3764	3M" Scotch-Weld" Structural Adhesive DP100 Plus 3M" Scotch-Weld" Instant Adhesive PR100 3M" Hot Melt Adhesive 3764, 3792	■ 3M™ Scotch-Weld™ Structural Adhesive DP620NS ■ 3M™ Scotch-Weld™ Instant Adhesive PR100*	3M" Scotch-Weld" Structural Adhesive DP8805NS 3M" Scotch-Weld" Instant Adhesive PR100 3M" Hot Melt Adhesive 3748, 3764 3M" Scotch-Weld" PUR Adhesive TE040, EZ250150	3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100" 3M" Hot Melt Adhesive 3748, 3764 3M" Scotch-Weld" PUR Adhesive TE040, EZ250150	3M" Scotch-Weld" Structural Adhesive DP620NS 3M" Scotch-Weld" Instant Adhesive SI100 3M" Hot Melt Adhesive 3764, 3792 3M" Scotch-Weld" PUR Adhesive EZ25150
Glass, Ceramic, Stones		■ 3M" Scotch-Weld" Structural Adhesive DP100 Plus 3M" Scotch-Weld" Instant Adhesive PR100 ■ 3M" Hot Melt Adhesive 3792	■ 3M <sup>∞</sup> Scotch-Weld <sup>∞</sup> Structural Adhesive DP100 Plus 3M <sup>∞</sup> Scotch-Weld <sup>∞</sup> Instant Adhesive PR100*	■ 3M* Scotch-Weld* Structural Adhesive DP100 Plus ■ 3M* Scotch-Weld* Instant Adhesive PR100 ■ 3M* Hot Melt Adhesive 3748, 3764	3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100" 3M" Hot Melt Adhesive 3748, 3764	3M" Scotch-Weld" Structural Adhesive DP420NS 3M" Scotch-Weld" Instant Adhesive S1100 3M" Hot Melt Adhesive 3792 3M" Scotch-Weld" PUR Adhesive EZ250120, EZ250150
Rubber, Elastomers			3M <sup>∞</sup> Scotch-Weld <sup>∞</sup> Instant Adhesive PR100*	■ 3M* Scotch-Weld** Structural Adhesive DF620NS ■ 3M* Scotch-Weld** Instant Adhesive PR100*	3M" Scotch-Weld" Instant Adhesive PR100*	3M" Scotch-Weld" Structural Adhesive DP604NS 3M" Scotch-Weld" Instant Adhesive SI100*
Plastice: HSE, MSE				3M" Scotch-Weld™ Structural Adhesive DP840SNS, DP880SNS 3M" Scotch-Weld™ Instant Adhesive PR100 3M" Hot Melt Adhesive 3748, 3764 3M" Scotch-Weld™ PUR Adhesive EZ250150	3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100* 3M" Hot Melt Adhesive 3748, 3764	3M" Scotch-Weld" Structural Adhesive DP620NS 3M" Scotch-Weld" Instant Adhesive S1100 3M" Hot Melt Adhesive 3764, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150
Plastics: LSE					3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100* 3M" Hot Melt Adhesive 3748, 3764	3M" Scotch-Weld" Structural Adhesive DP8010NS 3M" Scotch-Weld" Instant Adhesive S1100* 3M" Hot Melt Adhesive 3764, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150
Роом						3M" Scotch-Weld" Structural Adhesive DP100 3M" Scotch-Weld" Instant Adhesive S1100 3M" Hot Melt Adhesive 3792 3M" Scotch-Weld" PUR Adhesive EZ250120, EZ250060

 $<sup>\</sup>ensuremath{^{\star}}\xspace Primers may also be required in some cases. See specific product pages for primer details.$ 







This guide lists products that are commonly used for this specific application. It is important that the customer evaluates these suggested products in their specific application.

# What are Large Surface Lamination Assemblies?



Large surface bonds and laminations exist in multiple markets, such as transportation, appliance, furniture and construction.

Large Surface Lamination: Two surfaces (substrates) of similar size, either rigid or flexible, are bonded or laminated together where a majority of the surface is covered by the adhesive or tape in order to create the bond. Examples include high pressure laminate to tabletops, fabric to foam for furniture, veneers on wood and flexible transportation flooring.

#### Possible Adhesive or Tape Requirements:

- Cover full surface
- Flexible when dry; not stiff
- Allow for positioning parts
- Bonds quickly/little or no fixturing

### **Best 3M Solutions for Large Surface Lamination Assemblies**



### **3M™ Scotch-Weld™ Structural Adhesives** (pg 18–35)

Acrylic, epoxy and urethane structural adhesives that hold over 1,000 psi in overlap shear strength. Best suited for applications where high load-bearing strength is required.



### **3M™ Contact and Spray Adhesives** (pg 52–63)

Solvent and water based adhesives that can be sprayed, brushed or roll applied. Very fast and easy coverage of large areas including irregular and mildly textured shapes. Bonds the widest range of substrates.



### 3M™ Hot Melt Adhesives (pg 45–51)

100% solid, low VOC thermoplastic resins that reach bond strength in seconds. Long open-time formulations can be spray applied. Bonds irregular shapes and textured surfaces.



### **3M™ Scotch-Weld™ PUR Adhesives** (pg 36–37)

One component, hot applied thermosetting adhesive with immediate strength and holding power. Final cured strength over 1,000 psi. Long open-time formulations can be spray applied.



### **3M**<sup>™</sup> Adhesive Transfer Tapes (pg 87–92)

A pressure sensitive adhesive on a liner. Can be laminated onto a surface by hand or by automation. Instant adhesion with no mess or waste and very thin bondlines.

### Performance Factors for Large Surface Lamination Assemblies

All 3M technologies in the table below are commonly used in large surface bonding applications. Use the table below as a relative comparison of product performance.


Attribute	3M™ Scotch-Weld™ Structural Adhesives	3M™ Contact and Spray Adhesives	3M™ Hot Melt Adhesives	3M™ Scotch-Weld™ PUR Adhesives	3M™ Adhesive Transfer Tapes
Shear and Peel Strength	Best	Good	Better	Best	Better
Temperature and Solvent Resistance	Best	Good	Better	Best	Good
Aesthetics and Read Through	Good	Best	Better	Better	Best
Speed and Convenience of Application	Good	Best	Better	Better	Better
Rate of Strength Build	Good	Best	Best	Better	Best


### **Large Surface Lamination Assembly Solutions**

+	Metals, Paints, Glass	Rubber (EPDM, Santoprene®)	Foam and Cloth (Urethane, Fabrics)	Plasticized Vinyl	Plastics (ABS, Acrylic, Polycarbonate, Nylon)	Wood
Metals, Paints, Glass	3M" Scotch-Weld" Structural Adhesive LSB60 3M" Contact and Spray Adhesive 94 CA, 1357 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115HGS 3M" Adhesive Transfer Tape F9473PC, 9485PC	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 1300, 847 3M" Adhesive Transfer Tape 468MP*, 950	3M" Contact and Spray Adhesive 74, 100NF 3M" Hot Melt Adhesive 6111HT 3M" Adhesive Transfer Tape 6035PC, 950	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4491, 1000NF 3M" Adhesive Transfer Tape F9467U, F9465PC	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 94 CA, 4475 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape 468MP, 9472LE	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 94 CA, 1357 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115HGS 3M" Adhesive Transfer Tape 6035PC, 468MP
Rubber		3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4799 3M" Scotch-Weld" PUR Adhesive TS230 3M" Adhesive Transfer Tape 468MP*, 950	■ 3M" Contact and Spray Adhesive 4799 3M" Scotch-Weld" PUR Adhesive TS230, TS115 ■ 3M" Adhesive Transfer Tape 6035PC, 950	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4799 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape F9467U*, F9465PC	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4799 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape 468MP*, 9472LE	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4799 3M" Scotch-Weld" PUR Adhesive TS230, TS115HGS 3M" Adhesive Transfer Tape 468MP*, 950
Foam and Cloth			3M" Contact and Spray Adhesive 74, 100NF 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape 6035PC, 950	3M" Contact and Spray Adhesive 4491, 1000NF 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape 950, F9465PC	3M" Contact and Spray Adhesive 77, 74 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape 950, 6035PC	3M" Contact and Spray Adhesive 77, 1000NF 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115HGS 3M" Adhesive Transfer Tape 950, 6035PC
Plasticized Vinyl				3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4491, 1300 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape F9467U, F9465PC	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4491, 1300 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape F9467U, F9465PC	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 4491, 1000NF 3M" Scotch-Weld" PUR Adhesive TS230, T5115HGS 3M" Adhesive Transfer Tape F9467U, F9465PC
Plastics					3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 94 CA, 4475 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115 3M" Adhesive Transfer Tape 9472LE, 468MP	3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 94 CA, 4475 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115HGS 3M" Adhesive Transfer Tape 9472LE, 468MP
Wood						3M" Scotch-Weld" Structural Adhesive 2216 3M" Contact and Spray Adhesive 94 CA, 30NF 3M" Hot Melt Adhesive 6111HT 3M" Scotch-Weld" PUR Adhesive TS230, TS115HGS 3M" Adhesive Transfer Tape 6035PC, 468MP

 $<sup>\</sup>mbox{{\sc *}Primers}$  may also be required in some cases. See specific product pages for primer details.









This guide lists products that are commonly used for this specific application. It is important that the customer evaluates these suggested products in their specific application.

# What are Mounting and Trim Attachment Assemblies?



Mounting and trim attachment exists in multiple markets, such as transportation, appliance, furniture, construction and architecture.

**Mounting:** Applying an object to a surface. Generally, static loads are prevalent and the mounted item is smaller than the surface to which it is bonded. **Examples include small signs, mirrors and white boards, and panel-over-panel with partial adhesive coverage.** 

**Trim:** Decoration or identification added to a surface. **Examples include** nameplates, edge banding, bezels, rosettes and muntin bars.

# Possible Adhesive or Tape Requirements:

- Dead load holding strength
- Aesthetics
- Removability
- Fast bonding/little or no fixturing

### **Best 3M Solutions for Mounting and Trim Attachment Assemblies**



### **3M**<sup>™</sup> VHB<sup>™</sup> Tapes (pg 72–79)

High-strength bonding tapes that are a proven alternative to screws, rivets, welds and other mechanical fasteners. Can pre-apply to trim for production flexibility. Ideal for dissimilar substrates.



### **3M™ Scotch-Weld™ Structural Adhesives** (pg 18–35)

Acrylic, epoxy and urethane structural adhesives that hold over 1,000 psi in overlap shear strength. Use for heavy deadloads with smaller joint areas (Example: brackets on heavy panels, poorly matched parts with high spring-back forces).



### 3M™ Scotch-Weld™ Instant Adhesives (pg 38–39)

One part solvent-free cyanoacrylate (CA) adhesive that reaches handling strength in 5–30 seconds. Best for small very tight bondlines (<10cm2). Commonly used on rubbers and plastics.



### **3M**<sup>™</sup> Hot Melt Adhesives (pg 45–51)

100% solid, thermoplastic resins that reach bond strength in seconds. Best for wood and plastic.



### **3M™ Scotch-Weld™ PUR Adhesives** (pg 36–37)


One component, hot applied thermosetting adhesive with immediate strength and holding power. Final cured strength over 1,000 psi. Best for wood and plastic.

# 3M™ Reclosable Fasteners (pg 96–99)

3M™ Dual Lock™ and 3M™ Hook and Loop Reclosable Fasteners for strong yet easily removable fastening solutions. These products are ideal for quick mounting, trim or sign installation and change out.

# **3M™ Adhesive Transfer Tapes** (pg 87–92)

A pressure sensitive adhesive on a liner. Can be laminated



### 3M™ Double Coated Tapes (pg 81–85)

A paper, film or tissue carrier with pressure sensitive adhesive on both sides. Can be laminated onto a surface by hand or by automation. Can be pre-applied to trim. Provides very thin, aesthetic bondlines. Special formulations for LSE plastics.

### Performance Factors for Mounting and Trim Attachment Assemblies

All 3M technologies in the table below are commonly used in mounting and trim attachment applications. Use the table below as a relative comparison of product performance.

Attribute	3M™ VHB™ Tapes	3M™ Scotch-Weld™ Structural Adhesive	3M <sup>™</sup> Scotch-Weld <sup>™</sup> Instant Adhesive	3M™ Hot Melt Adhesives	3M <sup>™</sup> Scotch-Weld <sup>™</sup> PUR Adhesives	3M <sup>™</sup> Reclosable Fasteners	3M <sup>™</sup> Adhesive Transfer Tapes	3M <sup>™</sup> Double Coated Tapes
Shear and Peel Strength	Better	Best	Better	Better	Best	Good	Good	Good
Temperature and Solvent Resistance	Better	Best	Good	Good	Best	Better	Better	Better
Aesthetics	Best	Good	Better	Better	Better	Better	Best	Best
Repositionability During Application	Good	Best	Good	Good	Better	Better	Good	Better
Rate of Strength Build	Best	Good	Best	Best	Better	Best	Best	Best
Removable After Cure	Better	N/A	Good	Good	N/A	Best	Better	Better

### **Mounting and Trim Attachment Assembly Solutions**

+	Metals (Aluminum, Steel, Stainless, Galvanized)	Paints (Powder Coat, Painted Metal, Composite Panel, Sealed or Painted Wood)	Glass	Plastics: HSE, MSE (ABS, Acrylic, Polycarbonate, Nylon)	Plastics: LSE (Polypropylene, Polyethylene)	Wood
Metals	3M" VHB" Tape4941, 5952, RP+100GP 3M" Scotch-Weld" Structural Adhesive DP8805NS 3M" Hot Melt Adhesive 3789, 3747 3M" Scotch-Weld" PUR Adhesive TE040, EZ250150 3M" Reclosable Fastener SJ3550/51/52, SJ3571/72 3M" Adhesive Transfer Tape 468MP, F9473PC 3M" Double Coated Tape 9500PC	3M" VHB" Tape 4941,* 5952, RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8810NS 3M" Hot Melt Adhesive 3764, 3747 3M" Scotch-Weld" PUR Adhesive TE040, EZ250150 3M" Reclosable Fastener \$J3540/41/42, \$J3526N/27N 3M" Adhesive Transfer Tape 9472LE, 9485PC 3M" Double Coated Tape 9500PC	3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP420NS 3M" Hot Melt Adhesive 3789, 3747 3M" Reclosable Fastener SJ3560/61/62, SJ3571/72 3M" Adhesive Transfer Tape 468MP, F9473PC 3M" Double Coated Tape 9500PC	3M" VHB" Tape 4941,* 5952, RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8805NS 3M" Hot Melt Adhesive 3764, 3747 3M" Scotch-Weld" PUR Adhesive TE040, EZ250150 3M" Reclosable Fastener SJ3550/51/52, SJ3571/72 3M" Adhesive Transfer Tape 468MP, 9472LE 3M" Double Coated Tape 9500PC	3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Hot Melt Adhesive 3764, 3747 3M" Reclosable Fastener \$J3540/41/42, \$J3526N/27N 3M" Adhesive Transfer Tape 9472LE, 9485PC 3M" Double Coated Tape 9500PC	■ 3M" Hot Melt Adhesive 3792 ■ 3M" Scotch-Weld" PUR Adhesive EZ250150
Paints		3M" VHB" Tape 4941,* 5952, RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8810NS 3M" Scotch-Weld" Instant Adhesive PR100 3M" Hot Melt Adhesive 3764, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150 3M" Reclosable Fastener SJ3540/41/42, SJ3526N/2TN 3M" Adhesive Transfer Tape 9472LE, 468MP 3M" Double Coated Tape 9832, 9500PC	3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP420NS 3M" Hot Melt Adhesive 3764, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150 3M" Reclosable Fastener SJ3560/61/62, SJ3571/72 3M" Adhesive Transfer Tape 9472LE, 468MP 3M" Double Coated Tape 9832, 9500PC	3M" VHB" Tape 4941,* 5952, RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8410NS 3M" Scotch-Weld" Instant Adhesive PR100 3M" Hot Melt Adhesive 3747, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150 3M" Reclosable Fastener SJ3550/51/52, SJ3571/72 3M" Adhesive Transfer Tape 468MP, 9472LE 3M" Double Coated Tape 9832, 9500PC	3M" VHB" Tape *4941, *5952, *RP+100GP 3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100" 3M" Hot Melt Adhesive 3748, 3764 3M" Reclosable Fastener SJ3540/41/42, SJ3526N/27N 3M" Adhesive Transfer Tape 9472LE, 9485PC 3M" Double Coated Tape 9832, 9500PC	■ 3M" Hot Melt Adhesive 3764, 3792 ■ 3M" Scotch-Weld" PUR Adhesive EZ25150
Glass			3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP100 Plus Clear 3M" Hot Melt Adhesive 3792 3M" Reclosable Fastener SJ3560/61/62, SJ3571/72 3M" Adhesive Transfer Tape 468MP, F9473PC 3M" Double Coated Tape 9500PC	3M" VHB" Tape 4941,* 5952, RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP100 Plus 3M" Hot Melt Adhesive 3748, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150 3M" Reclosable Fastener SJ3550/61/52, SJ3571/72 3M" Adhesive Transfer Tape 468MP, 9485PC 3M" Double Coated Tape 9500PC	3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100* 3M" Hot Melt Adhesive 3748, 3764 3M" Reclosable Fastener SJ3540/41/42, SJ3526N/27N 3M" Adhesive Transfer Tape 9472LE, 9485PC 3M" Double Coated Tape 9500PC	■ 3M" Hot Melt Adhesive 3792 ■ 3M" Scotch-Weld" PUR Adhesive EZZ50120, EZ250150
Plastics: HSE, MSE				3M" VHB" Tape 4941,* 5952,* RP+100GP 3M" Scotch-Weld" Structural Adhesive DP8405NS 3M" Scotch-Weld" Instant Adhesive PR100 3M" Hot Melt Adhesive 3748, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150, EZ250030 3M" Reclosable Fastener SJ3550/51/52, SJ3571/72 3M" Adhesive Transfer Tape 468MP, 9472LE 3M" Double Coated Tape 9500PC, 9832	3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Sootch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100* 3M" Hot Melt Adhesive 3748, 3764 3M" Reclosable Fastener SJ3540/41/42, SJ35260/127N 3M" Adhesive Transfer Tape 9472LE, 9485PC 3M" Double Coated Tape 9500PC, 9832	■ 3M" Hot Melt Adhesive 3764, 3792 ■ 3M" Scotch-Weld" PUR Adhesive EZ250150
Plastics: LSE					3M" VHB" Tape 4941,* 5952,* RP+100GP* 3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Scotch-Weld" Instant Adhesive PR100* 3M" Hot Melt Adhesive 3748, 3764 3M" Reclosable Fastener SJ3540/41/42, SJ3526N/27N 3M" Adhesive Transfer Tape 9472LE, 9485PC 3M" Double Coated Tape 9500PC	3M" Hot Melt Adhesive 3764, 3792 3M" Scotch-Weld" PUR Adhesive EZ250150
Wood	mers may also be required in so					3M <sup>™</sup> Hot Melt Adhesive 3792 3M <sup>™</sup> Scotch-Weld <sup>™</sup> PUR Adhesive EZ250120, EZ250060

<sup>\*</sup>Primers may also be required in some cases. See specific product pages for primer details.

# For 3M™ VHB™ Tape applications in the Window and Door market, refer to page 78 for a selection of products.

This guide lists products that are commonly used for this specific application. It is important that the customer evaluates these suggested products in their specific application.

### What are Gasket Attachment Assemblies?

Gaskets are used in multiple markets, such as electronics, transportation, fluid handling equipment and appliance.



**Casketing:** Attachment of a substrate typically, foam, rubber or paper that acts as an interface or seal between two surfaces. 3M offers solutions for attaching preformed gaskets, and also solutions which can replace gaskets or bond and seal simultaneously. **Examples include air and liquid filters, fluid handling equipment, heat exchangers and ball joints.** 

# Possible Adhesive or Tape Requirements:

- Easy and fast to apply gaskets
- Resist fluids
- High adhesion to foams and rubber

### **Best 3M Solutions for Gasket Assemblies**



### **3M**™ **VHB**™ **Tapes** (pg 72–79)

High-strength bonding tapes that can be die-cut into a variety of shapes to replace rubber or foam gaskets, providing an instant, simple solution. Their closed-cell construction provides a watertight barrier between flat parts.



### 3M™ Scotch-Weld™ Instant Adhesives (pg 37–39)

One part solvent-free cyanoacrylate (CA) adhesive that reaches handling strength in 5–30 seconds. Best for small very tight bondlines (<10cm2). Commonly used on rubbers and plastics.



### ■ 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Gasket Makers (pg 41)

One-part anaerobic adhesives can be applied as a curing liquid gasket between complex metal shapes, replacing pre-formed gaskets.



### **3M™ Contact and Spray Adhesives** (pg 52–63)

Solvent and water based adhesives can be sprayed, brushed or roll applied. Very fast, easy and economical coverage of multiple substrates, irregular shapes and mild textures.



### **3M™ Adhesive Transfer Tapes** (pg 87–92)

Can be pre-applied to gasketing material which is then die-cut to provide parts. These products provide instant adhesion to flat, untextured substrates.



#### **3M™ Double Coated Tapes** (pg 81–85)

Can be pre-applied to gasketing material which is then die-cut to provide parts. These products provide instant adhesion.

### **Performance Factors for Gasket Assemblies**


All 3M technologies in the table below are commonly used in gasket attachment applications. Use the table below as a relative comparison of product performance.

Attribute	3M <sup>™</sup> VHB <sup>™</sup> Tapes	3M <sup>™</sup> Scotch-Weld <sup>™</sup> Instant Adhesives	3M™ Scotch-Weld™ Gasket Makers	3M™ Contact and Spray Adhesives	3M™ Adhesive Transfer Tapes	3M <sup>™</sup> Double Coated Tapes
High Strength and Rubber Bonding	N/A	Best	N/A	Better	Good	Good
Temperature and Solvent Resistance	Best	Good	Best	Best	Best	Best
Ease of Application	Best	Better	Better	Good	Best	Best
Rate of Strength Build	Best	Best	Good	Best	Best	Best

### **Gasket Attachment Assembly Solutions**

+	Metal	Glass	Paint	Plastics: HSE	Plastics: LSE
Rubber (EPDM, Santoprene®)	3M" Scotch-Weld" Instant Adhesive PR100* ■ 3M" Contact and Spray Adhesive 4799 ■ 3M" Adhesive Transfer Tape 468MP*, 950 ■ 3M" Double Coated Tape 9832	■ 3M" Contact and Spray Adhesive 4799 ■ 3M" Adhesive Transfer Tape 468MP", 950 ■ 3M" Double Coated Tape 9832	3M" Scotch-Weld" Instant Adhesive PR100*  ■ 3M" Contact and Spray Adhesive 4799  ■ 3M" Adhesive Transfer Tape 468MP*, 950  ■ 3M" Double Coated Tape 9832	3M™ Scotch-Weld™ Instant Adhesive PR100*  3M™ Contact and Spray Adhesive 4799  3M™ Adhesive Transfer Tape 468MP*, 950  3M™ Double Costed Tape 9832	3M" Scotch-Weld" Instant Adhesive PR100*  3M" Contact and Spray Adhesive 4799  3M" Adhesive Transfer Tape 9472LE*, 950  3M" Double Coated Tape 9832
Silicone Gaskets	3M" Scotch-Weld" Instant Adhesive PR100* 3M" Scotch-Weld" Gasket Maker GM18 replace gasket 3M" Adhesive Transfer Tape 91022 3M" Double Coated Tape 9731, 96042	■ 3M* Adhesive Transfer Tape 91022 ■ 3M* Double Coated Tape 9731, 96042	3M° Scotch-Weld° Instant Adhesive PR100* ■ 3M° Adhesive Transfer Tape 91022 ■ 3M° Double Coated Tape 9731, 96042	3M™ Scotch-Weld™ Instant Adhesive PR100*  3M™ Adhesive Transfer Tape 91022  3M™ Double Coated Tape 9731, 96042	3M" Scotch-Weld" Instant Adhesive PR100* ■ 3M" Adhesive Transfer Tape 91022 ■ 3M" Double Coated Tape 9731, 96042
Neoprene	3M <sup>™</sup> Scotch-Weld <sup>™</sup> Instant Adhesive PR100*  3M <sup>™</sup> Adhesive Transfer Tape 6035PC, 950  3M <sup>™</sup> Double Coated Tape 9832	■ 3M" Contact and Spray Adhesive 1300 ■ 3M" Adhesive Transfer Tape 6035PC, 950 ■ 3M" Double Coated Tape 9832	3M" Scotch-Weld" Instant Adhesive PR100*  3M" Contact and Spray Adhesive 1300  3M" Adhesive Transfer Tape 6035PC, 950  3M" Double Coated Tape 9832	3M* Scotch-Weld* Instant Adhesive PR100* 3M* Contact and Spray Adhesive 1300 3M* Adhesive Transfer Tape 6035PC, 950 3M* Double Coated Tape 9832	3M" Scotch-Weld" Instant Adhesive PR100*  3M" Contact and Spray Adhesive 90  3M" Adhesive Transfer Tape 6035PC, 950  3M" Double Coated Tape 9832
Nylon	3M" Scotch-Weld" Instant Adhesive PR100 3M" Adhesive Transfer Tape 9472LE	■ 3M* Contact and Spray Adhesive 1099 ■ 3M* Adhesive Transfer Tape 9472LE	3M" Scotch-Weld" Instant Adhesive PR100  3M" Contact and Spray Adhesive 1099  3M" Adhesive Transfer Tape 9472LE	3M* Scotch-Weld* Instant Adhesive PR100 ■ 3M* Contact and Spray Adhesive 1099 ■ 3M* Adhesive Transfer Tape 9472LE	3M" Scotch-Weld" Instant Adhesive PR100*  3M" Contact and Spray Adhesive 90  3M" Adhesive 97  Tape 9472LE
PTFE	3M <sup>∞</sup> Scotch-Weld <sup>∞</sup> Instant Adhesive PR100* ■ 3M <sup>∞</sup> Scotch-Weld <sup>∞</sup> Gasket Maker GM18 replace gasket ■ 3M <sup>∞</sup> Adhesive Transfer Tape 950	■ 3M* Adhesive Transfer Tape 9472LE	3M" Scotch-Weld" Instant Adhesive PR100* ■ 3M" Adhesive Transfer Tape 9472LE	■ 3M* Scotch-Weld* Instant Adhesive PR100* ■ 3M* Adhesive Transfer Tape 9472LE	3M" Scotch-Weld" Instant Adhesive PR100* ■ 3M" Adhesive Transfer Tape 9472LE

 $<sup>{}^\</sup>star \text{Primers may also be required in some cases. See specific product pages for primer details.}$ 





3M™ VHB™ Tape can replace gaskets on many substrates listed in the chart. 3M™ Scotch-Weld™ Gasket Makers are suitable to replace gaskets in metal to metal applications.





This guide lists products that are commonly used for this specific application. It is important that the customer evaluates these suggested products in their specific application.

# What is Sealing of Assemblies? What is Potting and Encapsulating of Assemblies?





Sealing and potting exists in multiple markets, such as transportation, metalworking, electronics, electrical, construction and MRO.

**Sealing:** Tape or sealant is applied over a seam to prevent fluid ingress or fluid egress. **Examples include roof seams on vehicles, seams on metal enclosures and pipe sealing.** 

**Potting and Encapsulating:** Adhesive flows over and around a component or fills in a chamber to protect components therein. **Examples include heavy duty electrical cords and connectors, electronics in plastic cases, circuit boards and concrete repair.** 

### Possible Adhesive or Tape Requirements:

- Highly elongating/flexible
- Fast cure for painting
- Durability

### Best 3M Solutions for Sealing, Potting and Encapsulating



### **3M™ Scotch-Weld™ Structural Adhesives** (pg 18–35)

Acrylic, epoxy and urethane structural adhesives are available in a variety of cure times and flow profiles for potting and encapsulation. Available in both rigid and flexible formulations.



### 3M™ Hot Melt Adhesives (pg 45-51)

Extrudable, 100% solid, thermoplastic resins designed for potting and encapsulating electrical components.



### 3M™ Adhesive Sealants (pg 64–68)

Acrylic, polyurethane and nitrile and hybrid are one component sealing technologies. Can be extruded in any shape on a substrate and are non-sag to fill gaps. Some formulations can be painted wet.



### 3M™ Extreme Sealing Tapes (pg 80)

Provides instant sealing and paint-ability when applied over seams or gaps. Conformable over rivets.

### Performance Factors for Sealing, Potting and Encapsulating

All 3M technologies in the table below are commonly used in sealing, potting and encapsulation applications. Use the table below as a relative comparison of product performance.

Attrib	pute	3M™ Scotch-Weld™ Structural Adhesives	3M <sup>™</sup> Hot Melt Adhesives	3M <sup>™</sup> Adhesive Sealants	3M™ Extreme Sealing Tapes
	Flexibility	N/A	N/A	Best	Best
Sealing	Ease of Application	N/A	N/A	Best	Better
Sea	Time to Paint (or handle part)	N/A	N/A	Good	Best
	Immediate Rework	N/A	N/A	Best	Good
_ 6c	Temperature and Solvent Resistance	Best	Better	Good	N/A
ig and sulating	Time to Paint (or handle part)	Good	Best	Good	N/A
Potting Encapsul	Flowability*	Best	Better	Good	N/A
ш	Adhesion to Substrates	Best	Better	Good	N/A

<sup>\*3</sup>M° Scotch-Weld® Structural Adhesives and 3M° Hot Melt Adhesives are used for potting and encapsulating where their flow and conformability allow them to fill into, or dome over, complex shapes. 3M° Adhesive Sealants are thick and can be dispensed into wide vertical or horizontal gaps, as well as over seams. 3M° Extreme Sealing Tape seals over seams and narrow gaps but does not flow into gaps. It can conform over low profile objects such as rivet heads.

### Sealing, Potting and Encapsulating Assembly Solutions

+	Metals (Aluminum, Steel, Stainless, Galvanized)	Paints (Powder Coat, Painted Metal, Composite Panel)	Glass	Plastics: HSE, MSE (ABS, Acrylic, Polycarbonate, Nylon)	Plastics: LSE (Polypropylene, Polyethylene)
Metals	3M" Scotch-Weld" Structural Adhesive 2216, DP270 3M" Hot Melt Adhesive 3797, 3748 VO 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	3M" Scotch-Weld" Structural Adhesive 2216, DP604NS 3M" Hot Melt Adhesive 3797, 3748 VO 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	3M" Scotch-Weld" Structural Adhesive DP125 Gray, DP100 Plus Clear 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	a 3M" Scotch-Weld" Structural Adhesive 2216, DP604NS a M" Hot Melt Adhesive 3797, 3748 VO a 3M" Adhesive Sealant 540*, 740* a M" Extreme Sealing Tape 4411B, 4411N, 4411G	3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Hot Melt Adhesive 3797, 3748 VO 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B*, 4411N*, 4411G*
Paints		3M" Scotch-Weld" Structural Adhesive 2216, DP604NS 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	■ 3M* Scotch-Weld* Structural Adhesive DP125 Gray, DP100 Plus Clear ■ 3M* Adhesive Sealant 540*, 740* ■ 3M* Extreme Sealing Tape 4411B, 4411N, 4411G	3M" Scotch-Weld" Structural Adhesive 2216, DP604NS 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	■ 3M" Scotch-Weld" Structural Adhesive DP8010 Blue ■ 3M" Adhesive Sealant 540*, 740* ■ 3M" Extreme Sealing Tape 4411B*, 4411N*, 4411G*
Glass			■ 3M* Scotch-Weld* Structural Adhesive DP125 Gray, DP100 Plus Clear 3M* Adhesive Sealant 540*, 740* ■ 3M* Extreme Sealing Tape 4411B, 4411N, 4411G	3M" Scotch-Weld" Structural Adhesive DP125 Gray, DP100 Plus Clear 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	■ 3M° Scotch-Weld° Structural Adhesive DP8010 Blue ■ 3M° Adhesive Sealant 540*, 740* ■ 3M° Extreme Sealing Tape 4411B*, 4411N*, 4411G*
Plastics: HSE, MSE				■ 3M" Scotch-Weld" Structural Adhesive 2216, DP604NS 3M" Hot Melt Adhesive 3797, 3748 VO ■ 3M" Adhesive Sealant 540*, 740* ■ 3M" Extreme Sealing Tape 4411B, 4411N, 4411G	■ 3M" Scotch-Weld" Structural Adhesive DP8010 Blue ■ 3M" Hot Melt Adhesive 3797, 3748 VO ■ 3M" Adhesive Sealant 540*, 740* ■ 3M" Extreme Sealing Tape 4411B*, 4411N*, 4411G*
Plastics: LSE					3M" Scotch-Weld" Structural Adhesive DP8010 Blue 3M" Hot Melt Adhesive 3797, 3748 VO 3M" Adhesive Sealant 540*, 740* 3M" Extreme Sealing Tape 4411B*, 4411N*, 4411G*

 $<sup>{}^{\</sup>star}$ Primers may also be required in some cases. See specific product pages for primer details.







This guide lists products that are commonly used for this specific application. It is important that the customer evaluates these suggested products in their specific application.

# Substrates and Adhesion — A Surface Phenomenon, So Know Surfaces Well.

Adhesive attaches to the surfaces of two substrates, unlike a process that fuses the substrates into a unified whole such as welding or solvent activation of plastics. When selecting a 3M adhesive or tape, surface condition must be considered: roughness, smoothness, porosity, coated, uncoated, cleanliness, flexibility size of part and surface energy of part.

Adhesive paste, for example, flows readily into a rough surface for improved effective adhesion. Flexible materials such as paper or thin gauge metal can be bonded with thin adhesive transfer tape. Large rigid parts with smooth clean surfaces can be bonded with a variety of 3M product ranging from double-coated foam tapes to two-part structural adhesives. Some plastics have plasticizers which migrate to the surface and degrade the bond over time, so plasticizer-resistant adhesive or tape is essential. If the surface has been powder coat painted, the coating is the bonding surface rather than the substrate, and you would want to consider a 3M tape or adhesive developed specifically for the surface.


Surface energy ranges from high to low. To illustrate the concept of surface energy, think of water on an unwaxed hood of a car. The unwaxed hood has high surface energy and the water on the hood flows into puddles. In comparison, a waxed hood has low surface energy and the water beads up rather than flow out. Similar to water, adhesive on a high surface energy flows and "wets out" the surface. "Wetting out" is required to form a strong bond.

As a rule of thumb, the higher the surface energy, the greater the strength of the adhesion.

Specially formulated adhesives are available for low surface energy surfaces. The following illustrations and surface rankings give an idea of the relative surface energy.

Regardless of surface energy, the substrate must be unified, dry and clean to maximize adhesive contact.

### **Surface Energy Chart**



### **Adhesives and Sealants**

# The best formulas deliver the best performance.

### **Powerful Adhesive and Sealant Solutions**

3M offers a wide range of innovative adhesives and sealants designed for industrial markets. High quality, precision formulations with proven performance provide reliable, long-term durability for a variety of applications, indoors and out.



# Design with Confidence. Build to Last.

In today's world, successful new products demand advancements in design, manufacturing processes and end-use performance. Industrial engineering and design professionals around the world depend on  $3M^{\text{\tiny M}}$  Scotch-Weld<sup> $\text{\tiny M}$ </sup> Structural Adhesives to help them design beyond the limits of mechanical fasteners to create next generation products.


# Trusted Innovations from Aerospace to Office Space

With over 60 years of experience developing innovative structural adhesives for aerospace, automotive and hundreds of other industries, 3M delivers the solutions you can trust. Our advanced formulations create durable bonds, even on challenging materials or in extreme conditions.

### 3M Global Service and Support

3M supports our customers with the testing, technology, and training needed to create better products. Our world-wide support staff has the experience you can rely on for everything from structural adhesive selection to process improvement.

Leverage 3M's proven selection of structural adhesives, deep industry expertise, and technical support to your advantage. Design with Confidence. Build to Last.



# 3M™ Scotch-Weld™ Structural Adhesives are Transforming the Way Engineers Think

### Advancing Design, Process and Performance

The benefits of designing and building products with 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Structural Adhesives help drive product success. Eliminating mechanical fasteners provides a wide range of benefits for all stages of product development.



**Improve Aesthetics:** Improve product appearance with invisible joints and smoother bond lines, reduce weight and noise, enhance corrosion and fatigue resistance, and more.

**Freedom of Design:** Join composites to metal, build with hard-to-bond plastics, and use thinner, lighter weight materials.



**Enhance Productivity:** Reduce labor and material costs, build faster with minimal surface prep and match cure rates to your process needs.

**Accurate and Easy:** Dispense by hand or with automated equipment, and choose from a wide range of viscosities and flow rates.



**Strong, Flexible Bonds:** Adhesives bond and seal simultaneously, eliminate stress concentration and absorb shock and vibration for durable bonds.


**Increased Durability:** Resist chemicals, environment, galvanic corrosion, fatigue, and material separation along edges or corners.

### Simplifying Adhesive Decisions for Your Application

The following questions will help you narrow adhesive choices to a few possibilities for evaluation.

#### Q: What materials will be bonded?

A: Structural adhesives work by adhering to the top surface of the bonded parts, so it's important to know the exact material and condition on those surfaces. For metals, will the adhesive be applied to bare metal, or will there be a paint



or coating on the surface? For plastics, exactly which base resin? Could there be residual release agents on the surfaces used for mold release?

#### Q: What is the preferred cure speed?

A: The chosen structural adhesive must have enough work life (open time, pot life) to allow proper mixing and application of the adhesive and assembling of the bonded parts. Smaller assemblies or shorter cycle time production



processes may be able to use a faster curing adhesive with a work life of only five minutes or less, while larger assemblies that require alignment and clamping will probably need a work life of 20 minutes or more.

### Q: What surface preparation will be required?


A: Structural adhesives generally prefer clean, rough, dry surfaces for highest bond strength. This typically means either light abrasion and solvent cleaning of the surface, or solvent cleaning followed by chemical etching or applying a primer.



Adhesion tests should be performed to determine the adequate surface preparation for a specific application.

### Q: What types of joints are best for structural adhesives?


A: Joint designs that put the adhesive bond under shear, tension, or compression forces will provide the highest strength. Designs that tend to apply peel or cleavage forces to the adhesive, where the applied stresses are not distributed over



the entire bond area, will have lower bond strength, but the bond may still be sufficient for the needs of the application. In addition, optimum bond line thickness typically ranges from 0.005" to 0.020". The adhesive qualification process should always include testing of prototype assemblies to ensure the adhesive will provide enough performance.

### Q: How are structural adhesives used and applied?


A: Structural adhesives come in many forms, including low viscosity liquids and non-sag pastes, one- and two-component formulations, short and long work lives, and various package sizes and shapes. Most two-part structural



adhesives are available in both bulk containers and convenient, easy-to-use cartridge mixing systems.

# Q: What are the general characteristics of the different types of structural adhesives?

A: All structural adhesives provide at least 1,000 psi of overlap shear strength to aluminum, but the different adhesive chemistries have various properties.



**Epoxy adhesives** come in both two-part adhesives (that cure upon mixing the two components) and one-part adhesives (that cure with temperature). They generally have the highest strength and overall performance. They also provide the best resistance to high temperatures, solvents and outdoor weathering. They adhere well to metals, woods and concrete, and the flexible epoxy adhesives also bond to some plastics and rubbers. Epoxy adhesives usually require clean, abraded surfaces to obtain maximum bond strength.


Acrylic adhesives are two-part adhesives that provide excellent bond strength and durability, although slightly lower than epoxy adhesives. However, they have several features that make them easier to use in many applications and manufacturing processes. These benefits include a much faster cure speed, higher tolerance for oily or unprepared bonding surfaces and the ability to bond a wide variety of materials, including nearly all plastics. Newer acrylic adhesive formulations are room temperature stable with a long shelf life, and some have much lower odor than regular acrylic adhesives.

**Urethane adhesives** are two-part adhesives that are relatively flexible when cured, and therefore tend to have excellent impact resistance and good adhesion to most plastics. They also bond well to woods, concrete and rubbers, but they tend to have reduced resistance to solvents and high temperatures. Uncured adhesive components are sensitive to moisture.


**Cyanoacrylate adhesives** (instant adhesives) are one-component, lower viscosity liquids that cure extremely quickly with just contact pressure and surface moisture. They adhere well, with thin bond lines, to plastics, metals and rubbers. With the use of primers, they can also adhere to low surface energy plastics and elastomers. They tend to have low flexibility, peel strength and impact resistance compared to other structural adhesives. They are generally used for applications such as gasket bonding and smaller assemblies.

Anaerobic adhesives are one-part adhesives that cure on active metal surfaces when oxygen gets excluded from the bond line. These products keep your factory running efficiently, reducing maintenance and leakage. They do not bond well to glass, plastics or rubbers, and are primarily used for applications such as locking threads and sealing pipe connections.


**PUR adhesives** (Polyurethane-reactive adhesives) are one-part adhesives that apply like a hot melt, but cure with ambient moisture for near structural strength bonds. Fast set times and build strength over the next 24–48 hours can reach as much as 1,000 psi in overlap shear strength. They are flexible and resistant to temperature extremes and most solvents. Most commonly used in bonds where at least one substrate contains or transmits moisture (such as wood or plastic).




Tensile is pull exerted equally over the entire joint. Pull direction is straight and away from the adhesive bond.



Shear is pull directed across the adhesive, forcing the substrates to slide over each other.



Cleavage is pull concentrated at one edge of the joint, exerting a prying force on the bond. The other edge of the joint is theoretically under zero stress.



Peel is concentrated along a thin line at the edge of the bond where one substrate is flexible.

# Key markets and applications for 3M™ Scotch-Weld™ Structural Adhesives



### **Sporting Goods**

### **Key Features and Benefits**

- Excellent impact resistance of high stressed bonds
- High strength for small joints
- High strength bonding of rubber, composites and metals to each other

Key Products DP420NS, DP8010, DP8710NS, PR100, DP8910NS







### **Specialty Vehicle**

### **Key Features and Benefits**

- Weight reduction
- High strength
- Vibration and fatigue resistance

Key Products DP6330NS, DP8410NS, DP8610NS, LSB60NS, TL42







### Signage

### **Key Features and Benefits**

- One adhesive to bond all of your substrates
- Strong formulations and thin bond lines
- Weather resistance
- UL recognition

Key Products DP100 Plus, DP8405NS, DP8710NS, DP8805NS, PR Gel







### Metalworking

### **Key Features and Benefits**

- High strength and durability
- Reduced surface preparation before bonding, and no grinding after bonding
- Save weight and improve appearance with adhesives instead of welds or rivets









### **Electronics**

### **Key Features and Benefits**

- Low halogen formulations available to meet customer needs
- Fast cure to speed production
- Protect sensitive electrical connections from the environment





Key Products DP270, DP420LH, DP8705NS, DP8910NS, TS230, PR100, 6101



### **Appliance**

### **Key Features and Benefits**

- Simplify operations by bonding after powdercoating
- Eliminate the challenge of bonding rigid to flexible substrates
- Noise damping
- Reduce complexity-bond and seal glass to metal in one step
- Key Products
   DP125, DP6310NS, DP8610NS, DP8710NS, DP8810NS, TS230, TL42







### **Aerospace**

### **Key Features and Benefits**

- Available in UL94 or FST compliant options
- Strong, yet flexible bond lines

Key Products 2216, DP100FR, DP420NS, DP640, TL71







### Plastic, Composite & Rubber

### **Key Features and Benefits**

- Bonding of low surface energy plastics without priming
- Impact resistant composite and nylon bonding





Key Products DP100 Plus, DP6310NS, DP8010, DP8405NS, DP8810NS, DP8910NS, TS230, PR100

### 3M™ Scotch-Weld™ Adhesives Selector Guide

Step 1: Select most difficult substrate. Step 2: Determine key attribute. Step 3: Select product family.



### **Structural Adhesive Families**

**Rigid Epoxy Adhesives** — Higher tensile strength at lower elongations for greater long-term holding power. Mostly used for rigid substrates (metals) with high static loads.

**Flexible Epoxy Adhesives** — Lower tensile strength at higher elongations for greater capability to withstand differential movement of bonded parts; higher peel strength and higher adhesion to most plastics.

**Toughened Epoxy Adhesives** — Higher tensile strength at lower elongations for fatigue resistance; best suited for dynamic stresses. They have long-term holding power, higher peel strength, and exceptional higher resistance against shock, vibration and impact loads. Lower adhesion to most thermoplastics.

**Heat-cured Epoxy Adhesives** — One-component, rigid adhesives with outstanding strength at elevated temperatures. These adhesives require a thermal cure, typically around 250–350°F (120–180°C) for 40–60 minutes.


**MMA Acrylic Adhesives** — Provides greater adhesion to a wide variety of materials including most plastics and paint systems, are tolerant of many surface contaminations. High impact resistance for metal bonds.

**Low Odor Acrylic Adhesives** — Less odor than typical acrylic adhesives and faster rate of strength build than most two-part structural adhesives. Excellent adhesion to a variety of materials, including plastics and paint systems. They provide high impact resistance for plastic bonds; and are tolerant of many surface contaminations.

**LSE and Nylon Bonding Acrylic Adhesives** — Outstanding adhesion to polyolefin materials such as polypropylene, polyethylene and TPO without surface treatment.

**Semi-rigid Urethane Adhesives** — Higher tensile modulus and lower elongation capability, with greater long-term holding power.

**Flexible Urethane Adhesives** — Lower tensile modulus and higher elongation capability. Excellent adhesion to most plastics.



Step 1: Select most difficult substrate. Step 2: Determine key attribute. Step 3: Select product family.

### **Instant Adhesive Families**

**Plastic & Rubber (PR) Instant Adhesives** bond to the widest variety of materials, have an extremely fast cure speed, and come in a wide range of viscosity.

**Surface Insensitive (SI) Instant Adhesives** cure even on acidic surfaces (such as wood, paper, leather, and ceramic); these adhesives have a slower cure speed than traditional instant adhesives.

**Low Odor (LO) Instant Adhesives** provide a reduced blooming effect for applications that require an improved appearance.

**General Purpose (EC) Instant Adhesives** are slightly less expensive products that have lower strength and impact resistance compared to traditional instant adhesives.

**Super Fast (SF) Instant Adhesives** provide the fastest rate of cure speed for most applications.

**Rubber Toughened (RT) Instant Adhesives** can be used for applications that require improved impact strength or vibration resistance; preferred for applications bonding two rigid materials together.

**Metal (MC) Instant Adhesives** provide performance on metal substrates.

**Engineered Grade (EG) Instant Adhesives** provide excellent overall performance for most applications.

### **Anaerobic Adhesive Families**

**Threadlockers (TL)** hold screws and other threaded fasteners in place to prevent loosening from shock, vibration, and thermal expansion and contraction; these adhesives replace lock washers and nylon-insert nuts.

### **PUR Adhesive Families**

**Wood PUR** — Higher shear strength at lower elongations for long term holding power. Mostly used for rigid wood substrates and some plastics.

**Plastic PUR** — Higher impact strength, elongation and flexibility for greater capacity to withstand movement of bonded parts. Higher adhesion to most plastics, glass and aluminum.

### **Substrate Selector**

Step 1: Select substrate. Step 2: Determine key attribute. Step 3: Select product (see definitions below).

		Plastic/Pain	ts/Coatings			Metals		Oily I	Metals	Comp	oosites		e/Stone/ cs/Glass	
		Low Surface	General		Temperature and Solvent		Other	Stainless Steel &	Other	Fiberglass/				
itings	Low Surface Energy	Energy  LSE Acrylic* Plastic & Rubber CA	Purpose LSE Acrylic* Plastic & Rubber CA	Rubber Plastic & Rubber CA*	Resistant N/A	Aluminum LSE Acrylic	Metals LSE Acrylic	Aluminum LSE Acrylic	Metals LSE Acrylic	SMC LSE Acrylic Toughened CA*	Epoxy LSE Acrylic Toughened CA*	Indoor LSE Acrylic	Outdoor LSE Acrylic	Wood LSE Acrylic Surface Insensitive CA*
Plastic/Paints/Coatings	General Purpose	LSE Acrylic* Plastic & Rubber CA	LO Acrylic MMA Acrylic Plastic PUR Flexible Epoxy Plastic & Rubber CA	Plastic & Rubber CA* Plastic PUR	Toughened Epoxy Flexible Epoxy	LO Acrylic MMA Acrylic Flexible Epoxy Plastic PUR Plastic & Rubber CA	DP8407NS Toughened Epoxy Flexible Epoxy Plastic PUR Plastic & Rubber CA	LO Acrylic MMA Acrylic	DP8407NS	Semi-rigid Urethane MMA Acrylic LO Acrylic Flexible Urethane Plastic PUR Toughened CA	Semi-rigid Urethane MMA Acrylic Flexible Epoxy Toughened Epoxy Plastic PUR Toughened CA	Flexible Epoxy Rigid Urethane Flexible Urethane Plastic PUR	Flexible Epoxy Flexible Urethane Plastic PUR	Wood PUR Flexible Epoxy Rigid Urethane Surface Insensitive CA
Rubber		Plastic & Rubber CA*	Plastic & Rubber CA* Plastic PUR	Plastic & Rubber CA*	N/A	Flexible Epoxy Plastic PUR	Flexible Epoxy Plastic PUR	N/A	N/A	Plastic & Rubber CA* Plastic PUR	Plastic & Rubber CA* Plastic PUR	Flexible Epoxy Plastic PUR	Flexible Epoxy Plastic PUR	Surface Insensitive CA* Plastic PUR Flexible Epoxy
	Temperature and Solvent Resistant	N/A	Toughened Epoxy Flexible Epoxy	N/A	Toughened Epoxy Flexible Epoxy	Toughened Epoxy Flexible Epoxy	One-part Heat-cured Epoxy Toughened Epoxy	Heat-cured Epoxy	Heat-cured Epoxy	Toughened Epoxy Flexible Epoxy Plastic PUR	Toughened Epoxy Flexible Epoxy Plastic PUR	Toughened Epoxy Flexible Epoxy	Flexible Epoxy	Toughened Epoxy Plastic PUR Flexible Epoxy
Metals	Stainless Steel & Aluminum	LSE Acrylic	LO Acrylic MMA Acrylic Flexible Epoxy Plastic PUR Plastic & Rubber CA	Plastic & Rubber CA* Plastic PUR	Toughened Epoxy Flexible Epoxy	LO Acrylic MMA Acrylic Toughened Epoxy Flexible Epoxy Rigid Epoxy Toughened CA	Heat-cured Epoxy Toughened Epoxy	LO Acrylic MMA Acrylic	DP8407NS Heat-cured Epoxy	Semi-rigid Urethane MMA Acrylic LO Acrylic Toughened Epoxy Plastic PUR Toughened CA	Semi-rigid Urethane Toughened Epoxy MMA Acrylic LO Acrylic Plastic PUR Toughened CA	Toughened Epoxy Flexible Epoxy	Flexible Epoxy	Plastic PUR Toughened Epoxy Rigid Epoxy Flexible Epoxy Surface Insensitive CA
	Other Metals	LSE Acrylic	DP8407NS Toughened Epoxy Flexible Epoxy Plastic PUR Plastic & Rubber CA	Plastic & Rubber CA* Plastic PUR	Heat-cured Epoxy Toughened Epoxy	Heat-cured Epoxy Toughened Epoxy	Toughened Epoxy Flexible Epoxy Heat-cured Epoxy DP810	DP8407NS Heat-cured Epoxy	DP8407NS Heat-cured Epoxy	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	Toughened Epoxy Flexible Epoxy Heat-cured Epoxy Plastic PUR	Toughened Epoxy Heat-cured Epoxy	Flexible Epoxy	Plastic PUR Toughened Epoxy
Metals	Stainless Steel & Aluminum	LSE Acrylic	MMA Acrylic	N/A	Heat-cured Epoxy	MMA Acrylic	DP8407NS Heat-cured Epoxy	MMA Acrylic	DP8407NS	MMA Acrylic LO Acrylic	MMA Acrylic LO Acrylic Heat-cured Epoxy	N/A	N/A	N/A
Oily	Other Metals	LSE Acrylic	DP8407NS	N/A	Heat-cured Epoxy	DP8407NS Heat-cured Epoxy	DP8407NS Heat-cured Epoxy	DP8407NS	DP8407NS Heat-cured Epoxy	DP8407NS	Heat-cured Epoxy	N/A	N/A	N/A
Composites	Fiberglass/ SMC	LSE Acrylic Toughened CA*	Semi-rigid Urethane MMA Acrylic LO Acrylic Flexible Urethane Plastic PUR Toughened CA	Plastic & Rubber CA* Plastic PUR	Toughened Epoxy Flexible Epoxy Plastic PUR	Semi-rigid Urethane MMA Acrylic LO Acrylic Toughened Epoxy Plastic PUR Toughened CA	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	MMA Acrylic LO Acrylic	DP8407NS	Semi-rigid Urethane MMA Acrylic LO Acrylic Toughened Epoxy Flexible Epoxy Plastic PUR Toughened CA	Semi-rigid Urethane Toughed Epoxy Flexible Epoxy Plastic PUR Toughened CA	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	Semi-rigid Urethane Flexible Epoxy Flexible Urethane Plastic PUR	Semi-rigid Urethane Toughened Epoxy Rigid Urethane Flexible Epoxy Plastic PUR
Comp	Ероху	LSE Acrylic Toughened CA*	Semi-rigid Urethane MMA Acrylic Flexible Epoxy Toughened Epoxy Plastic PUR Toughened CA	Plastic & Rubber CA* Plastic PUR	Toughened Epoxy Flexible Epoxy Plastic PUR	Semi-rigid Urethane Toughened Epoxy MMA Acrylic LO Acrylic Plastic PUR Toughened CA	Toughened Epoxy Flexible Epoxy Heat Cured Epoxy Plastic PUR	MMA Acrylic LO Acrylic Heat Cured Epoxy	Heat Cured Epoxy	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR Toughened CA	Toughened Epoxy Flexible Epoxy Plastic PUR Toughened CA	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	Semi-rigid Urethane Flexible Epoxy Plastic PUR	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR
Concrete/Stone/Ceramics/Glass	Indoor	LSE Acrylic	Flexible Epoxy Rigid Urethane Flexible Urethane Plastic PUR	Flexible Epoxy Plastic PUR	Toughened Epoxy Flexible Epoxy	Toughened Epoxy Flexible Epoxy	Toughened Epoxy Heat Cured Epoxy	N/A	N/A	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	Toughened Epoxy Flexible Epoxy Rigid Urethane Flexible Urethane	Flexible Epoxy Flexible Urethane	Flexible Epoxy Plastic PUR Flexible Urethane
Concrete/Stone	Outdoor	LSE Acrylic	Flexible Epoxy Flexible Urethane Plastic PUR	Flexible Epoxy Plastic PUR	Flexible Epoxy	Flexible Epoxy	Flexible Epoxy	N/A	N/A	Semi-rigid Urethane Flexible Epoxy Flexible Urethane Plastic PUR	Semi-rigid Urethane Flexible Epoxy Plastic PUR	Flexible Epoxy Flexible Urethane	Flexible Epoxy Flexible Urethane	Flexible Epoxy Plastic PUR Flexible Urethane
Wood		LSE Acrylic Surface Insensitive CA*	Wood PUR Flexible Epoxy Rigid Urethane Surface Insensitive CA	Wood PUR Surface Insensitive CA*	Toughened Epoxy Plastic PUR Flexible Epoxy	Wood PUR Toughened Epoxy Rigid Epoxy Flexible Epoxy Surface Insensitive CA	Wood PUR Toughened Epoxy	N/A	N/A	Semi-rigid Urethane Toughened Epoxy Rigid Urethane Flexible Epoxy Plastic PUR	Semi-rigid Urethane Toughened Epoxy Flexible Epoxy Plastic PUR	Flexible Epoxy Plastic PUR Flexible Urethane	Flexible Epoxy Plastic PUR Flexible Urethane	Wood PUR Rigid Epoxy Toughened Epoxy Rigid Urethane Surface Insensitive CA

**Bold = Best In Class Product** Light = Suggested Alternate Product \*With Primer

# **Coverage Guide**

### Approximate Coverages for 3M™ Scotch-Weld™ Adhesives in Duo-Pak Cartridges

Bead Size Dimension* inches (mm)	Linear ft./m per 37mL (2:1 Cart.)	Linear ft./m per 43mL (2:3 Cart.)	Linear ft./m per 45mL (10:1 Cart.)	Linear ft./m per 50mL (1:1 & Cart.)	Linear ft./m per 200mL (1:1 & 2:1 Cart.)	Linear ft./m per 400mL (1:1 & 2:1 Cart.)	Linear ft./m per 490mL (10:1 Cart.)	Linear ft./m per 295mL (1/10 gal. Cart.)
1/2 in. (12.7mm)	2 ft. (0.6m)	2 ft. (0.7m)	2 ft. (0.7m)	2.5 ft. (0.8m)	10 ft. (3m)	21 ft. (6m)	26 ft. (8m)	20 ft. (6m)
3/8 in. (9.5mm)	3.5 ft. (1m)	4 ft. (1m)	4 ft. (1m)	4.5 ft. (1m)	18 ft. (6m)	37 ft. (11m)	45 ft. (14m)	35 ft. (11m)
1/4 in. (6.4mm)	8 ft. (2m)	9 ft. (3m)	9 ft. (3m)	11 ft. (3m)	41 ft. (13m)	83 ft. (25m)	102 ft. (31m)	79 ft. (24m)
1/8 in. (3.2mm)	31 ft. (9m)	36 ft. (11m)	37 ft. (11m)	42 ft. (13m)	165 ft. (50m)	331 ft. (101m)	405 ft. (123m)	312 ft. (95m)
1/16 in. (1.6mm)	122 ft. (37m)	142 ft. (43m)	147 ft. (45m)	165 ft. (50m)	656 ft. (200m)	1,313 ft. (400m)	1,600 ft. (488m)	1,234 ft. (376m)

### Coverages per Gallon for Various Thicknesses of 100% Solids 3M Adhesives

#### Gal./1,000 ft<sup>2</sup> (L/1,000m<sup>2</sup>) **Wet Thickness** inches (mm) 3 ft<sup>2</sup> (0.1m<sup>2</sup>) 312 gal. (12,700L) 1/2 in. (12.7mm) 1/8 in. (3.2mm) 13 ft<sup>2</sup> (0.3m<sup>2</sup>) 78 gal. (3,175L) 1/16 in. (1.6mm) 26 ft<sup>2</sup> (0.6m<sup>2</sup>) 39 gal. (1,587L) 1/32 in. (0.8mm) 51 ft<sup>2</sup> (1m<sup>2</sup>) 20 gal. (794L) 25 mils (0.64mm) 64 ft<sup>2</sup> (1.5m<sup>2</sup>) 16 gal. (635L) 5 mils (0.13mm) 320 ft2 (8m2) 3 gal. (127L)

# Coverages per Gallon for Various Bead Sizes of 100% Solids 3M Adhesives

Bead Size Dimension* inches (mm)	Approx. lineal ft./gal. (m/L)	Approx. gal./1,000 lineal ft. (liter/1,000m)
1/2 in. (12.7mm)	196 ft. (16m)	5 gal. (63L)
3/8 in. (9.5mm)	350 ft. (28m)	3 gal. (36L)
1/4 in. (6.4mm)	785 ft. (63m)	1.3 gal. (16L)
1/8 in. (3.2mm)	3,130 ft. (252m)	0.3 gal. (4L)
1/16 in. (1.6mm)	12,420 ft. (1,000m)	0.1 gal. (1L)

<sup>\*</sup>Bead size is semi-circular bead with width equal to size noted and height at center of bead equal to 1/2 the width.

### Coverage Guide for 3M™ Scotch-Weld™ PUR Adhesives Approximate Coverage per Container (linear foot per container based on 1/8" dia. bead size)

1/10 Gallon Cartridge	2k Bag	5 Gallon Pail	55 Gallon Drum
250 ft. (76.2m)	1,650 ft. (502.9m)	13,500 ft. (41448m)	170,200 ft. (51576.9m)

# 3M™ Scotch-Weld™ Low Odor and MMA Acrylic Adhesives

3M's Low Odor and MMA Acrylic Adhesives are designed for all of your sign application needs. They provide excellent impact strength, high peel strength and greatly extended shelf life compared to ordinary structural adhesives.

With high structural strength, fast cure and environmental resistance, they are the first choice for the sign industry. DP8705NS, DP8710NS, DP8725NS, DP8405NS, DP8407NS, DP8410NS, DP8425NS, DP8610NS and DP8625NS



Note: The technical information and data on these pages should be considered representative or typical only and should not be used for specification purposes.



# Go-to products for Structural Bonding

### **High Strength and Metal Bonding**



Plastic and Multi-Material Bonding

Speed

# 3M™ Scotch-Weld™ Structural Adhesives (



### **3M<sup>™</sup> Scotch-Weld<sup>™</sup> Rigid Epoxies**

					).ke	ine dir	ing Roller of	e (nec)	р	rlap Shear: si (MPa)		
,,	Colori	<b>,</b>	io 8.A. ma	e steoler ins	work St. Cy	e Ster o	Roller 1	5 <sup>5</sup> /65°	( C)	(35,0)		
Product	Colory	Mixe	Agricus, Volation	Posting &	Appropriate	Tight Floati	ilmen 6	\$ ( 15° C)	£ 12 00 1,00	St. Site	J <sub>k</sub> c	Stock*
	ĺ						ĺ			48.5mL	00-638060-08994-1	7100148763
DP100 100	General									200mL	00-021200-87260-0	7100075490
Clear)	purpose;	1:1	13,000	5 min.	20 min.	2 (4)	900	1,500 (10)	300 (2)	400mL	00-021200-87261-7	7000121318
DP100 100 (Clear)	Rigid bonds					(4)	(0)	(10)	(2)	5 gal. pail A	00-021200-82345-9	7100086557
3										5 gal. pail B	00-021200-82344-2	7100086558
DP100FR										48.5mL	00-638060-08989-7	7100148760
100FR (Cream)	Flame retardant;	1:1	80.000	6 min.	20 min.	2	1,250	2,200	800	200mL	00-048011-56744-0	7000148268
( ·	UL94 V-0 rating	1:1	80,000	o min.	20 mm.	(4)	(9)	(15)	(6)	5 gal. pail A	00-048011-57230-7	7010366158
<b>(h)</b>										5 gal. pail B	00-048011-57229-1	7010366123
										48.5mL	00-638060-08974-3	7100148744
DP100NS 100NS	General purpose;	1:1	95.000	5 min.	20 min.	2	900	1,500	300	200mL	00-021200-87264-8	7100014024
(Translucent)	Non-sag	1.1	95,000	J 111111.	20 111111.	(4)	(6)	(10)	(2)	5 gal. pail A	0-00-21200-82257-5	7010367412
										5 gal. pail B	0-00-21200-82256-8	7010295308
										48.5mL	00-638060-08975-0	7100148745
DP270										200mL	00-021200-87836-7	7000121252
<b>270</b> (Black)	Rigid potting compound;	1:1	12.000	60 min.	3 hours	2	1,200	2,500	300	400mL	00-021200-87837-4	7100082565
(Diack)	Non-corrosive	1.1	12,000	00 111111.	o nours	(4)	(8)	(17)	(2)	Gallon kit	00-021200-82263-6	7000121253
•										5 gal. pail A	00-021200-82265-0	7000046463
										5 gal. pail B	00-021200-82264-3	7000046439
DP270										48.5mL	00-638060-08973-6	7100148730
<b>270</b> (Clear)	Rigid potting compound;	1:1	12.000	60 min.	3 hours	2	1,200	2,500	300	200mL	00-021200-87834-3	7100228179
(Glear)	Non-corrosive		12,000	00 111111.	Ollogis	(4)	(8)	(17)	(2)	5 gal. pail A	00-021200-82251-3	7000028575
<u> </u>										5 gal. pail B	00-021200-82250-6	7000028567
<b>1751 B/A</b> (Gray)	Excellent void filler; Rigid bonds	3:2	700,000	45 min.	10 hours	4 (7)	1,400 (10)	2,000 (14)	500 (3)	Gallon kit	00-021200-20105-9	7000046339
1838 B/A (Green)	Multi-purpose; Rigid bonds	4:5	400,000	60 min.	8 hours	4 (7)	1,500 (10)	3,000 (21)	500 (3)	Quart kit	00-021200-20152-3	7000046340
1838L B/A (Translucent)	Multi-purpose; Rigid bonds	1:1	10,000	60 min.	8 hours	4 (7)	2,000 (14)	2,500 (17)	300 (2)	Quart kit	00-021200-22646-5	7000036224
<b>2158 B/A</b> (Gray)	Multi-purpose; Rigid bonds	1:1	375,000	2 hours	10 hours	3 (5)	1,500 (10)	2,000 (14)	400 (3)	Gallon kit	00-021200-20262-9	7010330060

For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

Note: The technical information and data on these pages should be considered representative or typical only and should not be used for specification purposes.

# 3M™ Scotch-Weld™ Structural Adhesives 🛡 🗓 🚭 🗓 🚉









### **3M™ Scotch-Weld™ Flexible Epoxies**

						/	<b>~</b>	ngth of	e naco	ps	rlap Shear: si (MPa)		
	ری,	don		0 78:A	ate st. coles	be with	Aireste	C) Roller 1		o	~°°°		
	Product Co	<b>Key Features</b>	Mix C	Stircus Approxim	Str Approxim	St Approving	242 400g	ing leni julikleni	15°	1.67 1.60 1.00 1.00	Dr. Site	ikc	Stock*
	DP100					ĺ		ĺ			48.5mL	00-638060-08976-7	7100148750
	Plus										200mL	00-021200-87266-2 00-021200-87198-6	
*	100 Plus (Clear)	Very flexible; Colorless	1:1	8,500	4 min.	20 min.	55 (98)	3,000	3,500 (24)	200	5 gal. pail A 5 gal. pail B	00-021200-87198-8	
	(Gicai)	001011033					(00)	(21)	(2-1)	(1)	50 gal drum A	00-021200-07137-3	
	G.										50 gal drum B	00-068060-00520-5	
	DP105										48.5mL	00-638060-08981-1	7100148733
	105 (Clear)	Very flexible;	1:1	6,500	5 min.	20 min.	50	3,500	2,000	150	200mL	00-021200-87270-9	7010309884
	650	Colorless	1.1	0,500	J 111111.	20111111.	(89)	(24)	(14)	(1)	5 gal. pail A	00-021200-87206-8	
	(Control of the Control of the Contr										5 gal. pail B	00-021200-87205-1	7000000850
	DP110							0.700	0.500	0.50	48.5mL 200mL	00-638060-08990-3 00-021200-87274-7	7100148777 7000121312
	110	General purpose; Flexible bonds	1:1	55,000	8 min.	20 min.	40 (71)	2,700 (19)	3,500 (24)	250 (2)	5 gal. pail A	00-021200-87274-7	
	(Gray)	Trombio borido					( /	(.0)	(= .)	(-)	5 gal. pail B	00-021200-82471-5	
											48.5mL	00-638060-08993-4	
	DP110							0.500	0.500	000	200mL	00-021200-87846-6	7000148270
	110	General purpose; Flexible bonds	1:1	50,000	8 min.	20 min.	40 (71)	2,500 (17)	2,500 (17)	200	400mL	00-021200-87847-3	
	(Translucent)	Trombio borido					( /	()	()	(.,	5 gal. pail A	00-021200-82467-8	
											5 gal. pail B	00-021200-82466-1	7010366143
Product	DP125										48.5mL 200mL	00-638060-08985-9 00-021200-87844-2	7100148735 7000121264
5	<b>125</b> (Gray)	High performance;	1:1	52,500	25 min.	2.5 hours	90	3,400	4,300	400	400mL	00-021200-87845-9	
	(L)	Very flexible bonds		02,000	20	2.01.00.0	(160)	(23)	(30)	(3)	5 gal. pail A	00-021200-87218-1	7100084588
Key	•										5 gal. pail B	00-021200-87217-4	7100084538
	DP125	High performance;					85	4,000	2,500	150	48.5mL	00-638060-08983-5	7100148734
	125 (Translucent)	Very flexible bonds	1:1	15,000	25 min.	2.5 hours	(151)	(28)	(17)	(1)	400mL	00-021200-87843-5	
	( in an ioladocinty										48.5mL	00-638060-08980-4	7100148752
	DP190	High performance;	1:1	10,000	80 min.	6 hours	60	3,500	1,200	150	5 gal. pail A	00-638060-40468-3	7100218836
	(Translucent)	Flexible bonds		,			(107)	(24)	(8)	(1)	5 gal. pail B	00-638060-40467-6	7100218835
	DP190	High performance;									48.5mL	00-638060-08992-7	7010410438
40	(Gray)	Slightly flexible	1:1	80,000	90 min.	10 hours	50 (89)	1,500 (10)	2,500 (17)	400	200mL	00-021200-87840-4	7000121314
	(h)	bonds					(69)	(10)	(17)	(3)	400mL	00-021200-87841-1	7100076722
											41.5mL	00-068060-00115-3	
											2 oz. tube kit	00-021200-20351-0	
											Pint kit	00-021200-20354-1	7000046358
	2216 B/A	High performance;	2:3	80,000	90 min.	10 hours	50	3,000	3,200	400	Quart kit Gallon kit	00-021200-20356-5 00-021200-20358-9	
•	(Gray)	Very flexible bonds	2.3	80,000	90111111.	TOTIOUIS	(89)	(21)	(22)	(3)	5 gal. pail A	00-021200-20358-9	7000006816
											5 gal. pail B	00-021200-20360-2	
											50 gal drum A	00-021200-20366-4	
											50 gal drum B	00-021200-20361-9	7100166319
											2 oz. tube kit	00-021200-20851-5	
	2216 B/A	General purpose;					70	3,000	1,700	140	Quart kit	00-021200-20854-6	
		Very flexible bonds	1:1	10,000	2 hours	14 hours	(125)	(21)	(12)	(1)	Gallon kit	00-021200-20856-0	7000046480
											5 gal. pail A 5 gal. pail B	00-021200-64981-3 00-021200-64980-6	
	2216NS	High performance;					50	2,000	2,500	400	5 gal. pail A	00-021200-64980-6	7010367414
	<b>B/A</b> (Tan)	Non-sag	2:3	350,000	2 hours	10 hours	(89)	(14)	(17)	(3)	5 gal. pail B	00-021200-87179-5	
		-							<del></del>		, , , ,		

For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

Note: The technical information and data on these pages should be considered representative or typical only and should not be used for specification purposes.

# 



### 3M™ Scotch-Weld™ Toughened Epoxies

							, e	gir /	e), 12°C) /	ns	lap Shear: i (MPa)		
	Producticol	Keyfeatures		8:A	ate at o	ar of or	ate so she	C) aller 1	25 (15° C)				
	oduct	ny Featu	/14 P	ational totic	osky od otice	948 Solo 48	rding Co	no de cont	K 183	£102°C)	St. Co. Cy	Ikc.	5tock*
	ورد DP405	Terrele demolete	PW	10 bo. 115	13 46.44	8t. bb. 40 .	ot / 410 0	, , , , , , , , , , , , , , , , , , ,	10	/ 🗏		<u> </u>	
	<b>405</b> (Black)	Tough durable bonds;	2:1	70,000	4 min.	15 min.	40	4,500	4,500	600	50mL 5 gal. pail A	00-638060-08971-2	
	(4)	High impact resistance		, 0,000			(71)	(31)	(31)	(4)	5 gal. pail B	00-051111-07707-8	
											50mL	00-638060-08966-8	
		Tarrah danah la									200mL 400mL	00-021200-41530-2 00-021200-41529-6	
	DP420 420	Tough durable bonds;	2:1	30,000	20 min.	2 hours	75	4,500	4,500	1,250	Gallon Kit	00-051115-25796-4	
Ĩ	(Black)	High impact resistance	2.1	30,000	20 111111.	2 110015	(133)	(31)	(31)	(9)	5 gal. pail A	00-021200-41532-6	
		resistance									5 gal. pail B 43 gal. drum A	00-021200-41531-9	
											43 gal. drum B	00-021200-41533-3	
ţ	DP420	T 1 1 11									50mL	00-638060-08978-1	
Product	420 (Off-White)	Tough durable bonds;	2:1	30,000	20 min.	2 hours	70	4,500	4,500	450	200mL 400mL	00-021200-87832-9	
	(O11-Wilite)	High impact resistance	2.1	30,000	2011111.	2110015	(125)	(31)	(31)	(3)	5 gal. pail A	00-021200-87833-0	
Key	•	resistance									5 gal. pail B	00-021200-82238-4	7100001145
											50mL	00-638060-08987-3	
	DP420NS 420NS	Taurah durah la									200mL 400mL	00-021200-39286-3	
40	(Black)	Tough durable bonds;	2:1	180,000	20 min.	2 hours	60 (107)	4,500 (31)	4,500 (31)	1,250 (9)	5 gal. pail A	00-021200-31309-7	
	<b>(</b> L)	Non-sag					(107)	(31)	(31)	(9)	5 gal. pail B	00-021200-56587-8	
											50 gal. drum A 50 gal. drum B	00-048011-58133-0 00-048011-58132-3	
	DP460	Tough durable					80	4,500	4,500	700	5 gal. pail A	00-048011-38132-3	
*	<b>460</b> (Black)	bonds	2:1	30,000	60 min.	4 hours	(142)	(31)	(31)	(5)	5 gal. pail B	00-021200-25318-8	7000121265
											50mL	00-638060-08998-9	
	DP460										200mL 400mL	00-021200-87830-5	
_	460 (Off-White)	Tough durable	2:1	30,000	60 min.	4 hours	80	4,500	4,500	700	Quart kit	00-021200-82226-1	
Ĩ	(O11-VVIIIte)	bonds	2.1	30,000	00 111111.	4110015	(142)	(31)	(31)	(5)	5 gal. pail A	00-021200-82228-5	
	<b>@</b>										5 gal. pail B 53 gal. drum A	00-021200-82227-8	
											53 gal. drum B	0-00-76308-14623-8	
											50mL	00-638060-08968-2	
	DP460NS 460NS	Tough durable	2:1	125,000	60 min.	4 hours	70	3,600	4,900	4,650	200mL 400mL	00-021200-43671-0	
Ĩ	(Off-White)	bonds; Non-sag	2:1	125,000	ou min.	4 nours	(125)	(25)	(34)	(32)	5 gal. pail A	00-021200-43672-7	
											5 gal. pail B	00-021200-43673-4	7010301036
	<b>DP490</b> <b>490</b> (Black)	Tough durable					34	3,600	4,500	2,000	400		7,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,
	(Augustian )	bonds	2:1	90,000	90 min.	4 hours	(60)	(25)	(31)	(14)	400mL	04-054596-67913-9	7100200501
	7240FR	Tough durable					15	3,400	4,500	900	400mL	04-064035-15229-1	710033127
	(Black)	bonds	2:1	120,000	45 min.	6 hours	(92)	(18)	(27)	(12)	14 gal. Kit	54-046719-95284-2	7100042123
	LSB60	Tough durable bonds;					15	3,400	4,500	900	400mL	00-051115-63411-6	
	(Gray)	High impact	1:1	30,000	90 min.	5 hours	(27)	(23)	(31)	(6)	50 gal. drum A	00-051115-63418-5	
		resistance Tough durable									50 gal. drum B 5 gal. pail A	00-051115-63417-8	
	LSB60NS	bonds;					10	3,800	4,500	800	5 gal. pail B	00-051115-63427-7	
	(Gray)	Non-sag; High impact	1:1	60,500	90 min.	5 hours	(18)	(26)	(31)	(6)	50 gal. drum A	06-38060-40269-6	
		resistance									50 gal. drum B	06-38060-40270-2	7100198390
		Tough durable bonds;											
	LSB360NS	Non-sag;	1:1	60,500	10 hours	16 hours	30	4,000	4,000	800	55 gal. drum A	00-051115-64360-6	
	(Green)	Extra long work life;		55,555			(53)	(28)	(28)	(6)	55 gal. drum B	00-051115-64391-0	7010299359
		Bonds oily metals											

For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

# 3M™ Scotch-Weld™ Structural Adhesives 🛡 🗓 🕮 🕮








### 3M™ Scotch-Weld™ Heat-Cured Epoxies

					<u>~</u>	Cure Condition	ons Reg	(Ar.C)		verlap S psi (MP	a)		
	Product Colo	n Kenkedine	Approxit	nate at o	ne trini	b. togg	ns Pedia Pedia Roller R	( ) ( ) ( ) ( ) ( ) ( ) ( ) ( ) ( ) ( )	180°	<b>4</b> 88°C)	St. 122°C)	upc .	Stock*
	6101 (Off White) (1)	Excellent impact resistance; Low temp cure	30,000	20	149 (65)	N/A	N/A	N/A	N/A	N/A	30mL cart.	00-638060-40406-5	7100208553
	<b>1386</b> (Cream)	High temperature strength; Impact resistance	150,000	60	350 (177)	10 (18)	3,000 (2 1)	5,500 (38)	4,500 (31)	2,500 (17)	1 quart	00-021200-19917-2	7000046326
	<b>1469</b> (Cream)	High temperature strength; Low viscosity	60,000	120	350 (177)	2 (4)	3,150 (22)	3,700 (26)	3,700 (26)	3,600 (25)	1 quart 5 gal. pail	00-021200-19949-3 00-021200-19950-9	7000046328 7100056050
	2214 Hi-Temp New Formula (Gray)	High temperature strength; Environmental resistance	Paste	60	250 (121)	2 (4)	2,000 (14)	2,500 (17)	2,000 (14)	2,000 (14)	6 oz. cart. 5 gal. pail	00-021200-20833-1 00-021200-20835-5	7000046474 7010330200
	2214 Non-Metallic Filled (Cream)	High temperature strength; Higher insulation value	Paste	40	250 (121)	7 (12)	3,000 (2 1)	2,200 (15)	2,000 (14)	400 (3)	6 oz. cart.	00-021200-25496-3	7000121273
*	2214 Regular (Gray)	High temperature strength; Low temp curing	Paste	40	250 (121)	5 (9)	3,000 (2 1)	2,500 (17)	2,000 (14)	800 (6)	6 oz. cart. 1 quart 5 gal. pail	00-021200-20344-2 00-021200-20345-9 00-021200-23047-3	7000000811 7000046356 7100111206
	<b>2290</b> (Amber)	Low solids liquid coating for metal laminations	60	30-60	350 (177)	5 (9)	5,000 (34)	5,000 (34)	3,500 (24)	1,200 (8)	Gallon cont. 5 gal. pail 54 gal. drum	00-021200-76225-3 00-021200-76227-7 00-021200-76228-4	7000000897 7100144895 7100144896

### 3M™ Scotch-Weld™ Primer



### 3M™ Scotch-Weld™ **Epoxy Adhesive DP420NS**

3M Scotch-Weld Epoxy Adhesive DP420NS is a black, toughened, non-sag, two-part epoxy structural adhesive that provides good strength along with high impact and fatigue resistance. It can replace mechanical fasteners, screws, rivets and spot welds in many applications.



### 3M™ Scotch-Weld™ **Epoxy Adhesive DP100 Clear**

3M Scotch-Weld Epoxy Adhesive DP100 Clear is a very flexible, fast-setting, two-part epoxy adhesive that cures clear and colorless. It provides a strong, permanent bond, even under vibration and impact and is flexible when cured, making it a good choice for bonding dissimilar surfaces.



For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

Note: The technical information and data on these pages should be considered representative or typical only and should not be used for specification purposes.

# 3M™ Scotch-Weld™ Structural Adhesives © © © © © © 292









### 3M™ Scotch-Weld™ Standard MMA Acrylics and Low Odor Acrylics

					.,,e	ine e	ngth Re	s (MC)	ps	ap Shear: i (MPa)	/
Product.C	Again Key Festures		atione BiA	ste st. Okr	ste of Ca	rding 24	no low str	4 15°	1,62°C) 1,85°C	St. Site	
		Mix	John Wood isc	20 POSTUTE	of Look of	\$10° 6	1164 30	1/18	, , , %	Site	Jec story
	MA Acrylics Fast strength build;									48.5mL	00-638060-08982-8 7010410436
DP805 (Off-White)	Minimal surface prep	1:1	110,000	3 min.	10 min.	35 (62)	2,500 (17)	3,500 (24)	2,200 (15)	200mL	00-021200-87828-2 7010367390
DP820 (Light Yellow)	Tough durable bonds; Minimal surface prep	1:1	55,000	15 min.	40 min.	20 (36)	3,100 (21)	3,150 (22)	1,900 (13)	48.5mL 200mL	00-638060-08977-4 00-021200-89348-3 7010329704
DP8405NS 8405NS (Green)	High impact; Adhesion to most plastics	10:1	70,000	5 min.	15 min.	50 (89)	2,600 (18)	4,100 (28)	900 (6)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A 50 gal. drum B	00-051115-68963-5 7100009688 00-051115-68964-2 7100011056 00-051115-68981-9 7100102180 00-051115-68986-4 7100027430 00-051115-68980-2 7100101506 00-051115-68987-1 7100084534
DP8407NS 8407NS (Gray)	High impact; Adhesion to most plastics	10:1	20,000	7 min.	24 min.	50 (89)	3,400 (23)	4,500 (31)	1,400 (10)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A	00-638060-14631-6 7100179482 00-638060-14643-9 7100179480 00-638060-14658-3 7100179264 00-076308-86306-7 7100105384 00-638061-14659-0 7100179442
Mey Product (Green)	High impact; Adhesion to most plastics	10:1	70,000	10 min.	25 min.	50 (89)	3,600 (25)	4,100 (28)	800 (6)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A 50 gal. drum B	00-051115-70994-4 7100024055 00-051115-70995-1 7100024045 00-051115-68981-9 7100102180 00-051115-70997-5 7100064830 00-051115-68980- 7100101506 00-051115-71101-5 7100084532
DP8425NS 8425NS (Green)	High impact; Adhesion to most plastics	10:1	70,000	25 min.	50 min.	50 (89)	3,800 (26)	3,700 (26)	800 (6)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A 50 gal. drum B	00-051115-81303-0 7100078165 00-051115-81302-3 7100078166 00-051115-68981-9 7100102180 00-68060-00072-9 7100255721 00-0511115-81414-3 7100101506 00-051115-81031-6 7100084535
Low Odor A	crylics				ı.						
DP8705NS 8705NS (Black)	Low odor; Fast rate of strength build	10:1	80,000	5 min.	6 min.	34 (60)	4,350 (30) at -40°C	2,320 (16)	580 (4)	45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B	00-638060-40963-3   7100245036   00-638060-40964-0   7100245039   00-638060-40862-9   7100233358   00-638060-40863-6   7100234571   00-638060-40965-7   7100245037
DP8710NS										50 gal. drum B	00-638060-40966-4 7100245038
DP8710NS (Black) (II)	Low odor; Fast rate of strength build	10:1	80,000	10 min.	13 min.	34 (60)	4,350 (30) at -40°C	2,320 (16)	580 (4)	50 gal. drum B 45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B	00-638060-40966-4   7100245038 00-638060-40865-0   7100233349 00-638060-40866-7   7100233348 00-638060-40862-9   710023358 00-638060-40863-6   7100234571 00-638060-40868-1   7100234572 00-638060-40868-1   7100233166
B710NS (Black)  DP8725NS 8725NS (Black)	Fast rate of	10:1	80,000	10 min. 23 min.	13 min. 25 min.		(30) at			45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B	00-638060-40865-0 7100233349 00-638060-40866-7 7100233348 00-638060-40862-9 7100233358 00-638060-40863-6 7100234571 00-638060-40867-4 7100234572
DP8725NS 8725NS	Fast rate of strength build Low odor; Fast rate of					(60)	(30) at -40°C 4,350 (30) at	2,320	580	45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B 45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B	00-638060-40865-0     7100233349       00-638060-40866-7     7100233348       00-638060-40862-9     7100233358       00-638060-40863-6     7100234571       00-638060-40867-4     7100234572       00-638060-40868-1     7100234356       00-638060-40968-8     7100244858       00-638060-40968-8     7100244480       00-638060-40862-9     7100233358       00-638060-40863-6     7100234571       00-638060-40969-5     7100234571       7100234571     7100244480       7100234571     7100244480       7100244480     7100234571       7100244481     7100234571       7100244481     7100244481       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571       7100244481     7100234571 <td< th=""></td<>
DP8725NS 8725NS (Black)	Fast rate of strength build  Low odor; Fast rate of strength build  Tough durable bonds; High impact	10:1	80,000	23 min.	25 min.	(60) 34 (60)	(30) at -40°C 4,350 (30) at -40°C	2,320 (16)	580 (4)	45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B 45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B 48.5mL 200mL 1 gallon pail A 1 gallon pail B 4.4 gal. pail A	00-638060-40865-0       7100233349         00-638060-40866-7       7100233348         00-638060-40863-6       7100233558         00-638060-40863-6       7100234571         7100233758       7100234571         7100233758       7100234571         7100233166       7100233166         00-638060-40868-1       7100234158         00-638060-40968-8       7100244858         00-638060-40968-8       7100244858         00-638060-40863-6       710023358         7100234571       7100244861         00-638060-40969-5       7100244861         00-638060-40971-8       7100244862         00-638060-40969-5       7100144873         700-021200-49079-8       7100142848         00-048011-56711-2       7000046385         7000046385       7010365969

# 









### 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Low Odor Acrylics (cont.)

Product (Col	bor) Kenyfesture	s Mites	sio e 8: A din Approise of	st poorting	ate wite of the street of the	ate the step of the state of th	right pe		p:	/	Inc Good #
DP8805NS 8805NS (Green)	Low odor; Fast rate of strength build	10:1	80,000	5 min.	7 min.	30 (53)	800 (5)	3,600 (25)	900 (6)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A 50 gal. drum B	00-076308-98433-5
DP8810NS 8810NS (Green)	Low odor; Fast rate of strength build	10:1	80,000	10 min.	18 min.	30 (53)	900 (6)	3,600 (25)	800 (6)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A 50 gal. drum B	00-051128-99432-0 7100097574 00-051128-99431-3 7100075409 00-051115-81415-0 7100102180 00-076308-98442-7 7100097704 00-051115-81414-3 7100101506 00-076308-98443-4 7100097626
DP8810NS (Gray)	Low odor; Fast rate of strength build	10:1	80,000	10 min.	18 min.	30 (53)	900 (6)	3,600 (25)	800 (6)	45mL 490mL	00-076308-86152-0 7100097474 00-076308-98485-4 7010329557
DP8825NS 8825NS (Green)	Low odor; Fast rate of strength build	10:1	80,000	25 min.	44 min.	20 (36)	1,000 (7)	3,000 (21)	800 (6)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A 50 gal. drum B	00-051115-81288-0 7100067297 00-051115-81289-7 7100068120 00-051115-81415-0 7100102180 00-051115-81290-3 7100067291 00-051115-81414-3 7100101506 00-051115-81291-0 7100084533

### **3M™ Scotch-Weld™ Low Surface Energy and Nylon Bonder Acrylics**

	<b>Arognet</b> Cox		s nit cu	tio popolitic	ste st. Olego st. Application	de Arite Strong Of Strong	trinsus de la	roth Period of the State of the	STANSON ASK	ps	lap Shear: i (MPa)	, rc	Stock*
	<b>DP8005</b> (Black)	Bonds polyolefins and low surface energy materials	10:1	25,000	3 min.	3 hours	N/A	875 (6)	2,000 (14)	475 (3)	45mL 490mL	00-051128-99352-1 00-051128-99298-2	
	DP8005 (Off-White)	Bonds polyolefins and low surface energy materials	10:1	25,000	3 min.	3 hours	N/A	750 (5)	2,200 (15)	500 (3)	45mL 490mL	00-051128-99349-1 00-051128-99297-5	
Product	<b>DP8010 8010</b> (Blue)	Bonds polyolefins and low surface energy materials	10:1	20,000	10 min.	1 hour	N/A	2,700 (19)	2,700 (19)	500 (3)	45mL 490mL 1 gal. pail A 5 gal. pail B 5 gal. pail A	00-051115-71600-3 00-051115-71601-0 00-021200-49113-9 00-051115-71669-0 00-021200-49115-3	7100036719 7100050479 7100036720
	DP8910NS 8910NS (Black)	Bonds nylon and metal	10:1	45,000	10 min.	16 min.	10 (18)	2,175 (15)	3,190 (22)	1,595 (11)	45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B	00-068060-00546-5 00-068060-00547-2 00-638060-40862-9 00-638060-40863-6 00-068060-00548-9 00-068060-00549-6	7100314358 7100233358 7100234571 7100314557

### 3M™ Scotch-Weld™ Flexible Acrylics

Product. Col	Ley Festure	s Mixe	sio e 8: A justicio	ste st. colorida strydocotic for property	ate wite of the transfer of th	aterine de la constante de la	ight pe	STORED STORED TOTAL	p:		, gc	Stock *
DP8610NS 8610NS (Black)	Very flexible and no read through on thin metals	10:1	130,000	10 min.	18 min.	57 (100)	3,480 (24)	1,015 (7)	290 (2)	45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B	00-638060-40836-0 00-638060-40862-9 00-638060-40862-9 00-638060-40838-4 00-638060-40838-4 00-638060-40839-1	7100232802 7100233358 7100234571 7100234673
DP8625NS 8625NS (Black)	Very flexible and no read through on thin metals	10:1	130,000	23 min.	28 min.	57 (100)	3,480 (24)	1,015 (7)	290 (2)	45mL 490mL 1 gal. pail A 5 gal. pail A 5 gal. drum B 50 gal. drum B	00-638060-40972-5 00-638060-40973-2 00-638060-40862-9 00-638060-40863-6 00-638060-40974-9 00-638060-40975-6	7100244477 7100233358 7100234571 7100244476
<b>DP8625NS</b> <b>8625NS</b> (Grey)	Very flexible and no read through on thin metals	10:1	130,000	23 min.	28 min.	57 (100)	3,480 (24)	1,015 (7)	290 (2)	490mL 5 gal. pail A 50 gal. drum B	00-068060-00399-7 00-638060-40863-6 00-068060-75678-7	7100234571

# 



#### 3M™ Scotch-Weld™ Semi-Rigid Urethanes

	Product Con	ssi Kentedure	s shirt	silo a 8:1 la silo a	ste st. Oliversia	or Aire	ate the steel	right Res	K ANO O	psi	ap Shear: (MPa)	ikc	stock*
	DP600 600 (Gray)	Concrete repair; Self-leveling	1:1	6,000	1 min.	4 min.	20 (36)	3,200 (22)	2,300 (16)	700 (5)	48.5mL 8.4 fl. oz. 5 gal. pail A 5 gal. pail B	00-638060-08962-0 00-021200-96596-8 00-021200-96575-3 00-021200-96574-6	7100148740 7000046375 7010130543 7010170293
	DP600NS 600NS (Gray)	Concrete repair; Non-sag	1:1	Paste	1 min.	4 min.	8 (14)	2,700 (19)	2,300 (16)	700 (5)	48.5mL 5 gal. pail A 5 gal. pail B	00-638060-08964-4 00-068060-00005-7 00-068060-00004-0	7100249024
	DP605NS 605NS (Off-White)	Semi-rigid Non-sag	1:1	150,000	5 min.	20 min.	40 (71)	4,000 (28)	2,000 (14)	600 (4)	48.5mL	00-638060-08997-2	7100148767
	DP6301NS (Green)	Delivers strength and performance	1:1	Non-sag paste	1 min.	3 min.	36 (64)	2,018 (14)	1,653 (11)	224 (1)	400mL 50 gal. drum A 50 gal. drum B	00-068060-00068-2 00-068060-00070-5 00-068060-00069-9	7100255361
Key Product	DP6310NS (Green)	Multi-purpose; Energy absorbing	1:1	Non-sag paste	10 min.	45 min.	20 (36)	3,500 (24)	3,600 (25)	900 (6)	_ ~	00-076308-86407-1 00-076308-86398-2 00-076308-86782-9 00-076308-86748-5 00-076308-86783-6 00-076308-86749-2	7100109829 7100109830 7100143960 7100143915 7010415316 7010412199
	DP6330NS (Green)	Multi-purpose; Energy absorbing	1:1	Non-sag paste	30 min.	2 hours	20 (36)	3,600 (25)	3,600 (25)	1,000 (7)		00-076308-86431-6 00-076308-86433-0 00-076308-86780-5 00-076308-86701-0 00-076308-86781-2 00-076308-86727-0	7100109828 7100109827 7100143961 7100143701 7010409611 7010366145

#### 3M™ Scotch-Weld™ Flexible Urethanes

	Product (Col)	or teature	s mite	ational bid in significant in the significant in th	ste st colors stry Acothire	te wite of the state of the sta	tine de line of the state of th	noth per	k CAOCO 15°C	psi	ap Shear: (MPa)	nec .	Stock *
*	DP604NS 604NS (Black)	Flexible; Non-sag	1:1	Paste	4 min.	20 min.	30 (53)	1,400 (10)	600 (4)	300 (2)	48.5mL 400mL 5 gal. pail A 5 gal. pail B 50 gal. drum A 50 gal. drum B	00-638060-08961-3 00-051111-98301-0 00-021200-96462-6 00-021200-96461-9 00-076308-14205-6 00-076308-87087-4	7100148738 7100069452 7010365926 7010367265 7010329538 7010412243
*	DP620NS 620NS (Black)	Semi-flexible; Non-sag	1:1	Paste	20 min.	4 hours	40 (71)	3,000 (21)	2,500 (17)	500 (3)	48.5mL 400mL 5 gal. pail A 5 gal. pail B 50 gal. drum A 50 gal. drum B	00-638060-08960-6 00-048011-57287-1 00-076308-14144-8 00-076308-14135-6 00-076308-14135-5 00-076308-14146-3	7100148737 7000046372 7101329537 7010367262 7010301034 7010309744
	DP640 (Brown)	Tough flexible bonds	1:1	25,000	60 min.	8 hours	60 (107)	3,000 (21)	2,000 (14)	400 (3)	48.5mL	00-638060-08991-0	7100148761
	<b>3549</b> (Brown)	Tough flexible bonds	1:1	25,000	60 min.	8 hours	60 (107)	3,000 (21)	2,000 (14)	400 (3)	Quart kit	00-021200-20802-4	7000046485
	<b>DP5001 5001</b> (Black)	Flexible; Conveyor belt repair	1:1	100,000	1 min.	15 min.	N/A	N/A	600 (4)	N/A	400mL	00-051111-98296-9	7100028818

For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

# 









#### 3M™ Scotch-Weld™ PUR Adhesives — Wood Bonders

9	roduct (	podori Ken Keadures	Vieco Sira	A 12 ° CI LON HOOF IN THE BEAT	Operato Strato Appropriati	tires terest tires terest of the same	re O that	gation % Site	, ge	Stock**
<b>EZ250</b> (Off-W		Fast set time; UV tracer	7,000	1.5 min.	15 seconds	65	750	1/10 gal. 5 gal.	00-051115-23545-0 00-051115-23546-7	7000046529 7010310232
<b>EZ250</b> (Off-W		Medium set time; UV tracer	7,000	2 min.	60 seconds	60	675	1/10 gal. 5 gal.	00-051115-23550-4 00-051115-23551-1	7000046531 7010329734
<b>EZ250</b> (Off-W		Medium set time; Low viscosity; UV tracer	3,000	4 min.	120 seconds	60	625	1/10 gal.	00-051115-23554-2	7000046532
TE030 (Off-W		Fast set time; High viscosity; No UV tracer	16,000	1 min.	30 seconds	60	725	1/10 gal. 5 gal.	00-051115-25157-3 00-021200-82484-5	7000046536 7010310236
<b>TE100</b> (Off-W		Medium set time; UV tracer	7,000	2 min.	60 seconds	61	675	1/10 gal. 5 gal.	00-051115-25161-0 00-021200-87244-0	7000028590 7010295326
TE200 (Off-W		Medium set time; Low viscosity; UV tracer	3,000	4 min.	120 seconds	60	625	1/10 gal. 2 kilo	00-051115-25164-1 00-048011-53272-1	7000000905 7000046540

#### 3M™ Scotch-Weld™ PUR Adhesives — Plastic Bonders

	Product <sub>i</sub> Color	, Little's		Agrication Production	open construction of the state	Time lengt	ir /	ion.		
	Product	Keyfeatues	1,ec.052	Poble	Poblo Have	gor' sh	ore C th	Subation% Site	JAC	Stock*
	<b>EZ250030</b> (Off-White)	Fast set time, bonds a wide variety of plastics; No UV tracer	13,000	2 min.	30 seconds	50	725	1/10 gal. 5 gal.	00-051115-23541-2 00-051115-23542-9	7000046530 7000121357
	<b>EZ250150</b> (Off-White)	Long open time; Bonds plastics to metal, glass, wood; No UV tracer	9,000	4 min.	150 seconds	45	700	1/10 gal. 2 kilo 5 gal.	00-051115-23559-7 00-051115-23562-7 00-051115-23560-3	7000046533 7010295325 7010367590
	<b>EZ250200</b> (Off-White)	Long open time; Low viscosity; Bonds plastics, wood, and many other material combinations; No UV tracer	2,750	3 min.	120 seconds	30	400	1/10 gal. 2 kilo	00-048011-57402-8 00-048011-57401-1	7000046538 7010367604
	TE031 (Black)	Fast set time; Bonds a wide variety of plastics; no UV tracer	13,000	2 min.	30 seconds	50	725	1/10 gal. 5 gal.	00-051115-25159-7 00-021200-89573-9	7000000903 7100031123
*	TE031 (Off-White)	Fast set time; Bonds a wide variety of plastics; No UV tracer	13,000	2 min.	30 seconds	50	725	1/10 gal. 2 kilo	00-051115-25158-0 00-048011-53355-1	7000000902 7000028589
	TE040 (Black)	Fast set time; Strong flexible; bonds to plastic, wood, aluminum, glass; No UV tracer	7,000	2 min.	40 seconds	35	860	1/10 gal. 5 gal. 55 gal. drum	00-051115-64536-5 00-638060-14494-7 00-638060-14321-6	7100003450 7100172685 7100160468
	TE040 (Off-White)	Fast set time; Strong flexible bonds to plastic, wood, aluminum, glass; No UV tracer	7,000	2 min.	41 seconds	35	860	1/10 gal. 5 gal. 55 gal. drum	00-051115-25160-3 00-021200-25343-0 00-638060-14498-5	7000021292 7000136628 7100170133
	TS230 (Black)	Extrudable/sprayable; Long open time; Bonds plastics to metal, glass, and wood; No UV tracer	9,000	4 min.	150 seconds	45	700	1/10 gal. 2 kilo 5 gal. 55 gal. drum	00-051115-25166-5 00-048011-53273-8 00-021200-89583-8 00-638060-14675-0	7000000906 7000046541 7000121361 7100179521
Product	TS230 (Off-White)	Extrudable/sprayable long open time; Bonds plastics to metal, glass, and wood; No UV tracer	9,000	4 min.	150 seconds	45	700	1/10 gal. 2 kilo 5 gal. 55 gal. drum	00-051115-25165-8 00-048011-53271-4 00-021200-83640-4 00-021200-83639-8	7000000898 7000046534 7100024959 7100104259
	<b>TS230</b> (Gray)	Extrudable/sprayable long open time; Bonds plastics to metal, glass, and wood; No UV tracer	9,000	4 min.	150 seconds	45	700	55 gal. drum	00-638060-40191-0	7100191940
	Purge Material 3756	Purge PUR adhesives from bulk dispensing equipment	8,250	N/A	N/A	N/A	N/A	5 gal.	00-021200-56522-9	7000121333

For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

## 3M™ Scotch-Weld™ PUR Adhesives

#### 3M™ Scotch-Weld™ PUR Applicator/Preheater/Hardware


Product	<b>Descritation</b>	<sup>18</sup> c	Stock*
Applicator	PUR Easy 250 Applicator, pneumatically dispenses 1/10 gal. cartridges, US 120V	00-051115-23563-4	7000000958
Preheater	PUR Easy 250 Preheater, preheats up to four 1/10 gal. cartridges, 120V, Dual Temp	00-051115-23564-1	7000121608
System Accessories for	Applicator Bench Mount Bracket Assembly (bracket only)	00-021200-30086-8	7000121614
hands-free dispensing	Hot Melt Applicator Foot Pedal Assembly 9277	00-021200-82278-0	7000121596
Cartridge Nozzle	High Temperature Nozzles for PUR 1/10 gal. cartridges (Sample, 5/bag)	50-638060-40564-7	7100218849
	Adhesive Applicator Housing/Shroud Assembly Kit	00-051115-25783-4	7000028623
	Applicator Nozzle Shroud	00-048011-58320-4	7000148288
	Benchmount Quick Exhaust Assembly Replacement Kit	00-021200-31357-8	7010366711
	Applicator Air Coupler Filter Kit	00-021200-89475-6	7000046665
	Applicator Air Supply Line Kit	00-021200-89479-4	7000046668
	Applicator Air Valve Kit	00-048011-57410-3	7000046652
	Applicator Swivel Connector	00-048011-58298-6	7000046653
Repair Kits and Replacement Parts	Applicator End Cap	00-021200-89476-3	7000046666
Replacement raits	Applicator Heat Tube Assembly (120V) Kit	00-021200-89486-2	7010329969
	Applicator Heat Tube (240V)	00-021200-25303-4	7000046673
	Applicator On/Off Switch Kit	00-021200-89482-4	7100079509
	Applicator Power Cord Kit (120V)	00-021200-89481-7	7010366708
	Applicator Wire Stand	00-021200-89483-1	7010329970
	High Temperature (250 Degrees F) PUR Preheater Thermostat/TCO Kit	00-051115-23619-8	7010329954
	Low Temperature (170 Degrees F) PUR Preheater Thermostat/TCO Kit	00-051115-23618-1	7010366686
	Applicator Main Nozzle Assembly (includes nozzle, tip, tip cap and valve)	00-021200-89514-2	7000027561
	Applicator Main Nozzle	00-021200-89515-9	7000046672
Alternate Nozzle	Applicator Extension Tip, .072 in. orifice	00-021200-89471-8	7000046669
System (not for use with	Applicator Tip, .125 in. orifice	00-021200-89473-2	7000046671
disposable nozzles)	Applicator Tip, .063 in. orifice	00-021200-89472-5	7000046670
	Applicator Tip Cap	00-021200-87194-8	7100005819
	Applicator Valve Assembly	00-021200-83730-2	7000046650





#### 3M™ Scotch-Weld™ PUR Adhesives

PUR Adhesives enhance productivity with fast green strength. Shorter clamp times and reduced need for third-hand mechanical fasteners help speed up your production process without sacrificing ultimate strength.



For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

## 3M™ Scotch-Weld™ Instant Adhesives 🗓 🗐 🗐




#### 3M™ Scotch-Weld™ Instant Adhesives — Plastic and Rubber, Surface Insensive and Low Odor

Produ	ked feetings	rupical critical	Temperatur	a transe	o Handling	d Cine thous	<sup>Ifc</sup>	stock*
Plastic and	d Rubber							
PR Gel (Clear)	Fast cure, gel viscosity for max gap filling	Gel	-65° to 180°F (-54° to 82°C)	< 25 sec.	24	20 gram tube 300 gram cart	00-051115-25265-5 00-051115-25282-2	7100039255 7100039257
PR40 (Clear)	Low viscosity for close fitting plastic/rubber parts	40	-65° to 180°F (-54° to 82°C)	< 20 sec.	24	20 gram bottle	00-051115-25204-4	7010330469
PR100 (Clear)	General purpose, low viscosity plastic bonder	100	-65° to 180°F (-54° to 82°C)	< 35 sec.	24	20 gram bottle 500 gram bottle	00-051115-25214-3 00-051115-25213-6	7100039259 7100039200
PR600 (Clear)	Medium viscosity with some gap filling for plastic/rubbers	600	-65° to 180°F (-54° to 82°C)	< 45 sec.	24	50 gram bottle 500 gram bottle	00-051115-25241-9 00-051115-25240-2	7100039244 7100039246
PR1500 (Clear)	General purpose, high viscosity for gap filling	1,500	-65° to 180°F (-54° to 82°C)	< 45 sec.	24	20 gram bottle 500 gram bottle	00-051115-25222-8 00-051115-25221-1	7100039201 7100039203
Surface In	sensive							
SI Gel (Clear)	Fast cure, gel viscosity for maximum gap filling	Gel	-65° to 180°F (-54° to 82°C)	< 30 sec.	24	20 gram bottle 300 gram cart.	00-051115-25266-2 00-051115-25284-6	7100039258 7101330472
SI1500 (Clear)	High viscosity for gap filling	1,500	-65° to 180°F (-54° to 82°C)	< 30 sec.	24	50 gram bottle 500 gram bottle	00-048011-61662-9 00-051115-25245-7	7010330477 7100039243
Low Odor								
LO1000 (Clear)	General purpose, high viscosity with reduced odor and blooming, suitable for minor gap filling	1,000	-65° to 180°F (-54° to 82°C)	< 30 sec.	24	20 gram bottle	00-051111-91664-3	7100039269

#### 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Low **Odor and MMA Acrylic Adhesives**

3M's Low Odor and MMA Acrylic Adhesives are designed for all of your sign application needs. They provide excellent impact strength, high peel strength and greatly extended shelf life compared to ordinary structural adhesives. With high structural strength, fast cure and environmental resistance, they are the first choice for the sign industry.



## 3M™ Scotch-Weld™ Instant Adhesives 🗓 🗐 🗐



#### 3M™ Scotch-Weld™ Instant Adhesives — Super Fast, Rubber Toughened and Engineered Grade

<b>Produ</b> s	test features	word	gert (ca) Terresatu	e Ronde	Handing	dicae though	, gc	zrock*
<b>Super Fast</b>								
SF20 (Clear)	Fast cure; Optimum performance on wide range of rubbers and plastics	20	-65° to 180°F (-54° to 82°C)	< 10 sec.	24	20 gram bottle	00-051111-91667-4	7100049744
SF100 (Clear)	Fast cure; High strength with EPDM and other elastomers	100	-65° to 180°F (-54° to 82°C)	< 10 sec.	24	3 gram tube 20 gram bottle 500 gram bottle	00-048011-62630-7 00-048011-62631-4 00-048011-62629-1	7100039207 7100039206 7100039208
<b>Rubber Tou</b>	ıghened							
RT5000B (Black)	Rubber toughened for impact resistance; High viscosity for minor gap filling	5,000	-65° to 180°F (-54° to 82°C)	< 40 sec.	24	20 gram bottle 500 gram bottle	00-051111-91665-0 00-051115-25200-6	7100039251 7100039252
Engineered	d Grade							
CA4	Fast setting for a variety of plastics and rubbers	150	-65° to 180°F (-54° to 82°C)	5-40 sec.	24	2 gram tube 1 oz. bottle 1 lb. bottle	00-021200-96601-9 00-021200-96600-2 00-021200-96597-5	7010366320 7000028586 7000028587
CA5	Higher viscosity, slower setting version of CA4 for filling gaps; Meets CID A-A-3097, Type II, Class 3	2,000	-65° to 180°F (-54° to 82°C)	12-60 sec.	24	1 oz. bottle 1 lb. bottle	00-021200-74289-7 00-021200-74288-0	7000046524 7010367474
CA8	Rapid setting; Excellent adhesion to metals, plastics and rubbers; Meets CID A-A-3097, Type II, Class 2	70-130	-65° to 180°F (-54° to 82°C)	5-40 sec.	24	2 gram tube 1 oz. bottle 1 lb. bottle	00-021200-21065-5 00-021200-21066-2 00-021200-21067-9	7000121354 7000046526 7000046527
* CA40	Very fast setting; Excellent adhesion to many substrates including flexible vinyl and EPDM rubber	20	-65° to 180°F (-54° to 82°C)	3-20 sec.	24	1 oz. bottle 1 lb. bottle	00-021200-74290-3 00-021200-74291-0	7000000893 7000000894
CA40H	Higher viscosity version of CA40; Better void filling capabilities	400-600	-65° to 212°F (-54° to 100°C)	5-40 sec.	24	1 oz. bottle 1 lb. bottle	00-021200-21073-0 00-021200-21074-7	7000000895 7000000896
CA50 Gel	High-viscosity, non-sag gel; Less sensitive to acidic surfaces	20,000- 50,000	-65° to 212°F (-54° to 100°C)	60-120 sec.	24	20 gram tube	00-021200-82332-9	7100002517
CA100	High peel and impact strength; High thermal shock and heat resistance	2,500- 4,500	-65° to 212°F (-54° to 100°C)	20-70 sec.	24	1 oz. bottle 1 lb. bottle	00-021200-82334-3 00-021200-82335-0	7000000900 7000000901

For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.


## 3M™ Scotch-Weld™ Anaerobic Adhesives 🗓 292




#### 3M™ Scotch-Weld™ Instant Adhesive Primers and Activators

Product	Today New Year Heart Hear House	Typical	Time to h	anding ful	ine thousy	Jr.C	stork*
AC77	Instant adhesive primer for bonding of difficult-to-bond plastics such as polyethylene, polypropylene and polyacetal	<3	1–5 sec.	24	2 fl. oz. bottle 1 gallon can	00-048011-62728-1 00-638060-40067-8	7100039260 7100190206
AC79	Instant adhesive primer for bonding of difficult-to-bond elastomers such as silicone, fluoroelastomer and EPDM VOC compliant	2	1–5 sec.	24	2 fl. oz. bottle 8 fl. oz. bottle 4 liter can	00-051115-31388-2 00-051115-31389-9 00-051115-31390-5	7100039262 7100039264 7100039265
AC113	Instant adhesive general purpose accelerator; Will not attack plastics	<3	1-5 sec.	24	8 fl. oz. bottle	00-048011-62682-6	7100079891
Surface Activator	Clear, colorless organic-based liquid helps speed curing and prime surfaces; Comes with brush and spray pump	<10	1–5 sec.	24	2 fl. oz. bottle	00-021200-87937-1	7000046525

#### **Surface Preparation Selection Guide**



#### **Threadlocker Selection Guide**



For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

## 3M™ Scotch-Weld™ Anaerobic Adhesives

#### 3M™ Scotch-Weld™ Anaerobic Adhesives — Threadlockers and Activators

Product Threadloc	Color)  Kerkoatures	rapical rapide	osity (27) Temperatur	Range Time to	Handling Full	Cure Hours	ike.	Stock**
TL22 (Purple)	Screwlock — low removal torque fasteners less than a 1/4 in. (6mm)	1,200	-65° to 300°F (-54° to 149°C)	< 30 min.	24	50mL bottle	00-048011-62602-4	7100039159
<b>TL42</b> (Blue)	Nutlock — medium strength, general purpose	1,200	-65° to 300°F (-54° to 149°C)	< 30 min.	24	1mL pipette 10mL bottle 50mL bottle 250mL bottle 1 liter bottle	00-048011-62604-8 00-048011-62605-5 00-048011-62606-2 00-048011-62607-9 00-051115-25124-5	7100064043 7100039190 7100039193 7100039192 7010310189
TL43 (Blue)	Oil tolerant, medium strength, general purpose	10,000- 18,000	-65° to 300°F (-54° to 149°C)	< 30 min.	24	10mL bottle 50mL bottle 250mL bottle	00-051115-25138-2 00-051115-25139-9 00-051115-25140-5	7100039219 7100039222 7100039221
<b>TL71</b> (Red)	Permanent studlock for bolts and studs up to 1 in. (25mm)	500	-65° to 400°F (-54° to 204°C)	< 30 min.	24	10mL bottle 50mL bottle 250mL bottle	00-048011-62612-3 00-048011-62613-0 00-048011-62614-7	7100039197 7100039231 7100039230
TL90 (Green)	Penetrating adhesive for pre-assembled fasteners and porosity sealing of welds	20	-65° to 300°F (-54° to 149°C)	< 30 min.	24	10mL bottle 50mL bottle 250mL bottle	00-048011-62615-4 00-048011-62616-1 00-048011-62617-8	7100039234 7100039236 7100039235
Activators		,						
AC649 (Green)	Acetone-based green primer for inactive or very cold surfaces 30-day part life for pre-application California compliant	<3	N/A	<5 min.	24	8 fl. oz. bottle	00-048011-62709-0	7010367620

#### 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Multi-Material Composite Urethane Adhesive DP6310NS

3M™ Scotch-Weld™ Multi-Material Composite Urethane Adhesive DP6310NS is a green, non-sag, two-component urethane for bonding a variety of composites, plastics, metals and wood. This flexible adhesive has excellent elongation; and stress strain properties for durable bonding of composite parts and multi-material assemblies.



#### 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Plastic and Rubber Instant Adhesives

The PR (Plastic & Rubber) series of products bonds to most plastics and rubbers with a range of viscosities that will fit all your application needs. Just a single drop per square inch bonds several thousand pounds of holding power. They provide proven, world record strength with a hold of 8 metric tons.



For lead times on bulk adhesives, please contact your 3M representative.

Key Product Denotes product to consider first in this category. \* After Key Products, consider these.

## **3M™ Scotch-Weld™ EPX Applicators and Nozzles**

### **3M™ EPX Applicators and Nozzles**

Roduct	Respectate to Order's	Mix Radio	Rick	ge engit medies spatie mind prioris	
3M™ Scotch-Weld™ EPX™ Plus II Applicator* Stock #: 7100148764 UPC: 00-063806-01001-7 *Includes 1:1 / 2:1 shared plunger and 10:1 plunger.	1:1/2:1 Shared Plunger <b>Stock #:</b> 7010415317	48.5mL (1:1) 50mL (2:1)	3.6	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Square Green, 48.5mL/50mL Stock #: 7100104991 UPC: 0-00-76308-86434-7	Bulk: 7100148765 Bulk: 0-00-63806-01003-1
	UPC: 00-063806-01000-0	48.5mL (1:1) 50mL (2:1)	6.2	3M™ EPX™ Mixing Nozzle Helical White, 48.5mL/50mL Stock #: 7100148766 UPC: 00-063806-01004-8	Bulk: 7100148756 Bulk: 00-063806-01005-5
387	10:1 Plunger <b>Stock #:</b> 7010329933 <b>UPC:</b> 0-00-76308-86391-3	43mL (10:1) 45mL (10:1)	3.6	3M" Scotch-Weld" EPX" Mixing Nozzle Square Orange, 45mL Stock #: 7100007806 UPC: 0-00-51115-69043-3	Bulk: 7100148756 Bulk: 00-063806-01005-5
3M™ EPX™ Pneumatic Applicator 48.5/50mL Stock #: 7100148769 UPC: 00-063806-01006-2	N/A	43mL (10:1) 48.5mL (1:1)	3.6	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Square Green, 43mL/48.5mL Stock #: 7100104991 UPC: 0-00-76308-86434-7	Bulk: 7100148765 Bulk: 0-00-63806-01003-1
388		48.5mL (1:1) 50mL (2:1)	6.2	3M™ EPX™ Mixing Nozzle Helical White, 48.5mL/50mL Stock #: 7100148766 UPC: 00-063806-01004-8	Bulk: 7100148756 Bulk: 00-063806-01005-5
3M™ Scotch-Weld™ Dual Drive Manual 1:1/2:1 Applicator 200mL Stock #: 7100244673 UPC: 00-0638060-40916-9	1:1/2:1 Shared Plunger	200mL (2:1 & 1:1)	5.0	3M" Scotch-Weld" EPX" Mixing Nozzle Square Gold, 200mL/400mL Stock #: 7000028616 UPC: 00-063806-01004-8	
389	Stock #: 7100148764 UPC: 00-063806-01001-7	400mL (2:1 & 1:1)	7.5	3M" Scotch-Weld" EPX" Mixing Nozzle Helical White, 200mL/400mL Stock #: 7000046633 UPC: 0-00-21200-87982-1	
3M™ EPX™ 400mL Manual Applicator Stock #: 7000046634 UPC: 00-051111-98073-6	N/Δ	200mL (2:1 & 1:1)	5.0	3M" Scotch-Weld" EPX" Mixing Nozzle Square Gold, 200mL/400mL Stock #: 7000028616 UPC: 0-00-21200-97331-4	
390	N/A	400mL (2:1 & 1:1)	7.5	3M" Scotch-Weld" EPX" Mixing Nozzle Helical White, 200mL/ WW400mL Stock #: 7000046633 UPC: 0-00-21200-87982-1	

# **3M™ Scotch-Weld™ EPX Applicators and Nozzles**

#### **3M™ EPX™ Applicators and Nozzles**

<b>Product</b>	Rediction	riest ortess	kketi	a Length Hitches Spain History Options	
3M™ Scotch-Weld™ Dual Drive Manual 10:1 Applicator Stock #: 7100244472 UPC: 00-638060-40914-5	N/A	490mL (10:1)	9.5	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Helical Orange, 490mL Stock #: 7100304367 UPC: 0-00-51115-69042-6	Transpersorations (IAK)
391		490IIIE (10.1)	4.4	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Square Green, 490mL Stock #: 7100066351 UPC: 0-00-51115-81619-2	
3M™ Scotch-Weld™ Dual Drive Pneumatic 1:1/2:1 Applicator 200mL Stock #: 7100244628 UPC: 00-638060-40917-6		200mL	5.0	3M" Scotch-Weld" EPX" Mixing Nozzle Square Gold, 200mL/400mL Stock #: 7000028616 UPC: 0-00-21200-97331-4	
392	N/A	(2:1 & 1:1)	7.5	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Helical White, 200mL/400mL Stock #: 7000046633 UPC: 0-00-21200-87972-1	
3M" Scotch-Weld" Dual Drive Pneumatic 1:1/2:1 Applicator 400mL Stock #: 7100244682 UPC: 0-00-638060-40918-3	NIA	400mL	5.0	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Square Gold, 200mL/400mL Stock #: 7000028616 UPC: 0-00-21200-97331-4	
393	N/A	(2:1 & 1:1)	7.5	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Helical White, 200mL/400mL Stock #: 7000046633 UPC: 0-00-21200-87982-1	
3M™ Scotch-Weld™ Dual Drive Pneumatic Applicator 490mL Stock #: 7100244681 UPC: 00-638060-40919-0	N/A	490mL (10:1)	9.5	3M™ Scotch-Weld™ EPX™ Mixing Nozzle Helical Orange, 490mL Stock #: 7100304367 UPC: 0-00-51115-69042-6	* FURNISHER STREET
394			4.4	3M™ Scotch-Weld™ EPX™ Mixing Nozzle, Low Waste Square Green, 490mL Stock #: 7100066351 UPC: 0-00-51115-81619-2	
Standard Caulk Gun	N/A	3M™ Concrete Repair Urethane 8.4 oz. cartridges	5.5	3M" Concrete Repair 8.4 oz. Cartridge Nozzles Stock #: 7000046642 UPC: 0-00-48011-53382-7	

For low volume applications and take-it-to-the-job convenience, the 3M<sup>™</sup> EPX metal manual applicators comfortably dispense any of the 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Duo-Pak Structural Adhesives. For higher volume applications, select the 200mL manual dispenser, or the 200mL or 400mL pneumatic dispenser. For concrete repair, there are both manual or pneumatic options.

3M<sup>™</sup> Scotch-Weld<sup>™</sup> One-Part Heat Cured Epoxies require a unique manual or pneumatic dispenser, such as Semco® 250, 350, 850, 950, or equivalent.

## 3M<sup>™</sup> Scotch-Weld<sup>™</sup> Structural Adhesives Surface Preparation Tips

The following surface preparation steps are generally recommended for most substrates and structural adhesives. See Technical Data Sheets for more specific recommendations.

#### Metals

- Safely wipe surface with acetone or methyl ethyl ketone (MEK) using a clean cloth.
   A heavier degreaser may be needed if the substrate contains a layer of processing oil.
- 2. Lightly abrade surface with sandblasting, fine grit sandpaper or 3M™ Scotch-Brite™ 7447 maroon pads.
- 3. Wipe surface with acetone or MEK to remove debris.
- 4. Allow surface to dry before applying adhesive.

#### **Plastics and Rubbers**

- Lightly abrade surface with sandblasting, fine grit sandpaper or 3M™ Scotch-Brite™ 7447 maroon pads.
- 2. Wipe surface with isopropyl (IPA) alcohol using a clean cloth to remove debris.
- 3. Allow solvent to evaporate before applying adhesive.

#### Glass

- Wipe surface using a clean cloth with solvent containing 0.5 wt % silane adhesion promoter or wipe with 3M™ Scotch-Weld™ Metal Primer 3901.
- 2. Allow solvent to evaporate before applying adhesive.

## 3M™ Hot Melt Adhesive Selector Guide

Step 1: Select your assembly type.



#### **Small Joint Assembly**

Small joints are typically irregularly shaped, but only a few inches of overlap area.



#### **Large Surface Lamination**

Two surfaces of similar size, either rigid or flexible, are bonded or laminated together where majority of the surface is covered by adhesive.



#### **Mounting and Trim Attachment**

Small objects are mounted or added to a large surface.



(HT) has high temperature

resistance.

## 3M™ Hot Melt Spray Adhesives 😂 292




#### **Immediate Bonding of Foam and Other Lightweight Materials**

3M<sup>™</sup> Hot Melt Spray Adhesive is a fast, effective alternative to solventbased adhesives for bonding most foams, fabrics, plastics, wood and light-gauge metals. Applications range from furniture cushions to foam inserts, modular office panels to gym floor pads, and more. You simply spray a controlled pattern of 100% solids adhesive right where you want it. Apply to one or both surfaces and bond substrates immediately.

#### Other features include:

- Up to 10-minute open time for handling convenience and bonding larger areas
- Available in two colors to easily identify spray pattern\*
- Bulk format adhesives for ease of use in most delivery systems



Can bond multiple substrates, large surface areas with 1 or 2 surface applications.



In display cases for jewelry and other retail items, foam is bonded to foam and fabric. Low temperature spray will not damage heat-sensitive substrates.



In carrying case assembly, 3M™ Hot Melt Spray Adhesive bonds foam to foam, plywood, metal or plastic.

#### **Adhesives Characteristics and Suggested Coverage**

Product Characteristics	6111 HT/6111 HT Blue
Description	Higher Heat Resistance
Color	Tan/Blue
Open Time¹ One Surface (Foam/PVC)	3 min
Open Time <sup>1</sup> Two Surface (Foam/Foam)	8 min
Heat Resistance <sup>2</sup>	175°F (79°C)
Peel Adhesion³ (PIW) Fir	25.6
ABS	16.5
Polypropylene	14.4
PVC	16.3
Cold Rolled Steel	29.9
High Density Polyethylene	2.3

Typical Coverage	Smooth Surface	Textured Surface
Two Surface Applications	1-2g/ft²	2-3g/ft²
One Surface Application	3-5g/ft²	5-7g/ft²

- 1 Bonds were made by spraying adhesive onto 3/4" thick, 2 lb. density polyester urethane foam. Open time will vary depending on substrate.
- 2 Tested per 3M IATD test method C-3093 using 2 lb. dead load.
- 3 According to 3M IATD test method C-3012. 180° peel strength was determined at a cross head speed of 2"/min. at 73°F (23°C).

<sup>\*</sup>See chart below.

## 3M™ Hot Melt Adhesives and Applicators

#### The 3M Systems Approach to Help You Improve Productivity and Lower Costs

3M™ Hot Melt Adhesives and Applicators are advanced handheld systems to help you improve productivity, lower cost and minimize waste.

Adhesives are 100% solids thermoplastic resins that become fluid when heated and quickly wet the bonding surface. They cool, harden and reach bond strength in seconds. You can move assemblies immediately to keep production flowing. This helps eliminate clamps, fixturing and drying, and saves time, energy and space.

Each adhesive is designed and precisely manufactured for efficient use in one of the portable 3M™ Hot Melt Applicators. Bonds wood, plastic, foam, fabric, cardboard and more.



For bonding the guide to a drawer bottom, 3M<sup>™</sup> Hot Melt Adhesive 3792 provides high delivery rate and long bonding range.



3M<sup>™</sup> Hot Melt Applicator LT with 3M<sup>™</sup> Hot Melt Adhesive 3762LM low temperature (265°F/129°C) adhesive effectively bonds heat-sensitive substrates such as styrene foam to itself, corrugated or other surfaces without damaging the foam.



For sample and display boards, attach wood flooring, laminates, foams, fabrics or other materials and small products with 3M" Hot Melt Adhesive 3792.



For economical package sealing, 3M™ Hot Melt Adhesive 3762 is a versatile formulation with a bonding range for production speed. Variety of tips for package types.



To help with sound dampening on drawer bottoms, use 3M™ Hot Melt Adhesive 3792.



3M<sup>™</sup> Hot Melt Applicator LT and 3M<sup>™</sup> Hot Melt Adhesive 3792LM applied at low temperature (265°F/129°C) make quick work of welting, gimping, and bonding fabric to wood.



For versatility in P.O.P. assembly, 3M<sup>™</sup> Hot Melt Adhesive 3792 bonds a variety of plastics, woods and light gauge metals.

# Selecting a 3M™ Hot-Melt Applicator to Fit Your Needs



132

3M<sup>™</sup> Hot Melt Applicator TC with Quadrack, Gen II Converter. Medium volume. UPC# 68060-001481



129

3M™ Pneumatic Hot Melt Applicator PG II LT with Speedloader. High volume using low melt adhesive.

UPC# 021200-89395



134

3M™ Hot Melt Applicator AE, Gen II. Low volume.

UPC# 68060-002143





130

3M™ Hot Melt Applicator TC, Gen II. Low-medium volume.

UPC# 68060-001474





133

 $3M^{\!^{\intercal}}$  Pneumatic Hot Melt Applicator PG II with Speedloader. High volume.

UPC# 021200-22033





134

3M<sup>™</sup> Hot Melt Applicator AE, Gen II. Low volume.

UPC# 68060-002167





135

3M<sup>™</sup> Hot Melt Applicator EC, Gen II. Medium volume; variable temperature control. UPC# 68060-001443



## **3M™ Hot Melt Applicators**

Product	Weight <sup>1</sup>	Output <sup>2</sup> (lb./hr.)	Temp.³ °F (°C)	Power (120V)	Adhesive Dia. x L (in.)	Features	Warranty (Months)
Low Melt Applicators							
A 3M™ TC/TC-Q GEN II	1.05 lbs	4.0	265 (129)	250W	5/8 × 2 TC 5/8 × 8 Q	For use with low melt adhesives in TC or Quadrack Style.	12
Pneumatic PGII LT with Speedloader	4.3 lb	6.0	265 (129)	500W	1 × 3 PG	Pneumatic high output for low melt adhesives.	12
© 3M™ AE GEN II	1.05 lbs	4.0	265 (129)	250W	1/2 × 10 AE 1/2 × 12 AE	For use with low melt adhesives.	12
Hot Melt Applicators							
D 3M™ TC/TC-Q GEN II	1.05 lbs	4.0	380 (193)	250W	5/8 × 2 TC 5/8 × 8 Q	For use with standard melt adhesives in TC or Quadrack Style	12
E Pneumatic PG II with Speedloader	4.3 lb	7.5	385 (196)	500W	1 × 3 PG	Pneumatic high output for standard melt adhesives.	12
F 3M™ AE GEN II	1.05 lbs	4.0	380 (193)	250W	1/2 × 12 AE	For use with standard melt adhesives	12
Variable Applicators							
© 3M™ EC GEN II	1.4 lb	5.5	160 (320), 180 (356), 195 (380), 205 (401), 215 (419)	300W	5/8 × 8 Q	Temperature modules to operate with standard and low melt adhesives	12

- 1 Weight shown is for applicator only; does not include adhesive capacity.
- 2 Adhesive output will vary with conditions and the adhesive used. Values are approximate and are based on maximum steady-state flow.
- 3 Temperatures shown are nominal control values. Actual temperature will range slightly above and below this value.

#### **Accessories to Improve Your Productivity**

Product	Description	UPC	SN
9725	0.072 in. Mini Extension Tip	021200-21786	62-9725-9930-2
9785	0.07 in. Tapered Aluminum Extension (all applicators)	021200-82554	62-9785-9930-6
9921	0.090 in. Fluted Tip	021200-21840	62-9921-0066-9
9929	High Viscosity Valve (TC, EC, PG II)	021200-64840	62-9729-9930-4
9940	0.125 in. Fluted Tip	021200-22036	62-9940-6920-1
9946	0.072 in. Brass Extension (PG II, PG II LT)	021200-22040	62-9946-6980-2
Heavy-Duty	For use with PG II and PG II LT	021200-22039	62-9945-9930-6
Benchstand	For use with EC, TC and LT	021200-82418	62-9945-9935-5
Bench Mount	Includes bench nozzle assembly (Does not include applicator)	021200-82277	62-9276-9930-6
Bench Nozzle Assembly	For use with bench mounted applicator	021200-21713	62-9233-2781-1
Foot Pedal Assembly	For use with bench mounted applicator	021200-82278	62-9277-9930-4





Heavy-Duty Benchstands provide added convenience.





Foot pedal, magazine feeder and benchmount accessories can provide high capacity, hands-free operation for 3M™ Hot Melt PG II and PG II LT Applicators.



## 3M™ Hot Melt Adhesives

	Product/Cat #	Color	Features/Application Ideas	Sizes	Legacy SKU	SAP SKU	Case Qty.	Billing Unit	
<b>⊕</b>	Froduct/ Cat #	Color	Teatures/Application lueas	5/8 in. x 8 in. Q	62-3720-9132-2	7100025246	11	Offic	
35°C			Excellent "hot tack", fast setting for corrugated,	5/8 in. x 2 in. TC	62-3720-9132-2	7000121330	11		
logy 1-1	3762LM* Lead Product	Light Amber	beadboard, recouperage, repacking chipboard and wood. Economical, general purpose. Use with low	1 in. x 3 in. PG	62-3720-9330-2	7000121328	22	LBS.	
halol (12			melt applicator only.	1/2 in. x 12 in. AE	62-3720-9531-5	7000121329	11		
Tec 70°1									
Mel.				5/8 in. x 8 in. Q	62-3760-9132-8	7000000880	11		
Low Melt Technology: Applied 250–270°F (121–132°C)	3792LM* Lead Product	Clear	Clear, multi-purpose for wood, coated paper, polyolefins and other heat-sensitive materials.	5/8 in. x 2 in. TC	62-3760-9830-7	7000121341	11	LBS.	
pplie			P.O.P. displays. Use with low melt applicator only.	1 in. x 3 in. PG	62-3760-9330-8	7100020424	22		
⋖				1/2 in. x 12 in. AE	62-3760-9531-1	7100042234	11		
			I	5/0: 0: 0	00 0704 0400 0	7100000105	11		
	3731*	Tan	High heat resistance. Bonds plastics including polyethylene, polypropylene.	5/8 in. x 8 in. Q 1 in. x 3 in. PG	62-3731-9132-9 62-3731-9330-9	7100009195 7100020337	11 22	LBS.	
				5/8 in. x 8 in. Q	62-3738-9132-4	7100020007	11		
		_	High delivery rate and long bonding range. General	5/8 in. x 2 in. TC	62-3738-9830-3	7100009196	11		
	3738*	Tan	purpose for foundry sand cores, wood bonding, corrugated, selected plastics and chipboard.	1 in. x 3 in. PG	62-3738-9330-4	7100020456	22	LBS.	
				1/2 in. x 12 in. AE	62-3738-9531-7	7100023046	11		
				5/8 in. x 8 in. Q	62-3747-9132-5	7000000877	11		
	3747 Lead Product	Tan	General purpose for wide variety of plastics, wood	5/8 in. x 2 in. TC	62-3747-9830-4	7000121336	11	LBS.	
	3747 Product	l lall	and lightweight metals.	1 in. x 3 in. PG	62-3747-9330-5	7100020458	22	LDO.	
				1/2 in. x 12 in. AE	62-3747-9531-8	7100020323	11		
		Off-	Good thermal shock resistance. Non-corrosive to	5/8 in. x 8 in. Q	62-3748-9132-3	7000000878	11		
		White	copper for many electronic applications. Bonds	5/8 in. x 2 in. TC	62-3748-9830-2	7000000879	11	LBS.	
			polyolefins.	1 in. x 3 in. PG	62-3748-9330-3	7100005566	22		
		Light Yellow Self-extinguishing version of 3748. Meets UL 7	Salf-extinguishing version of 37/18 Meets III 1/10	5/8 in. x 8 in. Q	62-3768-9132-1	7000000887	11		
				5/8 in. x 2 in. TC	62-3768-9830-0	7000121345	11	LBS.	
ତ				1 in. x 3 in. PG	62-3768-9330-1	7010330271	22		
Hot Melt Technology: Applied 350-385°F (177-196°C)	3750	Tan	Low viscosity for high flow rate, increased production. Good hot tack, quick grab for packaging and woodworking.	1/2 in. x 10 in. AE	62-3726-9531-2	7000121331	11	LBS.	
Fechnol 15°F (17	3750	Clear	Low viscosity for high flow rate, increased production. Good hot tack, quick grab for packaging and woodworking.	1/2 in. x 10 in. AE	62-3729-9531-6	7000046499	11	LBS.	
et 1			5/8 in. x 8 in. Q	62-3762-9132-4	7100023053	11			
35C	3762 Lead	Tan	Excellent "hot tack", fast setting for corrugated, beadboard, recouperage, repacking chipboard	5/8 in. x 2 in. TC	62-3762-9830-3	7100020333	11	LBS.	
동혈	3762 Product		and wood. Economical, general purpose.	1 in. x 3 in. PG	62-3762-9330-4	7000046513	22	250.	
ρ				1/2 in. x 12 in. AE	62-3762-9531-7	7100023019	11		
			Dender which of also the budies and business	5/8 in. x 8 in. Q	62-3764-9132-0	7100008178	11		
	3764* Lead Product	Clear	Bonds variety of plastics including polycarbonate, polyethylene, and polypropylene. Flexible at low	5/8 in. x 2 in. TC	62-3764-9830-9	7000000886	11	LBS.	
			temperatures.	1 in. x 3 in. PG	62-3764-9330-0	7000000884	22		
				1/2 in. x 12 in. AE	62-3764-9531-3	7000000885	11		
	3779*	Amber	High heat resistance. High strength.	5/8 in. x 8 in. Q 5/8 in. x 2 in. TC	62-3779-9132-8 62-3779-9830-7	700000088	11 11	LBS.	
	3779"	Amber	Electronics wire attachment.	1 in. x 3 in. PG	62-3779-9330-8		22	LBS.	
							11		
	3789*	Brown	High performance for plastics. Impact resistant. Bonds vinyl and wood.	5/8 in. x 8 in. Q 1 in. x 3 in. PG	62-3789-9132-7 62-3789-9330-7	7100008737 7100020457		LBS.	
			Bonds vinyr and wood.				22		
				5/8 in. x 8 in. Q	62-3792-9132-1	7000000891	11		
	3792* Lead Product	Clear	Clear, multi-purpose for wood, corrugated, fabric, furniture, upholstery, novelties, and other	5/8 in. x 2 in. TC	62-3792-9830-0	7100020336	11	LBS.	
	The state of the s		lightweight materials.	1 in. x 3 in. PG	62-3792-9330-1	7100020334	22		
				1/2 in. x 12 in. AE	62-3792-9531-4	7100020335	11		
	3797	Off- White	High ball and ring. Low viscosity. Good for electrical potting.	5/8 in. x 2 in. TC 1 in. x 3 in. PG	62-3797-9830-9 62-3797-9330-0	7000121350 7000000892	11 22	LBS.	
					100000				
			T		60 6445 0005 :	7100000000			
늗			Sprayable hot melt adhesive, bonds to polyurethane		62-6115-9335-1		22		
Bulk Only	6111HT Lead Product	Tan, Blue	foam, felt, fabric and lightweight aluminum. Available	0.75 in. x 0.75 in. chips	62-6113-9335-6		22	LBS.	
Bull		] Dide	in Tan and Blue.	Cilips	62-6113-9339-8		850		
					62-6115-9339-3	7010309934	850	L	

<sup>\*</sup>Also available in bulk.

<sup>\*\*</sup>Initial starting point for temperature modules.

<sup>1.</sup> Brookfield Thermosel Viscometer in Centipoise; 2. Douglas Fir to Douglas Fir; 3. 1/8" semicircular bead, Douglas Fir to Douglas Fir; 4. Made from components listed as indirect food additives under FDA regulations for adhesives (21 CFR 175.105).

## **3M™ Hot Melt Adhesives**

	- 1 · / 2 · //	EC Temp. Control Modules**	VII 1: 070	Delivery Time 3 in. Length	Shear Strength PSI <sup>2</sup>	Open Time	FDA	UL 94
ត	Product/Cat #	Control Modules**	Viscosity CPS <sup>1</sup>	of Stick Type (sec.)  Q-TBD	72°F (22°C)	1/8 in. Bead <sup>3</sup> (sec.)	Listed <sup>4</sup>	Listing
Low Melt Technology: Applied 250–270°F (121–132°C)				TC-TBD				
logy 21–1	3762LM* Lead Product	N/A	4,000 @ 250°F	PG-45	Fir: 375	25	Yes	N/A
chno F (1)				AE-10				
lt Te				Q-15				
, Me				TC-TBD				
Low ied 2	3792LM* Lead Product	N/A	10,500 @ 250°F	PG-60	Fir: 280	40	Yes	V2
Appl				AE-TBD				
				7.2.755				
	3731*	420°F (215°C)	12,000 @ 375°F	Q-30	Fir: 490	30	_	N/A
	3731	(215°C)	12,000 @ 373 1	PG-65	PP: 430	30		IVA
				Q-TBD TC-15				
	3738*	400°F (205°C)	2,875 @ 375°F	PG-35	Fir: 350	50	Yes	V2
				AE-TBD				
	_			Q-15	Fir: 430			
	3747 Lead Product	400°F	4,100 @ 375°F	TC-TBD	Steel: 410	45	Yes	N/A
		(205°C)	,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,	PG-45	PVC: 410			
		h =-		AE-TBD Q-25		30		
	3748*	400°F (205°C)	5,750 @ 356°F	TC-TBD	Fir: 250		Yes	V2
		(203 C)		PG-65				
		400°F		Q-30				
	3748 VO	(205°C)	5,500 @ 392°F	TC-TBD PG-65	Fir: 205	30	_	VO
ပ္ပိ				FG-03				
gy: -196	3750	N/A	2,550 @ 375°F	AE-6	500, TBD	30	_	N/A
Hot Melt Technology: Applied 350–385°F (177–196°C)	3750	N/A	4,100 @ 375°F	AE-10	250, TBD	30	_	N/A
elt T		350°F		Q-15		35	Yes	
350	3762 Lead Product	(180°C); 380°F	4,650 @ 300°F	TC-TBD	545			V2
H H		(195°C)		PG-30 AE-TBD				
App				Q-20				
	3764* Lead Product	400°F	6,000 @ 375°F	TC-TBD	390	30	Yes	V2
	3764" Product	(205°C)	6,000 @ 375 F	PG-55	390	30	res	VZ
				AE-TBD				
	3779*	420°F	7,000 @ 375°F	Q-TBD TC-TBD	700	25	Yes	N/A
		(215°C)	.,,,,,,,,,	PC-75				
	3789*	420°F	5,200 @ 375°F	Q-25	570	50	Yes	V2
	3769"	(215°C)	5,200 @ 375 F	PG-70	570	50	res	VZ
		h-a		Q-15				
	3792* Lead Product	400°F (205°C)	5,000 @ 375°F	TC-TBD	250	<50	Yes	V2
		(203 C)		PG-45 AE-TBD				
		05005						
	3797	350°F (180°C)	3,600 @ 350°F	TC-20 PG-55	PP: 330	30	Yes	V2
				I	T	T		
Bulk Only	6111HT Lead Product	N/A	2,500-4,500 @ 375°F	N/A	PP: 300	1 surface: 180 2 surface: 480	_	N/A
B								

<sup>\*</sup>Also available in bulk.

<sup>\*\*</sup>Initial starting point for temperature modules.

## **Solvent and Water Based Adhesives**

#### Unite Performance, Productivity and Sustainability

3M™ Solvent and Water Based Adhesives start with the customer. Their process, their requirements and their wishes. Then the 3M team of industry experts, in conjunction with our comprehensive technology portfolio, offers customers versatility, efficiency and confidence to answer their "what if?"



#### **Performance**

## Find the RIGHT product for your assembly with the RIGHT questions:

- What substrates are being bonded?
- What are the issues with your current product?
- Are there any environmental Health and Safety requirements?
- Are there specific product attributes needed?
- Are there specific manufacturing requirements?
- What is the size of the substrate being sprayed?

#### Sustainability

#### Low Emissions. High Standards.



Going "green" does not mean that you have to give up on performance. For 40 years our engineers have been developing water-based, low VOC and GREENGUARD Certified adhesives that have been used in the most demanding applications.

# So, are you ready to go "green?" We're ready to take you there.



#### **Productivity**

Our goal is to make your business as efficient and effective as possible. How the adhesive gets to your assembly is equally as important as the adhesive itself. We work with you to integrate the best delivery system for your process.



#### **Cylinders**

- Self-contained and pressurized
- Portable
- Minimal equipment investment
- Low maintenance
- Optimized spray pattern cuts waste and maximizes coverage



#### **Aerosols**

- Convenient for smaller jobs or multiple stations
- Easy to use and no equipment



#### Bulk

- Cost effective
- Integrate into existing equipment

# Multipurpose Adhesives — Solvent and Water Based

## Insulation, Light Fabrics, Cardboard and Other Light Duty Bonding

Those working with HVAC, General Industrial, Signage, Exhibit/P.O.P. and packaging can effectively bond insulation, light fabrics, cardboard and paper with these versatile adhesives.

- Insulation attachment (polystyrene\*, fiber glass, foam, etc.)
- General assembly
- Temporary holding (third hand)
- P.O.P. displays
- Carton sealing, palletizing and label attachment

<sup>\*</sup>Not all products are compatible with polystyrene.



	MULTI-PURPOSE — Water Based Adhesives								
	Product	Requirement	Size Ava	ilability					
Key Product	1000NF	ONF ONE-SIDED BONDING		Bulk					
	49	Long open time, long tack time		Bulk					
	100NF	Immediate bonding		Bulk					





3M multipurpose adhesives are commonly used for installation of shoddy material, venting insulation and other foams and fabrics. Our product line offers the most versatility for adhesive delivery. 3M™ Super 77™ Multipurpose Spray Adhesive, for example, can be sprayed from bulk containers, cylinders or aerosol cans.



When thinking insulation, don't stop at heating and ventilation. In this application, our adhesives can be used for installation of foam for acoustical soundproofing.







The variety of applications for these multi-purpose adhesives is nearly endless. From adhering pool table felt, to building architectural models, and even bonding protective materials like dense foams into electronics, musical instrument or sensitive equipment cases. 3M has a spray adhesive solution to fit customers' needs.

## Woodworking and Large Surface Lamination — **Solvent and Water Based**


#### Wood, Metal and Rubber Flooring

Woodworking, transportation, construction, and general industrial markets can effectively bond metals, wood, rubber, carpet and flooring (vinyl tiles) with this line of adhesives. Some applications include transportation flooring and carpet, store fixtures and furniture.

- High pressure laminate (HPL) Edge banding
  - Countertops
  - Furniture
  - Display fixtures
- Specialty vehicle flooring
- Wood furniture
- Trade show displays



Marine and specialty vehicle applications, like installing carpet, rubber or synthetic flooring, are perfect for 3M sprayable adhesives. Our quick tack, low VOC and cylinder delivery are common benefits in this market.



	HEAVY-DUTY — Water Based Adhesives								
	Product	Size	Availability						
Key Product	30NF	HIGH STRENGTH		Bulk					
	2000NF	Faster initial strength		Bulk					
	1000NF	One surface bonding, fast assembly, plasticizer resistance		Bulk					

Bulk

Cylinder

Aerosol



Consider trade show exhibits and store fixtures that are often updated several times a year. 3M's adhesive line offers very low cost per square foot bonded for applications where our customers value total applied cost.



3M" Hi-Strength 90 Spray Adhesive has a long reputation of holding strong in critical applications like this edge banding strip. Also, 3M has multiple adhesives that are postformable. Postforming is where the laminate is heated and bent as much as 360° around a radius.

# Foam and Fabric Adhesives — Solvent and Water Based

#### **Upholstery and Furniture**

Users in the furniture manufacturing, upholstery, or transportation industry can rely on these adhesives to permanently bond open cell foam, closed cell foam and fabrics in a variety applications.

- Upholstered furniture and seating
- Headliners
- Office partitions
- General foam bonding

FOAM & FABRIC — Solvent Based Adhesives									
Product Requirement Size Availability									
74	Soft bond lines		Aerosol Cylinder						
77	Low soak in, mist spray		Aerosol Cylinder Bulk						

	FOAM & FABRIC — Water Based Adhesives								
	Product	Requirement	Size Ava	ilability					
Key Product	100NF	HIGH COVERAGE	Ĩ	Bulk					
	100NF + Activator	Faster initial strength	Î	Bulk					
	1000NF	One surface bonding, higher heat resistance		Bulk					





Foam and fabric applications can be very challenging. From soft bond lines to tight radiuses, our lineup can meet the demand. The 3M portfolio of water and solvent based adhesives truly give the customer "flexibility."



Aerosol adhesives provide either web or mist spray patterns with higher solid content than our competitors. This combination allows 3M adhesives to sit on the surface versus soaking in. More adhesive on the surface results in less adhesive usage and a better bond for the customer.




These solvent and water based adhesives are often used as a "third hand" to hold lightweight materials in place until they can be sewn or held in place by other assembly methods.

# High Performance Specialty Adhesives — Solvent and Water Based

#### **Rubber and Plastic**

Industrial, and Automotive professionals can rely on these adhesives to effectively bond rubber, plastics and specialty composites.

- Sealing and gasketing
- Chemical resistance
- Unique environments
  - Harsh environments
  - Chemical resistance



	SPECIALTY — Plastic Adhesives									
	Product	Size Availability								
Key Product	1099	RESISTS WATER, OIL AND PLASTICIZER	Bulk							
	1099L	Sprayable, low viscosity	Bulk							
	4693	Polyolefin bonding	Bulk							
	2262	Clear drying	Bulk							





In washing machine repair, 3M<sup>™</sup> Neoprene High Performance Rubber and Gasket Adhesive 1300 bonds with high immediate strength and seals the doughnut ring seal in the outer tub.



With excellent resistance to fuel and oil, 3M™ Nitrile High Performance Rubber and Gasket Adhesive 847 bonds and seals chemical drum gaskets in place.





## 3M™ Cleaners and Lubricants

# Convenience and a Fistful of Work Power for Maintenance and Production

In thousands of factories and plants, these aerosol chemicals are proven daily to save time and effort in maintenance and production. Lubricating, cleaning, inhibiting rust, and other tough jobs become finger-touch easy.

Compact container fits in a tool box to go readily to any job site and can help you reduce storage space and cost. With targeted application you get more usable product for your money.

3M aerosol chemicals contain no methylene chloride, chlorofluorocarbons (CFCs) or 1,1,1-trichlorethane (methyl chloroform).





3M<sup>™</sup> Silicone Spray Low VOC 60% lubricates cutting tools and tables. Fast, easy application helps prevent buildup of adhesive, wax, inks and paints. Won't stain or become gummy.



For fast, easy cleanup of gears, 3M™ Industrial Citrus Base Cleaner helps soften and loosen grease, oil and grime. After using this heavy-duty degreaser/cleaner, just wipe away with a shop towel.



3M™ Adhesive Remover removes adhesive without damaging surface underneath.

MAINTENANCE AND	MAINTENANCE AND CLEANING										
Product	Key Characteristics	Available Format	Color	Application Method	Spray Pattern	VOC Content					
		1 gal., 5 gal., 52 gal.	Pale Yellow	Brush/Roll/Spray	Mist	840g/L					
Adhesive Remover	Citrus based. Fast acting. No residue left behind.	18.5 oz. Aerosol	Pale Yellow	Spray	Mist	100%					
	Tvo residue fert beriind.	Mini Cylinder	Pale Yellow	Spray	Mist	800g/L					
Adhesive Remover – Low VOC <20% Clear	Extended dwell time. No residual film. Meets CARB/OTC VOC Requirements. Helps contribute to LEED® credits.	Aerosol	Clear	Spray	Mist	15%					
Industrial Citrus Base Cleaner	Citrus based. Non-corrosive. Cleans oil, grease, tar and grime.	Aerosol	Transparent	Spray	Mist	91%					
Silicone Spray 60% VOC	Excellent lubricant. Fast drying. Long lasting and non-staining.	Aerosol	Clear	Spray	Mist	60%					
Silicone Lubricant	Excellent lubricant. Fast Drying. Long-lasting and non-staining.	Aerosol	Clear	Spray	Mist	95%					

## 3M™ Cylinder Spray Adhesives

#### **Efficient, Portable and Easy to Use**

3M™ Cylinder Spray Adhesives have benefits over more traditional spray methods. Minimal startup costs, reduced downtime, simple hose and applicator setup make cylinders an obvious choice.

Whether your priorities are improving speed of application, making spraying easier or reducing capital equipment maintenance and other costs, 3M Cylinder Spray Adhesives get you there.

#### Advantages and benefits:

- Very efficient speed of application and reduction of overspray
- Convenient, portable and easy to use delivery system
- Maintenance free and very low equipment costs

#### Other benefits include:

- More efficient spraying over large surface areas or multiple parts means virtually all adhesive is used and very little is wasted
- Easy to learn, use and train new employees to spray
- Portable for easy transition and setup for multiple stations or field work

#### Key features include:

- High coverage
- Various spray patterns
- Greenguard Certified
- Range of open time (worklife)



146





Spray patterns from 1–18+" are achievable using  $3M^{\sim}$  Cylinder Spray Adhesives and various spray tips.

## Where to Start

#### **Product Selection**

The lead products for 3M™ Cylinder Adhesives are:

- 3M<sup>™</sup> Postforming 94 CA Cylinder Spray Adhesive
- 3M™ Hi-Strength 94 ET Cylinder Spray Adhesive
- 3M™ Holdfast 70 Cylinder Spray Adhesive

The majority of applications can be done with these three cylinder products.



3M™ Postforming 94 CA Cylinder Spray Adhesive is a low telegraphing that dries quickly to reach postformable strength in 1–5 minutes. A 1–15 minute open time provides flexibility in assembly speed. 3M™ Hi-Strength 94 ET Cylinder Spray Adhesive offers all the benefits of 3M™ Postforming 94 CA Cylinder Spray Adhesive, but delivers a higher tack and increased bonding range.



For fast, easy foam board installation, above and below grade, simply spray and stick with 3M™ HoldFast 70 Cylinder Spray Adhesive. Bonds foam to concrete, waterproofing, OSB and more without damaging the foam.

## Save Yourself the Hassle of Inefficient Spraying

#### Most common applications:

- High pressure laminate
- Foam/paper core steel door
- Upholstery
- Metal lamination
- Insulation bonding

#### Where to find these applications:

- Cabinet shops
- Elevator interiors
- Countertop shops
- Exhibit manufacturing
- Fixture/display manufacturing
- Office furniture
- Theatre/production sets
- Acoustic panel/partition

#### **Key Questions**

Asking the right questions related to the application will help you arrive at an adhesive selection quickly and painlessly.

#### Use A.S.P.E.C.

- What is the **APPLICATION** you are currently using the adhesive for?
- What **SUBSTRATES** does the adhesive need to bond too?
- Are there special **PROCESS** details the adhesive needs to accommodate? Such as high temperatures or VOC regulations?
- What kinds of END USE stress or environment will the bond be subject to? (e.g., boat carpet and saltwater conditions or exterior applications).
- How do you determine the **VALUE** beyond simply the **COST** of a product? (e.g., Improved coverage, reduced flammability or speed of application).



3M™ Cylinder Spray Adhesives do not atomize spray patterns with added airline. This means you get consistent even spray patterns, potentially saving rework and cleanup.



Consistent spray patterns and portable cylinders mean you can realize big improvements in efficiency and save time and labor costs.

#### 3M™ Cylinder Spray Adhesive Quick Reference Guide

Product	Application	Solids (%)	Solids – Bulk (%)	Cylinder VOCs (g/L)	Coverage*	Open Time (min)	Spray Pattern	Spray Applicator Type	Suggested Tips		
General Pu	General Purpose										
60CA	General Purpose	43	42	<80	2075	1-60	Lace	Standard	9501, 6501		
Specialty											
70	Construction, Marine, RV, Polystyrene	21	26	544	1036	1-60	Lace	Standard	QSS tip		
71	Composites	20	NA	<80	1090	1-20	Mist	Standard	250050, 650050		
74	Foam Bonding	22	36	563	1151	1-15	Lace	Standard	9501, 6501		
77	Multi-Purpose	27	36	548	1458	1-15	Mist	Standard	250050, 650050		
78 ET	Polystyrene	17	35	582	894	1-60	Lace	Standard	9501, 6501		
High Perfo	rmance, High Temp	erature Lam	inating								
78 HT	Polystyrene	15	27	601	771	1-60	Lace	Standard	9501, 6501		
90	Laminating	13	23	571	680	1-10	Lace	Standard	9501, 6501, 250050		
92	Laminating	23	34	577	1224	1-20	Lace	Standard	9501, 6501, 250050		
94 CA	Laminating	28	34	<80	1332	1-15	Pebble	Restricted	4001, 6501		
94 ET	Laminating	25	25	<80	1189	1-60	Pebble	Restricted	4001, 6501		

#### 3M™ Cylinder Spray Adhesive Equipment and Accessories







OSS





**Hose Swivel** 





Spray Tip	Angle	Spray Pattern Width
9501	95°	Wide
6501	65°	Medium
4001	40°	Narrow
QSS*	_	Very Wide
250050	25°	Very Narrow
650050	65°	Medium

\*For 3M™ HoldFast 70 Spray Adhesive.

Note: The technical information and data on these pages should be considered representative or typical only and should not be used for specification purposes.

**T-Fitting** 

## 



Product	Available Format	Solids Weight Percent (Approx.)	Key Characteristics	Adhesive Strength	Color	Application Method	Bonding Range (Two Surfaces)	Flammability	Heat Resistance (SAFT)	Spray Pattern	VOC Content
MULTI-PURPOSE											
Multi-Purpose 27	Aerosol	21%	Fast tack. Lightweight applications. Mist spray pattern.	Low	Clear	Spray	15 sec- 10 min	Flammable	140°F	Mist	59%
General	5 gal., 54 gal.	43%	High solids for increased coverage. High tack general purpose adhesive.	Medium	Clear	Brush/Roll/ Spray	1-60 min	Flammable	170°F	Pebble	79g/L
Purpose 60 CA	Large, Int. Cylinder	42%	High solids for increased coverage. High tack general purpose adhesive.	Medium	Clear	Brush/Roll/ Spray	1-60 min	Flammable	170°F	Pebble	73g/L
	5 gal., 52 gal.	26%	Extremely versatile and very fast tacking. Unique wide web spray pattern with	Medium	Clear	Brush/Roll/ Spray	1-60 min	Flammable	190°F	Web	562g/L
HoldFast 70	Large, Int. and Jumbo Cylinder	21%	heavy body and low soak-in. Bonds polystyrene without degrading surface.	Medium	Clear	Brush/Roll/ Spray	1-60 min	Flammable	190°F	Web	562g/L
	Aerosol	25%		Low	Clear	Spray	15 sec- 15 min	Flammable	150°F	Mist	54%
Super 77™	5 gal., 52 gal.	36%	Low soak-in for long lasting bond. High coverage and aggressive tack. Bonds quickly in 15 seconds.	Low	Clear	Brush/Roll/ Spray	15 sec- 15 min	Flammable	150°F	Mist	504g/L
	Large Cylinder	27%	15 seconds.	Low	Clear	Spray	15 sec- 15 min	Flammable	150°F	Mist	535g/L
Super 77™ CA Multi-Purpose (Low VOC)	Aerosol	19%	Aggressive tack. Quick bonding. Long bonding range.	Low	Clear	Spray	15 sec- 30 min	Flammable	205°F	Mist	<25%
Fastbond™ Insulation Adhesive 49	5 gal. box, 5 gal., 50 gal., 100 gal., 255 gal.	55%	Fast tacking, high performance, pressure sensitive adhesive for lightweight materials. Low VOC and GREENGUARD Certified. UL MAGW2 component recognition.	Low	Clear	Brush/Roll/ Spray	5 min.– 8 hrs.	Non- flammable	-	Mist	2g/L
HEAVY DUTY											
Neoprene Contact 5	5 gal., 53 gal.	19%	High performance contact adhesive. Sprayable. Fast drying.	High	Light Yellow	Spray	10-60 min	Flammable	300°F	Web	687g/L
Neoprene Contact 10	1 qt., 1 gal., 5 gal., 54 gal.	23%	Brushable and rollable with higher coverage.	High	Light Yellow	Brush/Roll	10-60 min	Flammable	300°F	Web	589g/L
Heavy Duty 20	Aerosol	17%	Fast grab. Variable width spray pattern. Forms strong bonds to a variety of substrates.	High	Clear	Spray	1-30 min	Flammable	210°F	Web	52%
	5 gal., 52 gal.	23%	High strength. High temperature resistance.	High	Clear	Brush/Roll/ Spray	1–10 min	Flammable	250°F	Web	356g/L
Hi-Strength 90	Large, Int and Jumbo Cylinder	13%	High strength. High temperature resistance.	High	Clear	Spray	1–10 min	Flammable	250°F	Web	586g/L
	Aerosol	13%	High strength. High temperature resistance.	High	Clear	Spray	1–10 min	Flammable	250°F	Web	54%

# 



Product HEAVY DUTY	Available Format	Solids Weight Percent (Approx.)	Key Characteristics	Adhesive Strength	Color	Application Method	Bonding Range (Two Surfaces)	Flammability	Heat Resistance (SAFT)	Spray Pattern	VOC Content
Hi-Strength 90 CA (Low VOC)	Aerosol	23%	High strength.	High	Clear	Spray	1-30 min	Flammable	200°F	Web	<25%
	5 gal., 54 gal.	34%	High strength. High temperature resistance. Versatile, high-tack adhesive.	High	Clear/ Red	Spray	1–20 min	Flammable	250+°F	Web	577g/L
Hi-Strength 92	Large, Int and Jumbo Cylinder	23%	High strength. High temperature resistance. Versatile, high-tack adhesive.	High	Clear/ Red	Spray	1–20 min	Flammable	250+°F	Web	577g/L
Hi-Strength Postforming	5 gal., 54 gal.	34%	High solids for increased coverage. Unique non-telegraphing spray pattern with	High	Clear/ Red	Brush/Roll/ Spray	1–15 min	Flammable	210°F	Pebble	79g/L
94 CA (Low VOC)	Large, Int	28%	postformable strength. Low VOC, SCAQMD 1168 and LEED® Compliant.	High	Clear/ Red	Spray	1–15 min	Flammable	210°F	Pebble	79g/L
Fastbond <sup>™</sup> Contact Adhesive 30NF	1 qt., 1 gal., 5 gal., 52 gal., 270 gal.	49%	Non-flammable water-based contact adhesive. Extremely high strength, high temperature resistant. Meets MIL-A-24179A, Type I, GREENGUARD Certified, SCAQMD 1168, LEED® Compliant.	High	Neutral/ Green	Brush/Roll/ Spray	30 min.– 4 hours	Non- flammable	300°F	Mist	37g/L
Fastbond™ Contact Adhesive 30H	52 gal., 270 gal.	48%	Long bonding range with high immediate bond strength. Economical high coverage. Low mist version of 30NF.	High	Green	Brush/Roll/ Spray	30 min.– 4 hours	Non- flammable	300°F	Mist	37g/L
Fastbond™ 2000NF	5 gal., 50 gal., 270 gal.	49%	Water dispersed, activated adhesive. Immediate bonding and handling strength without forced drying. GREENGUARD Certified.	High	Blue/ Light Orange/ Neutral	Co-Spray	2 min.– 2 hours	Non- flammable	300°F	Mist	37g/L
FOAM & FABRIC											
Foam & Fabric 24	Aerosol	17%	Aggressive tack. Foam-tearing strength. Variable width lace spray pattern.	Medium	Orange	Spray	30 sec 30 min.	Flammable	170°F	Web	53%
	Aerosol	22%	Extremely fast tack. Soft non-dimpling glue line. Immediate foam tearing strength.	Medium	Clear/ Orange	Spray	30 sec- 15 min	Flammable	170°F	Web	<55%
Foam Fast 74	52 gal.	36%	Extremely fast tack. Soft non-dimpling glue line. Immediate foam tearing strength.	Medium	Clear/ Orange	Brush/Roll/ Spray	30 sec- 15 min	Flammable	170°F	Web	352g/L
	Large, Int and Jumbo Cylinder	22%	Extremely fast tack. Soft non-dimpling glue line. Immediate foam tearing strength.	Medium	Clear/ Orange	Brush/Roll/ Spray	30 sec- 15 min	Flammable	170°F	Web	563g/L
Foam Fast 74 CA (Low VOC)	Aerosol	23%	Extremely fast tack. Soft non-dimpling glue line. Immediate foam tearing strength.	Medium	Clear/ Orange	Spray	30 sec- 15 min	Flammable	200°F	Web	<25%
Fastbond™ Foam Adhesive 100NF	1 gal., 5 gal., 52 gal., 100 gal., 255 gal.	47%	One-part, fast setting — foam and fabric adhesive. GREENGUARD Certified. Can be activated for immediate bonding.	Medium	Neutral/ Lavender	Spray	1–20 min	Non- flammable	-	Mist	0g/L

## Solvent and Water Based Adhesives Output Description:



Product	Available Format	Solids Weight Percent (Approx.)	Key Characteristics	Adhesive Strength	Color	Application Method	Bonding Range (Two Surfaces)	Flammability	Heat Resistance (SAFT)	Spray Pattern	VOC Content
Pressure Sensitive 72	Aerosol	15%	Permanently tacky and repositionable. Long open time. Variable width lace	Medium	Blue	Spray	1 min.– 8 hrs.	Flammable	170°F	Web	55%
Hi-Tack 76	Aerosol	13.5%	Fast tacking. One surface bonds. Variable width lace spray pattern.	High	Clear	Spray	1–60 min.	Flammable	230°F	Web	55%
	5 gal.	19%	Bonds polystyrene with no surface degradation. Fast	Medium	Clear	Spray	1–15 min	Flammable	190°F	Web	566g/L
Polystyrene 78	Aerosol	19%	grabbing and fast drying. Uniform spray pattern for fast and easy application.	Medium	Clear	Spray	1–15 min	Flammable	190°F	Web	62%
Polystyrene 78ET	Large, Int and Jumbo Cylinder	17%	Bonds polystyrene with no surface degradation. Extended tack time for long working time. Uniform spray pattern for fast and easy application.	Medium	Clear/ Green	Spray	1–60 min	Flammable	200°F	Web	622g/L
Hi-Temp	Large, Int and Jumbo Cylinder	27%	Bonds polystyrene with no surface degradation. High temperature	Medium	Blue	Spray	1–60 min	Flammable	230+°F	Web	611g/L
Polystyrene 78HT	Large, Int and Jumbo Cylinder	15%	resistance. Can be used for roofing membrane attachment.	Medium	Blue	Spray	1–60 min	Flammable	230+°F	Web	611g/L
Rubber and Vinyl 80	Aerosol	13%	High strength. High temperature resistance. Fast setting.	High	Yellow	Spray	3–30 min	Flammable	300+°F	Web	54%
847 High Performance Rubber & Gasket Adhesive	5 oz., 1 qt., 1 gal., 5 gal., 54 gal.	36%	Quick drying and flexible with fuel and oil resistance. Able to reactivate with heat and solvent. Curable with heat.	Medium	Brown	Brush/Flow	Up to 15 min	Flammable	_	Brush	0g/L
847H High Performance Rubber & Gasket Adhesive	5 gal., 52 gal.	51%	High viscosity. Able to reactivate with heat and solvent. Curable with heat.	Medium	Brown	Brush/Flow	Up to 10 min	Flammable	_	Brush	5g/L
1099 High Performance Plastic Adhesive	5 oz., 1 qt., 1 gal., 5 gal., 54 gal.	34%	Fast drying and heat curable. Resists weathering, water, oil, plasticizer migration and aliphatic fuels.	High	Light Tan	Brush/Flow	Up to 40 min	Flammable	_	Brush/ Flow	5g/L
1099L High Performance Plastic Adhesive	5 gal.	24%	Sprayable version of 1099. Fast drying and heat curable. Resists weathering, water, oil, plasticizer migration and aliphatic fuels.	High	Light Tan	Brush/Spray	Up to 20 min	Flammable	_	Brush/ Flow	443g/L
1300 High Performance Rubber & Gasket Adhesive	5 oz., 1 qt., 1 gal., 5 gal.	37%	High immediate strength. Fast-drying and heat resistant for rubber and metal. Meets MMM-A-121.	High	Yellow	Brush/Flow	Up to 12 min	Flammable	300°F	Brush/ Flow	667g/L
1300L High Performance Rubber & Gasket Adhesive	1 qt., 1 gal., 5 gal., 54 gal.	30%	Lower viscosity for spraying. Fast-drying and heat resistant for rubber and metal. Meets MMM-A-121.	High	Yellow	Brush/Spray	Up to 8 min	Flammable	300°F	Brush/ Spray	≤706g/L

# Solvent and Water Based Adhesives 😂 💿 292



Product SPECIALTY	Available Format	Solids Weight Percent (Approx.)	Key Characteristics	Adhesive Strength	Color	Application Method	Bonding Range (Two Surfaces)	Flammability	Heat Resistance (SAFT)	Spray Pattern	VOC Content
1357 High Performance Contact Adhesive	5 oz., 1 pt., 1 qt., 1 gal., 5 gal., 54 gal. (Light Yellow only 5 gal. and 55 gal.)	25%	Rapid build up to a very high strength bond for metal. Resists heat and continuous load stress. Meets MMM-A-121 requirements.	High	Gray- Green/ Light Yellow	Brush/Spray	10-30 min	Flammable	300°F	Web	≤582g/L
1357L High Performance Contact Adhesive	5 gal., 54 gal.	18%	Low viscosity. Resists heat and continuous load stress.	High	Gray- Green	Spray	10-30 min	Flammable	300°F	Web	515g/L
2262 Plastic Adhesive	1 qt., 5 gal.	27%	Clear and non-staining. Resists plasticizer migration for bonding many flexible vinyls. Fast tack.	High	Clear	Brush/Flow	2-20 min	Flammable	_	Brush/ Flow	177g/L
4475 Industrial Plastic Adhesive	5 oz, 1 qt., 5 gal.	43%	Clear plastic adhesive. Fast drying. Strong environmental resistance.	Medium	Clear	Brush/Flow	1–10 min	Flammable	_	Brush/ Flow	600g/L
4491 Industrial Adhesive	345 gal., 5 gal., 54 gal.	24%	Securely bonds vinyl with resistance to plasticizer migration. Versatile plastic adhesive. Excellent environmental resistance.	High	Light Tan	Brush/Roll/ Spray	Up to 20 min	Flammable	_	Web	190g/L
4693 High Performance Industrial Plastic Adhesive	5 oz, 1 qt., 1 gal., 5 gal., 54 gal., (High viscosity only 5 oz)	26%	Excellent plastic adhesive. Long tack range. Water and heat resistant.	Medium	Clear	Brush/Spray	10-60 min	Flammable	_	Web	597g/L
4799 Industrial Adhesive	5 oz, 1 qt., 1 gal., 5 gal.	32%	Water and heat resistant. Dries rapidly. EPDM bonder.	Medium	Black	Brush/Trowel	1–10 min.	Flammable	_	Brush/ Trowel	628g/L
Fast Tack 1000NF	1 gal., 5 gal., 52 gal., 255 tote	49%	One-part immediate handling strength. Low overspray and high coverage. Bonds a wide variety of substrates with high temperature resistance.	High	Neutral/ Purple	Spray	1–10 min	Non- flammable	300°F	Mist	0g/L
Fastbond™ Spray Activator 1	1 qt., 1L spray bottle, 5 gal., 30 gal.	_	GREENGUARD Certified. Low VOC and LEED® Compliant. UL MAGW2 component recognition.	_	Clear	Spray	_	Non- flammable	_	Mist	0g/L

## **3M™ Adhesive Sealants**







#### The economical choice for high strength, long lasting elastomeric bonding and sealing.

3M Adhesive Sealants are suitable for bonding and sealing a wide variety of substrates including: glass, wood, composites and plastics.






3M™ Polyurethane Sealant 740 moisture cures to a flexible seal/bond between exterior skins and metal framework and between wood flooring and metal framework. Tensile strength up to 580 psi is enough to replace mechanical fasteners in many situations.



3M" Polyurethane Glass Adhesive Sealant 590 is a fast curing one-component, high viscosity polyurethane sealant for bonding windshields and other substrates requiring high strength. This adhesive sealant is certified for 1 Hour Drive Away Time.



3M" Marine Adhesive Sealant 4000 UV Fast Cure cures completely in only 48 hours to a strong flexible bond/seal. Applications include: assembly above or below the waterline such as, hull and stern joints, hull to deck seams, marine hardware and more.



3M™ Polyurethane Sealant 560 is an all-purpose, single-component, moisture-curing, gap-filling polyurethane that creates permanently elastic seals and bonds in a wide variety of substrates.




Seam sealing ductwork with 3M™ Polyurethane Sealant 540 will prevent air and dust intrusion. Its flexibility assists with vibration damping.



3M<sup>™</sup> Adhesive Sealant 740 UV has superior UV resistance that is ideal for sealing seams and filling gaps for exterior applications.

## Durable, flexible bonding and sealing.

Find the right 3M™ Adhesive Sealant for your job.



359

## **3M™ Adhesive Sealants**







### Proven performance in demanding applications

Product	Description	Tensile Strength psi (MPa)	Stress at 100% Strain psi (MPa)	Elongation (%)	Skin Time (min.)	Hardness (Shore A)	Color (Dry)	Application Method	Typical Handling Strength	Cure Rate (mm/ 24 hours)	Service Temp. Range °F (°C)
	rurethane Adhesive Sealants e, Paintable once skin forms, Mu	ulti-purpos	e)								
525	All-around sealing; very flexible, excellent for concrete.	300 (2.1)	75 (0.5)	>800	90-150	25	Gray	Bead	N/A	3	-22 to 176 (-30 to 80)
540	Multi-purpose sealing.	350 (2.4	90 (0.6)	>700	60-90	40	White, Gray, Black	Bead	24 hrs.	3	-40 to 194 (-40 to 90)
550FC	Multi-purpose adhesive sealant.	375 (2.6	150 (1.0)	>500	50-90	45	White, Gray, Black	Bead	24 hrs.	4	-40 to 194 (-40 to 90)
550FC + AC63	Two component system for accelerated cure of 550.	275 (1.9)	125 (0.9)	>500	20	45	White, Gray, Black	Bead	20 min. full cure	20 min.	-40 to 194 (-40 to 90)
551	Properties similar to 550FC with longer open time.	450 (3.1)	200 (1.4)	>600	120-180	45	White	Bead	24 hrs.	4	-40 to 194 (-40 to 90)
560	High strength adhesive sealant.	380 (2.6)	200 (1.4)	>300	50-60	55	White, Gray, Black	Bead	24 hrs.	4	-40 to 194 (-40 to 90)
560 + AC63	Two component system for accelerated cure of 560.	350 (2.4)	140 (0.9)	>500	40	50	White, Gray, Black	Bead	3 hrs.	<24 hours full cure	-40 to 194 (-40 to 90)
590	Structural glass bonding; approved for windshield replacement.	1170 (8.3)	475 (3.4)	400	25-40	65	Black	Bead	3-hr. drive-away time (FMVSS 212)	3.5	-40 to 194 (-40 to 90)
	ne Modified Polymer (SMP) Adh t UV performance, Can be paint			yanate-free)							
730UV	Clear, cosmetic sealing with excellent UV resistance.	300 (2.1)	120 (0.8)	>200	25-30	30	Clear	Bead	24 hrs.	3.5	-40 to 194 (-40 to 90)
740UV	Multi-purpose sealing; excellent UV resistance, low VOC.	180 (1.2)	168 (1.2)	130	40-60	30	White, Gray, Black	Bead	24 hrs.	3.5	-40 to 194 (-40 to 90)
760UV	Multi-purpose bonding; excellent UV resistance, low VOC.	440 (3.0)	280 (1.9)	180	10-30	55	White, Gray, Black	Bead	24 hrs.	3.5	-40 to 212 (-40 to 100)

Product	Description	Tensile Strength psi (MPa)	Stress at 100% Strain psi (MPa)	Elongation (%)	Skin Time (min)	Hardness (Shore A)	Color (Dry)	Application Method	Typical Handling Strength	Cure Rate (mm/ 24 hrs.)	Service Temp. Range °F (°C)
3M™ Wea	therban <sup>™</sup> Sealants										
5354	High tack butyl tape for sealing; easy to compress, resists cold flow.	N/A	N/A	N/A	N/A	60	Black	Tape	N/A	N/A	N/A
PF5422	Thread reinforced butyl tape. Respositionable without clean up. Weather resistant.	125 (0.9)	25 (0.2)	400	30	N/A	Black	Tape	N/A	N/A	N/A
3M™ Spec	cialty Sealant and Adhesive Products										
800	Solvent-based rubber dries to flexible seal. Solvent resistant.	100 (0.7)	70 (0.5)	1200	10	N/A	Red-Brown	Bead	24 hrs.	0.8	-65 to 200 (-54 to 93)
606	Weatherban™ Acrylic Sealant; Multipurpose indoor and outdoor sealing.	260 (1.8)	153 (1.0)	146	30	60	White	Bead	N/A	1.5	-28 to 180 (-33 to 82)
2084	Scotch-Seal™ solvent-based rubber industrial sealant. Metal sealant; aluminum color. Oil and fuel resistant.	700 (4.8)	475 (3.3)	800	5	30	Aluminum	Bead	24 hrs.	0.7	-65 to 200 (-54 to 93)
5010	Moisture-curing polyurethane. Excellent wood bonder.	275 (19)	N/A	N/A	3-5	N/A	Cream	Bead	24 hrs.	N/A	-22 to 212 (-30 to 100)

# 3M™ Adhesive Sealants © © © 292



#### Marine sealants

Product	Description	Tensile Strength psi (MPa)	Stress at 100% Strain psi (MPa)	Elongation (%)	Skin Time (min.)	Hardness (Shore A)	Color (Dry)	Application Method	Typical Handling Strength	Cure Rate (mm/ 24 hrs.)	Service Temp. Range °F (°C)
	urethane Adhesive Sealants e, Paintable once skin forms, Mu	ılti-purpos	e)								
5200	Polyurethane. Industry standard for over 50 years. Permanent bonding of gelcoat, fiberglass. Long working time. Bonds/seals above and below waterline.	650 (4.5)	450 (3.1)	>230	>48 hrs.	70	White, Black, Tan, Mahogany	Bead	>48 hrs.	<1	-40 to 190 (-40 to 88)
5200 FC	Polyurethane. Fast cure version of 5200. Up to 1 hour open time. Permanent bonding. Bonds/seals above and below waterline.	600 (4.1)	200 (1.4)	>350	60-120	60	White	Bead	48 hrs.	3	-40 to 190 (-40 to 88)
4200 FC	Polyurethane. Medium strength bonding and water tight sealing; can be removed after prolonged use. Bonds/ seals above and below waterline.	220 (1.5)	180 (1.2)	>275	50-90	40	White, Black	Bead	24 hrs.	3	-40 to 194 (-40 to 90)
	ne Modified Polymer (SMP) Adhe t UV performance, Can be paint			vanate-free)							
4000 UV	SMP. High perf ormance, medium strength bonding and water tight sealing; excellent UV resistance. Bonds/seals above and below waterline.	450 (3.1)	210 (1.4)	>300	15–30	40	White, Black	Bead	24 hrs.	3.5	-40 to 194 (-40 to 90)
	one Adhesive Sealants t UV performance, Clear/White	Marine Sili	icone)								
Marine Silicone	High quality, marine grade, non-yellowing silicone. Mildew resistant, non-sagging. Removable. Bonds/seals above waterline.	220 (1.5)	65 (0.5)	>350	5–10	20	White, Clear	Bead	N/A	3	-40 to 190 (-40 to 88)

### Primers and adhesion promoters

Product	Description	Color	Viscosity	VOC g/L	
P591	All purpose primer	Black	Low	613	Polyurethane
P592	Metal primer	Clear	Low	790	Silane
AP596	Adhesion promoter cleaner	Clear	Low	798	Silane

### **Applicators**

Туре	Manual	Pneumatic	Manual	Manual	Pneumatic	Pneumatic
310mL Cartridges	310		400M	600M		34A
350mL Sausage Packs		400 A-2K	400M	600M	600A	34A
400mL Sausage Packs			400M	600M	600A	34A
600mL Sausage Packs				600M	600A	

## **3M™ Adhesive Sealants**



# Marine sealants comparison guide



Features	4000 UV	4200 FC	5200	5200 FC	Marine Grade Silicone	590
Sealing	Yes	Yes	Yes	Yes	Yes	Yes
Bonding	Excellent	Good	Excellent*	Excellent	Poor	Good
Strength	Medium	Medium	High	High	Low	N/A
Chemical base	SMP	Polyurethane	Polyurethane	Polyurethane	Silicone	Polyurethane
Curing time	24 hrs.	24 hrs.	5-7 days	24 hrs.	24 hrs.	24 hrs.
Tack free time (70°F/21°C @ 50% RH)	30 min.	2 hrs.	24-48 hrs.	1 hr.	10 min.	30 min.
Cure rate (mm per 24 hours)	>3.5	>3	<1	3	3	3

Good Best Better						
Applications	4000 UV	4200 FC	5200	5200 FC	Marine Grade Silicone	590
Deck to hull bonding	Better	Better	Best	Best		
General purpose sealing and bonding	Best	Better	Best	Best	Above Waterline Only	
Bedding	Best	Best	Better	Better	Good	
Keel sealing	Good	Good	Best*	Best		
General interior sealing	Better	Better			Best	
Sealing wood to deck or superstructure		Better	Best	Best		
Sanitary sealing					Best	
Plastic acrylic window sealing	Best					Best
Wood deck caulking Not recommended for teak deck caulking.	Better	Better	Best	Best	Good	
Bonding anti-slip plates in engine rooms	Good		Best	Best		
Sealing exterior strong UV radiation zones	Best**	Good	Good		Above Waterline Only	
Bonding decorative panels (vertical); work surfaces (horizontal); deck hardware (deck/fittings); wood to wood	Better	Better	Best	Best		
Bonding thru hull; hatches and port lights; fiberglass to fiberglass	Best	Better	Best	Best		

<sup>\*</sup>Bonding to bare aluminum is not recommended for applications with continuous water immersion.

<sup>\*\*4000</sup>UV Black is the only recommended product for this application.

## **3M™ Concrete Repair Products**

#### Fast, Convenient Crack and Spall Repair, Expansion Joints, Custom Threading and Anchoring, and More

3M™ Concrete Repair Products offer a complete line of conveniently packaged and dispensed adhesives/ sealants for every job from cracks and joints to spalls and more.

Repairs are long lasting with strong, flexible bonds that resist weathering, expansion and contraction.

Fast setting allows you and your customers to drive on repaired surfaces in as few as five minutes. You can choose non-sag or self-leveling formulations for repairs on both vertical and horizontal surfaces. Non-sag formulation facilitates step and ledge repair.



3M" Concrete Repair 600 self-leveling flows smoothly into cleaned cracks and gaps and hardens in as little as 5 minutes.



50mL and 12 fl oz. duo-pak cartridges, 5-gallon pails and 55 gallon drums are available to meet your production volume requirements. Nozzle automatically and precisely meters, mixes, and dispenses two-part urethane formulation. Apply material precisely where needed to conserve material.



Make fast work of lengthy expansion or control joints and other larger jobs with the heavy-duty manual applicator and 12 fl oz. duo-pak cartridges.

3M concrete repair formulations harden to any depth without cracking for custom threading and anchoring.

		Key Features	Mix Ratio (Vol.) B:A	Approx. Viscosity at 75°F (24°C) (cP)	Approx. Mixed Work Life at 75°F (24°C)	Approx. Time to Handling Strength at 75°F (24°C)	Floating Roller Peel PLI (N/cm) at 75°F (24°C)	Overlap Shear: psi (MPa)					
	Product (Color)							-40°F (-40°C)	75°F (24°C)	180°F (82°C)	Size	UPC	Stock#
*	<b>DP600</b> <b>600</b> (Gray)	Concrete repair, Self-leveling	1:1	6,000	1 min	4 min	20 (36)	3,200 (22)	2,300 (16)	700 (5)	50mL 400mL 8.4 fl oz. 5 gal. pail A 5 gal. pail B	00-021200-56602-8 00-051111-98303-4 00-021200-96596-8 00-021200-96575-3 00-021200-96574-6	62-2649-3530-5 62-2649-1233-8 62-2749-8535-7
	DP600NS 600NS (Gray)	Concrete repair, Non-sag	1:1	Paste	1 min	4 min	8 (14)	2,700 (19)	2,300 (16)	700 (5)	50mL 400mL	00-021200-56606-6 00-051111-98312-6	
	<b>DP5106</b> (Gray)	Helps relieve stress in large segments of concrete floors	1:1	34,000	4 min	40 min	N/A	N/A	1,100 (8)	N/A	400mL 5 gal. pail A 5 gal. pail B	00-051111-98297-6 00-021200-96584-5 00-021200-96583-8	62-3527-9535-4

#### **Accessories**

Product	Size	Description
Manual Dispenser 98073	400mL	Heavy-duty applicator.
Pneumatic Dispenser 87979	400mL	Applicator for high volume jobs.
Mix Tip - Higher Throughput 97331	400mL	General use tip.
Mix Tip - Longer Reach 87982	400mL	Alternative nozzle with longer reach.
Mixing Nozzle (threaded) 53382	8.4 fl oz.	Mixes Concrete Repair 600.

After Key Products, consider these.

## **3M Industrial Adhesives and Tapes**

Notes:						

# **Bonding Tapes**

# Convenience meets extreme bonding power.

# **Powerful Bonding Solutions**

Help your customers successfully bond a variety of materials with strength and speed for permanent, structural and repositionable applications. Our double-sided bonding tapes provide shear strength, conformability, surface adhesion and temperature resistance.



### Dream. Design. Deliver.

Since 1980, 3M™ VHB™ Tape has offered unlimited design and application possibilities. By working with 3M's engineering experts, product designers know they can count on this reliable solution. Lab-tested and proven in the real world, 3M™ VHB™ Tape eliminates rivets, bolts, screws and welds.

- Durability for long-term performance indoors and out
- Productivity through application ease and versatility
- Instant bonding
- Smooth, invisible appearance
- Viscoelastic properties absorb shock and distribute stress evenly over the bond line
- Bond dissimilar materials with confidence






3M™ VHB™ Tape bonds panels to a bus on contact. The tape seals against water, moisture and more. Bonding power eliminates mechanical fasteners for a smooth, clean surface. Viscoelastic properties help absorb shock and vibration for bond reliability.



To join a variety of materials for high impact visual combinations throughout a refrigerator, 3M™ VHB™ Tape bonds painted and unpainted metal, HSE and LSE plastics, ceramics and more.



For assembly efficiency, die-cut pieces of 3M™ VHB™ Tape bond components on a laptop.



3M<sup>™</sup> VHB<sup>™</sup> Tapes bond panel stiffeners on contact to pre-painted metal cabinetry. Unlike welding, applying the tape does not damage the finish.



Mirrored ceiling panels are held in place with 3M" VHB" Tapes rather than screws. This helps maintain a clean, smooth appearance without distorting the reflective surfaces.



For a heat resistant bond, 3M™ VHB™ Tape GPH Series bonds and seals stainless steel trim to the glass oven door with strength enough to replace mechanical fasteners. Door surface is smooth and attractive.



With high holding power and long-term reliability, 3M<sup>™</sup> VHB<sup>™</sup> Tape bonds dimensional letters to a painted wall for indoor or outdoor signage.

# **3M<sup>™</sup> VHB<sup>™</sup> Tapes — Typical Applications**

3M™ VHB™ Tape is a proven high-strength alternative to screws, rivets, welds and other forms of traditional fastening methods. While a screw or a rivet can join two substrates at a single point, 3M™ VHB™ Tape permanently adheres one substrate to another and spreads the stress load across the entire length of the joint. The most common applications for 3M™ VHB™ Tape are:

- Reduce weight and solve dynamic force challenges
- Create a clean appearance






- Exceptional vibration and corrosion resistance
- Deliver unique designs





- Securely seal dissimilar materials
- Enhance productivity
- Create innovative designs





- Unlimited opportunities to enhance products
- Flexibility of production and design





# **3M<sup>™</sup> VHB<sup>™</sup> Tapes**

	Tape Thickness				Temp. Re	esistance		Relative	Adhesion	
Product	w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas
4941 Tape		.,,,,		.,,,,		7100.00	1.00.010.100			, pp. oanon raodo
4926	15 (0.4)	Α								
4936	25 (0.64)	Α	-							
4936F	25 (0.64)	F	Gray, closed-cell acrylic							Bond and seal polycarbonate lens
4941	45 (1.1)	А	foam carrier. Conformable, Good	Multi-	300°F	200°F	High	High	Med	over LCD. Bond and seal plastic
4941F	45 (1.1)	D	adhesion to many	purpose	(149°C)	(93°C)				windows to pre-painted control panels/switch gear. Mount vinyl
4956	62 (1.6)	А	painted metals. Plasticizer resistant. UL	Acrylic						wiring ducts and conduit
4956F	62 (1.6)	F	746C.							channels. Seam vinyl banners.
4991	90 (2.3)	F			250°F (121°C)	200°F (93°C)	High	High	Med	
4991B	90 (2.3)	F	Black version of 4991.	Multi- purpose Acrylic	250°F (121°C)	200°F (93°C)	High	High	Med	Bond and seal polycarbonate lens over LCD. Bond and seal plastic
4919F	25 (0.64)	F	Black version of 4936F.	Multi-						windows to pre-painted control panels/switch gear. Mount vinyl
4947F	45 (1.1)	F	Black version of 4941F.	purpose	300°F (149°C)	200°F (93°C)	High	High	Med	wiring ducts and conduit
4979F	62 (1.6)	F	Black version of 4956F.	Acrylic	(149 C)	(93 C)				channels. Seam vinyl banners.
5952 Tape	Family	,							_	
5906	6 (0.15)	G	Black, closed-cell							
5907	8 (0.2)	G	acrylic foam carrier. Good adhesion to many	Modified	300°F	250°F				Bond and seal polycarbonate lens over LCD. Lens and touch panel
5908	10 (0.25)	G	painted surfaces,	Acrylic	(149°C)	(121°C)	High	High	Med	bonding. Logo attachment. P.O.P.
5909	12 (0.3)	G	including powder coated paint.							and display construction.
5915	16 (0.4)	F								
5915P	16 (0.4)	Е								
5925	25 (0.6)	F								
5925P	25 (0.6)	Е	Black, closed-cell acrylic foam carrier.							Bonds to a variety of plastics
5930	32 (0.8)	F	Good adhesion to many	Modified	300°F	250°F	1.151.	1.15 1-	NAI	and paint systems. Bond
5930P	32 (0.8)	Е	painted surfaces, including powder coated	Acrylic	(149°C)	(121°C)	High	High	Med	architectural signs to frames. Attach trim and extrusions.
5952	45 (1.1)	F	paint.							Hat channels and stiffeners.
5952P	45 (1.1)	Е	UL 746C.							
5962	62 (1.6)	F								
5962P	62 (1.6)	Е								
5958FR	40 (1)	F	Meets FAR 25.853 (a) 12 sec vertical burn Appendix F, Part 1 (a) (ii)	Modified Acrylic	300°F (149°C)	200°F (93°C)	High	High	Med	Overhead stow bins, signage, kick plates, galley modules, plastic and metal decorative trim, ceiling tile stiffeners, mirror mounting, air duct spuds, floor and wall panel attachment and clip attachment.
RP+ Tape F	amily									
RP+040GP	16 (0.4)	А								
RP+040GF	16 (0.4)	F								
RP+060GP	25 (0.6)	А								
RP+060GF	25 (0.6)	F	Gray, closed-cell acrylic foam carrier.	Multi-	45005	05005				D. H. B. SW
RP+080GP	32 (0.8)	А	Conformable. Good	purpose	450°F (230°C)	250°F (121°C)	High	High	Med	Panel bonding, stiffener attachment and trim attachment.
RP+080GF	32 (0.8)	F	adhesion to many painted metals.	Acrylic		( = 1 0 )				
RP+110GP	45 (1.1)	А								
RP+110GF	45 (1.1)	F								
RP+160GP	62 (1.6)	А								

### Liner Types:

A - 3 mil 54# Densified Kraft Paper

B - 5 mil Clear Polyethylene Film

C – 2 mil Polyester Film

D – 5 mil Red Polyethylene Film E - 4 mil 58# Polycoated Kraft Paper

F – 5 mil Red Printed Polyethylene Film

G - 3 mil Clear Polyethylene Film

H - 5 mil Green PE Film

### Relative Adhesion:

HSE - High Surface Energy LSE - Low Surface Energy

Multi-purpose Acrylic: Bonds to a wide range of materials including metals, glass, and high and medium surface energy plastics and paints. Resists migration of plasticizers in vinyl substrates.

Modified Acrylic: Bonds to medium low surface energy paints and plastics, including many powder coated paints in addition to the substrates listed with the multi-purpose acrylic adhesive (except plasticized vinyl). General Purpose Acrylic: Bonds to most higher surface energy substrates including metal, glass and high surface energy plastics.

Low Temperature Acrylic: Bonds down to 32°F (0°C) compared to 50°F (10°C) for most acrylic adhesives. Bonds most high surface energy substrates including metal, glass and high surface energy plastics. Low Surface Energy: High performance synthetic adhesive bonds to many lower surface energy substrates, including many plastics and powder coated paints, plus smooth general purpose substrates.

# **3M<sup>™</sup> VHB<sup>™</sup> Tapes**

	Таре				Temp. Re	esistance		Relative	Adhesion		
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas	
RP+ Tape Fami				.,,,,		TIOONS				7 PP TO A T	
RP+160GF	62 (1.6)	F									
RP+230GP	90 (2.3)	А	Gray, closed-cell acrylic foam carrier. Conformable. Good	Multi- purpose	450°F (230°C)	250°F (121°C)	High	High	Med	Panel bonding, stiffener attachment and trim	
RP+040GF	90 (2.3)	F	adhesion to many painted metals.	Acrylic	(200 0)	(121 0)				attachment.	
LSE Tape Fami	ily										
LSE-060WF	25 (0.6)	F	Specifically for LSE substrates							Made to live outdoors. Resists hot, cold and cycling temperature,	
LSE-110WF	45 (1.10)	F	such as polypropylene (PP), thermoplastic elastomers (TPE) and thermoplastic olefins (TPO).	LSE Acrylic	300°F (150°C)	200°F (93°C)	High	High	High	UV light, moisture and solvents. Seals against environmental conditions. Low-temperature bonding with high initial	
LSE-160WF	62 (1.6)	F	oletins (TPO).							tack at low temperatures on frost-free surfaces down to 0°C.	
GPH Tape Fam	nily			1	I	I	1				
GPH-060GF	25 (0.6)	F	Superior high-temperature	115.1						High temperature resistance allows tape	
GPH-110GF	45 (1.10)	F	performance for powder coat or liquid paint processes and multi material bonding.	High Temp Acrylic	450°F (230°C)	300°F (150°C	High	High	Medium	to reduce the number of "touches," leading to a more streamlined	
GPH-160GF	62 (1.6)	F	material boliding.							manufacturing process.	
4950 Tape Far	nily	1		1	T	T	1				
4914	10 (0.25)	А									
4920	15 (0.4)	А									
4929	25 (0.6)	С		General						Attach stiffeners in air conditioners, office	
4930	45 (1.1)	А	Closed-cell acrylic foam carrier. UL 746C.	Purpose Acrylic	300°F (149°C)	200°F (93°C)	High	High	Low	furniture and telecommunications	
4930F	45 (1.1)	D		Acrylic						equipment.	
4949	45 (1.1)	С									
4950	45 (1.1)	А									
4955	80 (2)	С								Attach stiffeners in	
4959	120 (3)	С	Closed-cell acrylic foam carrier. UL 746C.	General Purpose	400°F (204°C)	300°F (149°C)	High	High	Low	air conditioners, office furniture and	
4959F	120 (3)	D	,	Acrylic	(2010)	(5 0)				telecommunications equipment.	
4910 Tape Far	nily										
4905	20 (0.5)	F	Clear, acrylic construction for	General	300°F	200°F				Mount backlit translucent signs.	
4910	40 (1)	F	joining transparent material.	Purpose Acrylic	(149°C)	(93°C)	High	High	Low	Edge-bond resin filled glass.	
4611 Tape Far	nily	1	l		ı	ı				l	
4646	25 (0.6)	D									
4611	45 (1.1)	D	Dark gray, closed-cell acrylic foam carrier. High temperature resistance. UL 746C.	m General Purpose Acrylic	e (222°C)			High	Low	Pre-powder coat paint applications. Hat channels and stiffeners.	
4655	62 (1.6)	D		, -						channels and stiffeners.	

### Liner Types:

A - 3 mil 54# Densified Kraft Paper

B - 5 mil Clear Polyethylene Film

C – 2 mil Polyester Film

D – 5 mil Red Polyethylene Film

E – 4 mil 58# Polycoated Kraft Paper F – 5 mil Red Printed Polyethylene Film

G - 3 mil Clear Polyethylene Film

H - 5 mil Green PE Film

### Relative Adhesion:

HSE - High Surface Energy LSE - Low Surface Energy

Multi-purpose Acrylic: Bonds to a wide range of materials including metals, glass, and high and medium surface energy plastics and paints. Resists migration of plasticizers in vinyl substrates.

Modified Acrylic: Bonds to medium low surface energy paints and plastics, including many powder coated paints in addition to the substrates listed with the multi-purpose acrylic adhesive (except plasticized vinyl). General Purpose Acrylic: Bonds to most higher surface energy substrates including metal, glass and high surface energy plastics.

Low Temperature Acrylic: Bonds down to 32°F (0°C) compared to 50°F (10°C) for most acrylic adhesives. Bonds most high surface energy substrates including metal, glass and high surface energy plastics. Low Surface Energy: High performance synthetic adhesive bonds to many lower surface energy substrates, including many plastics and powder coated paints, plus smooth general purpose substrates.

# 3M™ VHB™ Thin Foam Tapes

With a uniquely thin form,  $3M^{\text{\tiny M}} \text{ VHB}^{\text{\tiny M}}$  Thin Foam Tapes go where thicker foam tapes simply can't, while still providing the same great benefits of regular  $3M^{\text{\tiny M}} \text{ VHB}^{\text{\tiny M}}$  Tapes. Common applications include LCD, lens and touch panel bonding, logo attachment and point of purchase displays.





	Tape Thickness				Temp. Resi	stance		Relative	Adhesion		
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas	
5900 Tape F	Family										
5906	6 (0.15)	G	Black, closed-cell acrylic							LCD lane and touch	
5907	8 (0.2)	G	foam carrier. Good adhesion	Modified	300°F (149°C)	250°F	I II ada	115 1-	NAl	LCD, lens and touch panel bonding, logo	
5908	10 (0.25)	G	to many painted surfaces, including powder coated	Acrylic		(121°C)	High	High	Med	attachment, P.O.P. and	
5909	12 (0.3)	G	paint.							display construction.	
4914 Tape F	Family										
4914-015	6 (0.15)	А	White, closed-cell acrylic								
4914-020	8 (0.2)	А	foam carrier.	General	300°F	200°F				LCD, lens and touch panel bonding, logo	
4914	10 (0.25)	А	White, closed-cell acrylic foam carrier. All-purpose adhesive. UL 746C.	Purpose	(149°C)	(93°C)	High	High	Low	attachment, P.O.P. and display construction.	

See key on page 74.

# 3M™ VHB™ Tape for Commercial Vehicles and Trailers

# **Built Tough with Smooth Sides to Look Good for the Long Haul**

For durability and smooth sides on trailers, trucks, buses, and other commercial vehicles, 3M<sup>™</sup> VHB<sup>™</sup> Tapes are proven to go the distance.

- 3M™ VHB™ Tape is up to 41% quieter than mechanical fasteners with up to 30% less vibration at highway speeds
- Surfaces of truck panels are aesthetically smooth and graphics apply easily
- Permanently bonds and seals

3M<sup>™</sup> VHB<sup>™</sup> Tapes for Commercial Vehicles and Trailers are only available through authorized distributors and a warranty may be available on pre-approved applications.



Mechanically fastened at 36,000 miles — leaks at less than 75 psi.



Smooth sides with 3M™ VHB™ Tape at 100,000 miles — no leaks at 3200 psi.

	Tape				Temp. Re	esistance		
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	Application Ideas
CV45F	45 (1.1)	D	Gray, closed-cell acrylic foam carrier.	Multi-	300°F	200°F		Bond overlap seams on vehicle side panels.
CV62F	62 (1.6)	F	Conformable. Good adhesion to many painted metals.	purpose Acrylic	(149°C)	(93°C)	High	Bond vehicle side panels to posts.

See key on page 74.

# **3M™ VHB™ Structural Glazing Tapes**

### Application Ease and Immediate Handling Strength for Increased Productivity

3M™ VHB™ Structural Glazing Tapes have been proven in thousands of buildings worldwide since 1990 as an alternative to structural silicone and spacer tapes/gaskets.

Immediate handling strength results in faster throughput and delivery. No mixing or curing simplifies manufacturing.

Proven technology with a 30+ year history in construction, an application warranty\* is available for qualifying applications in select countries.



	Tape Thickness				Temp. Re	esistance	Relative	Adhesion	
Product	w/o Liner mils (mm)	Liner	Description	Adhesive Type	Min Hr+	Days Weeks	HSE	LSE	Solvent Resistance
G23F	90 (2.3)	_	Gray, closed-cell acrylic foam carrier. Conformable.	Multi-purpose	300°F	200°F	High	Med	High
B23F	90 (2.3)		Black, closed-cell acrylic foam carrier. Conformable.	Acrylic	(149°C)	(93°C)	nign	ivied	nign

<sup>\*3</sup>M\* VHB\* Structural Glazing Tapes are only available for structural glazing applications approved by 3M Technical Service through select distributors. See key on page 74.

# 3M™ VHB™ Architectural Panel Tapes


# Proven for More Than 30 Years in Applications from Denver to Singapore


For quick permanent assembly of cladding and curtain wall panels, 3M™ VHB™ Tapes provide an ideal combination of durability, performance and application ease.

Bond to a wide range of architectural panel substrates including dissimilar materials. With design flexibility, create visibly stunning facades.

Application warranty available for qualifying applications in select countries.







	Таре				Temp. Resistance			Relative Adhesion	
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE
G11F	45 (1.1)		Gray, closed-cell acrylic foam carrier. Conformable.						
B11F	45 (1.1)		Black, closed-cell acrylic foam carrier. Conformable.		300°F	200°F	NAl	1.15	NAI
G16F	62 (1.6)	Red,	Gray, closed-cell acrylic foam carrier. Conformable.	Multi-	(149°C)	(93°C)	Med	High	Med
B16F	62 (1.6)	Printed Film	Black, closed-cell acrylic foam carrier. Conformable.	purpose Acrylic					
G90F	90 (2.3)		Gray, closed-cell acrylic foam carrier. Conformable.		250°F	200°F	Med	Himb	Med
B90F	90 (2.3)		Black, closed-cell acrylic foam carrier. Conformable.		(121°C)	(93°C)	ivied	High	ivied

See key on page 74.

# 






### Attach Wood, Vinyl, Composite or Painted Metal Muntin Bars to Windows

These high strength tapes conform to glass with good wet-out and resistance to UV light, thermal expansion and contraction, solvents and cleaners. Tapes below are available only for approved window and door customers. Pre-approved applications may be eligible for a 10-year warranty.







	Tape Thickness				Temp. Resistance			Relative Adhesion	
Product	w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE
G45P	45 (1.1)	А	Gray, closed-cell acrylic foam carrier. Conformable.						
G45F	45 (1.1)	D	Gray, closed-cell acrylic foam carrier. Conformable.	Multi-purpose Adhesive	300°F (149°C)	200°F (93°C)	High	High	Med
B45F	45 (1.1)	F	Black, closed-cell acrylic foam carrier. Conformable.	7.0	(1.10-0)	(00 0)			

See key on page 74

# 3M™ VHB™ Tape for Sign and Display

### **Reliable and Immediate Bonding**

For indoor and outdoor signage, 3M™ VHB™ Tapes hold immediately without the work of screws and the mess and curing time of liquid adhesives.

- Bond metals, plastics, glass, foam board and more
- Invisible fastening for smooth, attractive surfaces





3M™ VHB™ Tape provides durable bonding in outdoor applications.



Clear 3M™ VHB™ Tape permanently bonds aluminum letters to glass and appears almost invisible from behind the pane.

	Tape				Temp. Re	esistance		Relative	Adhesion		
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas	
5952	45 (1.1)	F	Black or white, closed-cell acrylic foam		00005	05005				Bond and seal	
5962	62 (1.6)	F	carrier. Good adhesion to many painted surfaces, including powder coated paint. UL 746C.	Modified Acrylic	300°F (149°C)	250°F (121°C)	High	High	Med	metal and plastic through a sign.	
LSE-060WF	25 (0.6)	F	Specifically for LSE substrates such as							Outdoor use.	
LSE-110WF	45 (1.10)	F	polypropylene (PP), thermoplastic elastomers	LSE Acrylic	300°F (150°C)	200°F (93°C)	High	High	High	Seals against environmental	
LSE-160WF	62 (1.6)	F	(TPE) and thermoplastic olefins (TPO).	710.7.10	(100 0)	(00 0)				conditions.	
4910	40 (1)	F	Clear, acrylic construction for joining transparent material.	General Purpose	300°F (149°C)	200°F (93°C)	High	High	Low	Bond unpainted metal.	
4941	45 (1.1)	А	Gray, closed-cell acrylic foam carrier.	Multi-purpose	300°F	200°F	11: 1	115		Bond flexible	
4956	62 (1.6)	А	Good adhesion to many painted metals. Plasticizer resistant. UL 746C.	Acrylic	(149°C) (93°C)		High	High	Med	vinyl banners.	


# 





### 3M™ VHB™ Tape is the Ultimate Solution for Appliance **Design Applications**

From the kitchen to the laundry room, trust in 3M™ VHB™ Tape to expand design freedom in everything from how the side panels hold together to the way a brand's logo is displayed. Thanks to the viscoelastic properties of 3M™ VHB™ Tape, OEM consumer and commercial design engineers and manufacturers have access to a new realm of opportunities for beautiful, more efficient household appliance designs.



	Tape				Temp. Re	Temp. Resistance			Adhesion	
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas
4941	45 (1.1)	А	Gray, closed-cell acrylic foam carrier.	Multi-purpose Acrylic	300°F (149°C)	200°F (93°C)	High	High	Med	Logo attachment,
5952	45 (1.1)	F	Black, closed-cell acrylic foam carrier.	Modified Acrylic	300°F (149°C)	250°F (121°C)	High	High	Med	overlay attach- ment and control panel assembly.
RP+110GP	45 (1.1)	А	Gray, closed-cell acrylic foam carrier.	Multi-purpose Acrylic	450°F (230°C)	250°F (121°C)	High	High	Med	paner assembly.

See key on page 74.

# **3M™ VHB™ Tape for Electronics**

Electronic designs are becoming lighter, thinner and smaller every day. Bulky mechanical systems can be replaced with the incredible, strong, long-lasting viscoelastic bond of 3M™ VHB™ Tape. Expand design freedom and simplify manufacturing processes while meeting the challenges of a dynamic market and look no further than 3M™ VHB™ Tape.



	Tape			Temp. Resistance				Relative Adhesion		
Product	Thickness w/o Liner mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas
5908	10 (0.25)	G								Bond and seal polycarbonate
5915	16 (0.4)	F	Black, closed-cell	Modified	300°F	250°F	High	High	Med	lens over LCD. Bond and seal
5925	25 (0.6)	F	acrylic foam carrier.	Acrylic	(149°C)	(121°C)	) High	iigii Higii	riigii ivieu	plastic windows to pre-painted control panels/switch gear.
5952	45 (1.1)	F								Mount vinyl wiring ducts and
RP+040GP	16 (0.4)	А	Gray, closed-cell	Multi- purpose	450°F	250°F	High	High	Med	conduit channels. Electronic component and assembly
RP+110GP	45 (1.1)	А	acrylic foam carrier.	Acrylic	(230°C)	(121°C)	riigii	Ingli	ivied	attachment.

See key on page 74.

## 3M™ Primers

Product	Solvent	Active Ingredients	VOCs	Color	Flashpoint	Coverage	Application Ideas
AP111	Isopropyl Alcohol (IPA)	Less than 5% by weight	5.91 lb./gal. (708g/L)	Clear	52°F (11°C)	19m²/L (800 ft²/gal.) based on .002 in. wet coating thickness depending on method of application	Promote better adhesion for bare metals and painted surfaces.
AP115	Isopropyl Alcohol and Water	Less than 1% by weight	6.08 lb./gal. (728g/L)	Clear	53°F (12°C)	20–25 ft² per 4 fl oz. bottle (1.8–2.3m² per 118mL bottle)	Promote better adhesion for glass.
Primer 94	See SDS	See SDS	Approx 6.3 lb./gal. (755g/L) less H20 and exempt solvents	Clear Light Yellow/Clear Dark Orange	-4°F (-20°C)	600 ft²/gal. (211m²/L)	Promote better adhesion for a variety of plastic surfaces such as polyethylene, polypropylene, ABS and PET/PBT blends.
Primer UPUV	See SDS	Approx. 5% by weight	3.58 lbs/gal. (429g/L)	Clear	-5°F (-21°C)	600 ft²/gal. (211m²/L)	Improved environmental, health, and safety profile compared to 3M™ Tape Primer 94.

# **3M™ Extreme Sealing Tapes**




292

### From Trailer, Bus and Rail Car Roof Seams to Metal Enclosures, a Sure Winner Over Traditional Sealants

- Sticks on contact to many metals and plastics without dripping, oozing or clean-up
- Increases productivity throughput with no drying time; immediately paintable\*
- Conforms over contours, edges, rivets and screw heads for a water tight seal
- Looks neat and precise for improved aesthetics
- Outstanding resistance to many common industrial solvents
- Excellent resistance to abrasion and high pressure washing

<sup>\*</sup>Accepts many paints. Test paint on tape to check for compatibility.





### **Suggested Uses**

- RV trailer and roofs
- Metal enclosures
- Awnings
- Trailer home roofs
- Metal storage buildings
- Vent stacks/windows
- Gutters and downspouts
- Skylights
- Outdoor signs/displays
- Leak patching and repairs



Scan the code to download the 3M™ Extreme Sealing Tape Exterior Durability Report.

			Tape	Tensile Strength		90° Peel A						
Product	Color	Backing/ Adhesive	Thickness mils (mm)	lb/in (N/cm)	Aluminum	Stainless Steel	Glass	Truck Paint	PVC	ABS	Widths in. (mm)	Length yd. (m)
4411G	Grey		40 (1)	13 (23)	15 (26)	16 (28)	15 (26)	15 (26)	15 (26)	16 (28)		36 (32.9)
4411N	Neutral/Translucent	lonomer	40 (1)	13 (23)	15 (26)	15 (26)	15 (26)	14 (25)	16 (28)	16 (28)	0.75, 1, 2,	36 (32.9)
4411B	Black	Film/Pressure Sensitive	40 (1)	13 (23)	19 (33)	17 (30)	19 (33)	17 (30)	19 (33)	18 (32)	2.5, 3, 4 (19, 25, 50,	36 (32.9)
4412G	Grey	Acrylic	80 (2)	13 (23)	18 (32)	18 (32)	16 (28)	17 (30)	18 (32)	18 (32)	65, 75, 100)	18 (16.5)
4412N	Neutral/Translucent		80 (2)	13 (23)	18 (32)	18 (32)	19 (33)	19 (33)	19 (33)	19 (33)		18 (16.5)


<sup>†</sup>Adhesion promoters were used on peel Adhesion test substrates.

# **3M™ Double Coated Foam Tapes**

# Flexible Foam Carriers Fill Gaps and Help Bond Irregular Surfaces

In bonding rough or irregular surfaces, 3M™ Double Coated Foam Tapes fill gaps and distribute stress uniformly over the bonded area.

- Bond line that seals, cushions and damps vibration
- Resists impact
- Withstands a wide temperature range to meet your application requirements
- Provides good insulating qualities
- Select from rubber or acrylic adhesive and a choice of different foam carriers: urethane, polyethylene or acrylic





To replace screws and liquid adhesives, 3M™ Multipurpose Mounting Tape 4016 bonds immediately to many indoor surfaces, even permanently mounting a plastic soap dispenser to a mirror.




 $3M^{\it \tiny m}$  Double Coated Foam Tapes can be precisely die-cut and pre-applied to the back of any shape. Ready to mount to a variety of surfaces.



To permanently mount to a textured wall, 3M™ Extra Thick Multipurpose Mounting Tape 4008 bonds on contact and fills gaps between the surfaces.



3M™ Double Coated Urethane Foam Tapes bond plastic signs to painted cinder block. The foam fills gaps between irregular surfaces. Various foam thicknesses are available for surface conformance based on the degree of roughness.



3M™ Double Coated Polyethylene Foam Tapes with high tack adhesive bond foam spacers between the planes of a 3-dimensional P.O.P. display.

# **3M™ Double Coated Foam Tapes**

	Tape				Temp. Re	esistance		Relative	Adhesion	
Product	Thickness mils (mm)	Liner Type	Description	Adhesive Type	Min Hr	Days Weeks	Adhesive Type	HSE	LSE	Application Ideas
Urethane	•									
4004	250 (6.4)	Α								
4008	125 (3.2)	Α	Off white an an all							Bond acoustic panels to walls. Mount air fresheners. Mount
4016	62 (1.6)	Α	Off-white, open-cell urethane foam carrier. High shear adhesive with high	100	380°F (193°C)	220°F (104°C)	Med	High	Low	soap dispensers. Mount interior signs and nameplates. Attach
4026	62 (1.6)	Α	temperature resistance.							wire clips to various surfaces. Mount electrical channel to wall.
4032	31 (0.8)	Α								
4052	31 (0.8)	Α	Black version of 4032.	100	380°F	220°F	Med	High	Low	Bond acoustic panels to walls.
4056	62 (1.6)	Α	Black versions of 4016 and 4026.	100	(193°C)	(104°C)	ivied	nign	LOW	Mount air fresheners. Mount soap dispensers. Mount interior signs and nameplates. Attach
4085	45 (1.1)	Е	Off-white, open-cell urethane foam carrier. High tack adhesive.	740	200°F (93°C)	125°F (52°C)	Med	High	Low	wire clips to various surfaces. Mount electrical channel to wall.
Polyethy	lene									
4462	31 (0.8)	В	White or black, closed-cell	745	158°F	120°F				Attach hooks, wire clips and
4466	62 (1.6)	В	polyethylene foam carrier. High tack adhesive.	745	(70°C)	(49°C)	Med	High	Low	racks. Mount retail shelf price channels. Mount pen holders.
4492	31 (0.8)	С	White or black, closed-cell polyethylene foam carrier.	430	180°F	158°F	Med	High	Low	Mount nameplates on awards and novelties. P.O.P. displays
4496	62 (1.6)	С	High shear adhesive with high temperature resistance.	430	(82°C)	(70°C)	ivied	nign	LOW	and signs.
Acrylic										
4658F	31 (0.8)	D	Clear, closed-cell, acrylic foam tape. Clean removability from many substrates.	100	212°F (100°C)	175°F (80°C)	High	High	Low	Removable P.O.P. displays. Signs. Exhibits and trade shows. Nameplates.

Liner Types:

A - 3 mil 62# Densified Kraft paper - Green plaid

B - 3 mil Densified Kraft paper - White

C – 4 mil 58# Polycoated Kraft paper – Tan

D - 2 mil Polyester film - Clear

E – 3 mil Densified Kraft paper – Tan

Relative Adhesion: HSE – High Surface Energy LSE – Low Surface Energy



# **3M™ Double Coated Tapes**

# A Variety of Carriers for Easy Handling and Dispensing

3M™ Double Coated Tapes are engineered with adhesive on both sides of paper, film or tissue. This increases the dimensional stability of the adhesive for easy handling and application.

Depending on your production volume, you can apply tape by hand or with automatic high-volume dispensers. Select paper, polyester film or other synthetic carriers to help meet your special needs. Different adhesives (rubber, silicone or acrylic) can be on opposite sides of the carrier to join different materials. Your choice of properties include high temperature resistance, conformability to irregular surfaces, high initial adhesion, high shear strength and more.



With differential adhesive, the silicone adhesive side of 3M™ Double Coated Tape adheres to a silicone rubber keypad. Acrylic adhesive side adheres to a plastic base.



Simply roll on a strip or band of 3M™ Double Coated Tape 9832 for quick edge banding with no special equipment. Pressure sensitive adhesive tape grabs with immediate handling strength for improved productivity.



3M™ Double Coated Tape 410M is the quick, convenient way to bond golf club grips to shafts. Adhesive sets up fast and bonds firmly for long-lasting performance.



For precise fit, 3M™ Double Coated Tape is pre-applied to foam gasketing materials and then die-cut to size. This helps increase dimensional stability of the part to facilitate assembly.

		Tape Liner			Adh	esion			Temp.	Range				
Product	Description/Application Ideas	Cal. (mils)	Carrier Type	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
200MP/30	OLSE (Differential Adhesive)													
040015	Differential double coated tape featuring High Performance Acrylic Adhesive	0.7	DET	58#	4.0	24 in. x		10	9	1	3	9	-40	250
9496LE	200MP and Low Surface Energy Acrylic Adhesive 300LSE.	6.7	PET	PCK	4.2	36 in. sheets	_	9	9	10	1	7	-40	250
300LSE (L	ow Surface Energy Acrylic)													
93005LE	Very thin double-coated tape polyester tape with good anti-lifting properties.	2.0	PET	58# PCK/ 83# PCK	4.2/ 6.2	48 in. x 60 yd.	-	9	9	10	1	8	-40	300
93010LE		3.9	PET	58# PCK	4.2	54 in. x 180 yd.	-	9	9	10	1	8	-40	300
93015LE	High adhesion to polypropylene and LSE plastics for excellent graphic appearances. Good chemical/humidity resistance.	5.9	PET	58# PCK	4.2	54 in. x 180 yd.	-	9	9	10	1	8	-40	300
93020LE	,		PET	58# PCK	4.2	54 in. x 180 yd.	-	9	9	10	1	8	-40	300

### Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# 3M<sup>™</sup> Double Coated Tapes Output Description:



		Таре		Line	r				Adhe	esion			Temp.	Range
Product	Description/Application Ideas	Cal. (mils)	Carrier Type	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
300 (High 9	Strength Acrylic)													
444	Foam lamination. Gasket attachment.	3.9	PET	55# DK	3.2	48 in. x 108 yd.	-	7	9	9	9	6	-40	250
444PC	Foam lamination. Gasket attachment.	3.9	PET	58# PCK	4.2	48 in. x 108 yd.	-	7	9	9	9	6	-40	250
300MP+ (H	ligh Tack Acrylic)													
9832+	General purpose tape with improved temperature resistance.	4.8	PET	58# PCK	4.2	54 in. x 250 yd.	-	7	7	4	9	-	-40 (-40)	_
9832HL+	Same as 9832+ except with a heavier liner.	4.8	PET	83# PCK	6.2	54 in. x 250 yd.	-	7	7	4	9	-	-40 (-40)	_
99786+	Thin non-woven carrier for dimensional stability and improved handling.	5.5	Non- woven	58# PCK Printed	4.2	48 in. x 180 yd.	-	7	7	4	9	-	-40 (-40)	-
99786NP+	Same as 99786+ except on an unprinted liner.	5.5	Non- woven	58# PCK Unprinted	4.2	54 in. x 180 yd.	-	7	7	4	9	-	-40 (-40)	_
340 (High 1	Tack Acrylic)												'	
9456	High tack acrylic adhesive with good adhesion to many plastics.	5.0	Tissue	55# DK	3.2	54 in. x 180 yd.	-	6	6	5	4	8	-40	180
9824	Foam lamination. Gasket attachment.	3.1	PET	55# DK	3.2	54 in. x 250 yd.	-	6	6	5	4	8	-40	180
9828	Foam lamination. Gasket attachment.	4.0	PET	55# DK	3.2	54 in. x 250 yd.	-	6	6	5	4	8	-40	180
9828PC	High tack acrylic adhesive with good adhesion to many foams.	4.0	PET	74# PCK	5.6	54 in. x 250 yd.	-	6	6	5	4	8	-40	180
350 (High F	Performance Acrylic)													
9500PC	High performance with good chemical resistance.	5.6	PET	61.5 PCK	4.5	48 in. x 108 yd.	-	9	10	10	9	8	-40	450
3028EK	Same as 9500PC with an extensible kraft liner which facilitates narrow slitting.	5.6	PET	Extensible Kraft	5.5	48 in. x 108 yd.	-	9	10	10	9	8	-40	450
375 (High F	Performance Double Coated)													
9086	Easy tearing, easy handling.	7.5	Tissue	Glassine Black Logo	3.0	54 in. x 750 yd.	-	High	High	Med	Low	Good	-10	250
9087	Thick adhesive to bond rough surfaces.	10.2	PVC	Glassine Green Logo	3.0	54 in. x 750 yd.	-	High	High	Med	Low	Good	-10	185
400 (Acryli	c Adhesive)													
415	Splice papers, films and foils.	4.0	PET	60# DK	4.0	48 in. x 108 yd.	-	5	5	5	5	5	-60	250
9576	Splice papers, films and foils.	4.0	Clear PP	60# DK	4.0	27 in. x 360 yd.	-	5	5	5	5	5	-60	250

# Values: 1 = Lowest Performance; 10 = Highest Performance Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# **3M™ Double Coated Tapes**

Silicone/	Acrylic Differential													
9731	Differential adhesive. Silicone/Acrylic double coated tape. Ideal for attaching silicone materials to HSE or LSE materials.	5.5	PET	Clear PET/54# Tan PCK	3.0/5.4	48 in. x 180 yd.	_	10	10	9	8	8	-40	300
Silicone														
96042	Silicone attachment. Silicone linered for easier processing.	5	PET	White PET	2	48 in. x 180 yd.	-	9	8	7	6	10	-40	350
700/745	/760 (Synthetic Rubber)													
9443NP	High tack rubber adhesive with good adhesion to most plastics.	6	HDPE	60# DK	3.7	27 in. x 120 yd.	-	8	9	9	2	2	-40	200
9579	Core starting on metal cores.	9	HDPE	62# DK	3.7	27 in. x 144 yd.	-	8	9	9	2	2	-40	200
9589	Carpet attachment.	9	HDPE	60# DK	3.7	26 in. x 144 yd.	-	8	9	9	2	2	-40	200
830/850	/860 (Natural Rubber)													
401M	Used for mounting rubber or photopolymer printing plates.	9.0	Paper	54# DK	3.0	22 in. x 108 yd.	-	8	8	8	5	1	-40	180
410M	Core starting/end tabbing of papers, films and foils.	6.0	Paper	54# DK	3.0	23.5 in. x 108 yd.	-	8	8	8	5	1	-40	200
900 (Mis	cellaneous)													
9737	Clear, thin PET carrier. Aggressive and versatile splicing tape.	3.5	PET	55# DK White	3.5	54 in. x 180 yd.	-	5	5	2	5	7	-10	300
9738	Clear, non-woven tissue carrier. Aggressive and versatile splicing tape.	4.3	Non- woven tissue	55# DK White	4.3	54 in. x 180 yd.	-	5	5	2	5	7	-10	300
9740	Clear, high peel, tack and shear strength. Performance grade splicing tape for corrugators.	3.5	PET	55# DK	3.5	54 in. x 180 yd.	-	6	6	2	3	6	10	425
9741	Clear, thick, super aggressive tape. Adheres to a wide variety of substrates for splicing applications.	6.5	PET	55# Glassine	6.5	54 in. x 180 yd.	-	7	7	3	7	5	-40	200
9816L	General purpose, high tack, rubber-based adhesive.	3.5	PET	60# Kraft	3.5	54 in. x 200 yd.	-	8	8	7	7	3	-40	150
9816M	General purpose, high tack, rubber-based adhesive.	3.5	PET	74# Kraft	3.5	54 in. x 200 yd.	-	8	8	7	7	3	-40	150
9816H	General purpose, high tack, rubber-based adhesive.	3.5	PET	14 pt. Board	3.5	54 in. x 200 yd.	-	8	8	7	7	3	-40	150
9817L	Exposed side is acrylic, liner side is rubber-based. Excellent quick stick and adhesion to high and low energy surfaces.	3.3	PET	60# Kraft	3.5	54 in. x 200 yd.	-	8	7	6	7	3	-40	175
9817M	Exposed side is acrylic, liner side is rubber-based. Excellent quick stick and adhesion to high and low energy surfaces.	3.3	PET	74# Kraft	3.5	54 in. x 200 yd.	-	8	8	7	6	3	-40	175
9817H	Exposed side is acrylic, liner side is rubber-based. Excellent quick stick and adhesion to high and low energy surfaces.	3.3	PET	14 pt. Board	3.5	54 in. x 200 yd.	-	8	8	7	6	3	-40	175
Specialty	Differential Rubber/Acrylic													
9377	Flame retardant double-coated tape for carpet installation to bond carpet to interior floorboards.	11.0	PP	58# PCK	4.2	24 in. x 25 yd.	-	4, 10	_	-	-	8	40	250

# Values: 1 = Lowest Performance; 10 = Highest Performance Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# 3M™ Removable/Repositionable Tapes


### Versatility for Many Substrates on On-Off and Open-Close Applications

Some 3M™ Removable/Repositionable Tapes feature a "permanent" adhesive on one side of a film or tissue carrier and a removable/repositionable adhesive on the other side.

Other tapes in the line offer different levels of adhesion on each side. And others feature equal adhesive strength on each side for reliable attachment but with easy separation for repositioning or multiple openings and closings.

You can join substrates that include glass, metals, wood, paper, painted surfaces and many plastics.

With linered versions, you can initially join one side to a surface while the other side is covered with the liner, ready to be joined later to the second surface. Linerless versions are used for bonding both surfaces at the same time.





High tack side of 3M™ Removable/ Repositionable Tape 9415 "permanently" adheres to cores for winding up paper or film. Low tack side releases the paper or film when unwinding.

	I				•				مالہ ۵	•			<b>T</b>	D
		Tape			iner					esion				Range
Product	Description/Application Ideas	Cal. (mils)	Carrier Type	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
400/100	0* (Differential Adhesive)													
9415PC	Differential adhesive; polyester film carrier.	2	PET	78# PCK	6.0	48 in. x 216 yd.	-	5	5	5	4	5	-20	150
9416	Differential adhesive; tissue carrier.	1	Tissue	70# PCK	5.6	48 in. x 216 yd.	-	3	1	1	-	2	-20	150
928ATG	Reverse wound ATG version of 9416 on 1 in. core. Used with ATG700 Applicator.	1	Tissue	70# PCK	5.6	Up to 3/4 in. W Up to 36 yd. L	_	3	1	1	-	2	-20	150
420/105	0* (Differential Adhesive)													
9425	High tack/medium tack for	5.5	UPVC	58#	4.2	48 in. x 144	_	8	7	1	4	2	-20	125
9425	repositionable parts.	5.5	UPVC	PCK	4.2	yd. 48 In. X 144	_	3	1	1	1	2	-20	125
0.405117	High tack/medium tack acrylic adhesive	_	DET	58#	4.2	48 in. x 144	_	8	7	1	4	2		050
9425HT	offers permanent adhesion to one substrate with removability to the other.	5	PET	PCK	4.2	yd.	-	3	1	1	1	2	-20	250
400/107	0 (Repositionable Acrylic)													
665	Differential adhesive; linerless.	3.5	UPVC	None	-	46 in. x 108 yd.	-	5	5	5	4	5	-60	125
666	Differential adhesive; linered.	3.5	UPVC	LDPE	4.0	46 in. x 108 yd.	-	5	5	5	4	5	-60	125
800 (Nati	ural Rubber)													
401M	Temporary positioning or fixturing of parts during machining operations	9	Paper	54# DK	3	22 in. x 108 yd.	-	8	8	8	5	1	-40	180
410M	and plate mounting.	6	Paper	54# DK	3	23.5 in. x 108 yd.	-	8	8	8	5	1	-40	200

<sup>\*</sup>Second number reflects removable adhesive side.

### Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.


# **3M™ Adhesive Transfer Tapes**

### Neat, Precise Application and High Performance in a Variety of Applications

3M<sup>™</sup> Adhesive Transfer Tapes are rolls of pressure sensitive adhesive pre-applied to a special release liner.

For application, the tape is simply pressed, adhesive side down, to a surface and the liner is peeled off.

A variety of adhesive properties and liners are available to meet requirements for applications such as nameplate attachment to high and low surface energy plastics, appliance graphic overlays that perform in high temperatures, foam gasketing, web splicing and more.





With high cohesive strength, 3M™ Adhesive 200MP bonds aggressively with excellent temperature resistance. Meets the non-fogging specifications of the automotive industry.



For bonding flexible vinyl in such applications as door gaskets, 3M™ Adhesive Transfer Tape F9465PC resists the effect of plasticizers that tend to migrate from the vinyl.



3M<sup>™</sup> Adhesive Transfer Tape 465 has the grab strength for many printing splices, including flying splices, zero speed and manual overlap. Can be used with a variety of paper grades.



3M<sup>™</sup> Adhesive Transfer Tape 467MP is used to laminate metal foil to a circuit board to reduce interference on electronic circuitry.



For graphic beauty, 3M™ Acrylic Adhesive 100 attaches graphics in closed environments. With low odor, reduced outgassing and low fogging, it is used extensively in the automotive, aerospace and appliance industries.

# 3M™ Adhesive Transfer Tapes 😂 🍑 🗓 292



		Adhesive	Li	ner				Adhe	sion			Temp.	Range
Product	Description/Application Ideas	Caliper (mils)	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
	ligh Performance Acrylic)	(iiiis)	1,750	(111113)	OIZO	Орссо	Metal	T lustio	T lustio	r ouiii	ite sisti	( ' '	(1)
F9460PC	High performance industrial joining and metal fabrication.	2	58# PCK	4.2	60 in. x 180 yd.	UL	10	7	1	2	10	-40	500
F9469PC	High performance industrial joining and metal fabrication.	5	58# PCK	4.2	60 in. x 180 yd.	UL	10	7	1	2	10	-40	500
F9473PC	High performance industrial joining and metal fabrication.	10	58# PCK	4.2	60 in. x 180 yd.	UL	10	7	1	2	10	-40	500
200MP (Hi	gh Performance Acrylic)												
467MC	Same as 467MP with a paper MicroChannel liner to aid in bubble and wrinkle free graphic attachment.	2	58# PCK	4.2	54 in. x 180 yd.	-	10	9	1	3	9	-40	400
467MCF	Same as 467MP with a polyester MicroChannel liner to aid in bubble and wrinkle free graphic attachment.	2	PET	4.2	54 in. x 180 yd.	-	10	9	1	3	9	-40	400
467MP	Graphic attachment and general industrial joining. Industry standard. 60 in. width master also available.	2	58# PCK	4.2	48 in. x 180 yd.	UL MH	10	9	1	3	9	-40	400
467MPF	Polyester liner for rotary processing of graphic and die cut parts.	2	PET	2.0	54 in. x 180 yd.	UL	10	9	1	3	9	-40	400
468MC	Same as 468MP with a paper MicroChannel liner to aid in bubble and wrinkle free graphic attachment.	5	58# PCK	4.0	54 in. x 180 yd.	-	10	9	1	3	9	-40	400
468MCF	Same as 468MP with a polyester MicroChannel liner to aid in bubble and wrinkle free graphic attachment.	5	PET	4.0	54 in. x 180 yd.	_	10	9	1	3	9	-40	400
468MP	Industry standard for graphic attachment and die cut parts. 60 in. width master also available.	5	58# PCK	4.2	48 in. x 180 yd.	UL MH	10	9	1	3	9	-40	400
468MPF	Thicker version of 467MPF.	5	PET	2.0	54 in. x 180 yd.	UL	10	9	1	3	9	-40	400
9667MP	Same as 467MP on heavy, lay-flat liner for kiss-cutting. 48 in. width master also available.	2	83# PCK	6.2	54 in. x 180 yd.	UL	10	9	1	3	9	-40	400
9668MP	Same as 468MP on heavy, lay-flat liner. 48 in. width master also available.	5	83# PCK	6.2	54 in. x 180 yd.	UL MH	10	9	1	3	9	-40	400
9668MPL	Better lay-flat properties.	5	94# PCK	7.0	60 in. x 180 yd.	-	10	9	1	3	9	-40	400
220 (Indus	trial Acrylic)												
9502	Economical attachment of graphics and industrial joining. 60 in. width master also available.	2	58# PCK	4.2	48 in. x 180 yd.	UL	8	7	1	2	8	-40	350
9505	Thicker version of 9502 for textured surfaces. 60 in. width master also available.	5	58# PCK	4.2	48 in. x 180 yd.	UL	8	7	1	2	8	-40	350
9552	Double-linered laminating adhesive version of 9502.	2.3	58/58# PCK	4.2	48 in. x 360 yd.	UL	8	7	1	2	8	-40	350
9555	Double-linered laminating adhesive version of 9505.	4.9	58/58# PCK	4.2	48 in. x 360 yd.	UL	8	7	1	2	8	-40	350

### Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# 3M™ Adhesive Transfer Tapes **② ② 292**



		Adhesive	L	iner				Adhe	esion			Temp.	Range
Product	Description/Application Ideas	Caliper (mils)	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
290 (Low	Outgassing Acrylic)												
501FL	Ultra-clean adhesive for low outgassing applications.	1	PET	2.0	54 in. x 180 yd.	-	9	7	1	2	9	-40	450
502FL	Ultra-clean adhesive for low outgassing applications.	2	PET	2.0	54 in. x 180 yd.	-	9	7	1	2	9	-40	450
300 (High	Strength Acrylic)												
927	Attach gaskets and a variety of industrial foam materials.	2	60# DK	3.5	48 in. x 180 yd.	-	7	9	9	9	6	-40	250
950	Thicker version of 927.	5	60# DK	3.5	48 in. x 180 yd.	UL	7	9	9	9	6	-40	250
950EK	Thicker version of 927 with extensible Kraft liner.	5	78# EK	6.0	48 in. x 180 yd.	-	7	9	9	9	6	-40	250
992U	For performance-engineered labels. UV indicator in adhesive.	2	55# DK	3.2	48 in. x 180 yd.	UL	7	9	9	9	6	-40	250
9458	Thin, high tack adhesive for rotary processing HSE and LSE parts.	1	55# DK	3.2	54 in. x 360 yd.	UL	7	9	9	9	6	-40	250
9459W	White version of laminating adhesive 9459S.	1.5	55# DK	3.2	48 in. x 360 yd.	UL	7	9	9	9	6	-40	250
9471	For smooth LSE plastics.	2	60# DK	3.5	48 in. x 180 yd.	UL MH	7	9	9	9	6	-40	250
9472	5.0 mil version of 9471; for textured surfaces.	5	60# DK	3.5	48 in. x 180 yd.	UL MH	7	9	9	9	6	-40	250
9653	A 3.5 mil version of 9471 on a heavy, lay-flat liner for kiss-cutting.	3.5	83# PCK	6.2	48 in. x 180 yd.	UL	7	9	9	9	6	-40	250
9671	Heavier linered version of 9471 for easy handling, lay-flat properties.	2	83# PCK	6.2	48 in. x 180 yd.	UL MH	7	9	9	9	6	-40	250
9672	Heavier linered version of 9472 for easy handling, lay-flat properties.	5	83# PCK	6.2	48 in. x 180 yd.	UL	7	9	9	9	6	-40	250
9673	Same as 9671 with unprinted liner.	2	83# PCK	6.2	48 in. x 180 yd.	UL MH	7	9	9	9	6	-40	250
300FR (Fla	ıme Retardant)												
9372W	Flame retardant. Moisture stable liner.	2	83# PCK	6.2	60 in. x 180 yd.	UL	8	9	9	9	6	-40	250
9372DKW	Flame retardant. Rotary diecuttable liner.	2	55# DK	3.2	60 in. x 180 yd.	UL	8	9	9	9	6	-40	250
9375W	Flame retardant. Moisture stable liner.	5	83# PCK	6.2	60 in. x 180 yd.	UL	8	9	9	9	6	-40	250

<sup>\*</sup>Products in this platform are  $3M^{\mbox{\tiny M}}\mbox{ VHB}^{\mbox{\tiny M}}\mbox{ Tapes offering our highest strength.}$ MH meets Mil-P-19834B Type I.

### Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# 3M™ Adhesive Transfer Tapes 😂 🍑 🗓 292



		Adhesive	L	iner				Adhe	sion			Temp.	Range
Product	Description/Application Ideas	Caliper (mils)	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
300LSE (L	ow Surface Energy Acrylic)												
9453FL	Film linered version of 9453LE for rotary processing.	3.5	PET	2.0	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9453LE	A 3.5 mil version of 9471LE for application to rough surfaces. 48 in. master width available.	3.5	58# PCK	4.2	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9471FL	Film linered version of 9471LE for rotary processing.	2.3	PET	2.0	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9471LE	Bonds graphics to powder coatings, LSE plastics and oily materials.	2.3	58# PCK	4.2	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9472FL	A 5 mil version of 9471LE with film liner for textured surfaces.	5.2	PET	2.0	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9472LE	Thicker adhesive for textured LSE plastics and powder coatings.	5.2	58# PCK	4.2	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9653LE	Heavy linered 9453LE for easy handling and lay-flat properties.	3.5	83# PCK	6.2	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9671LE	Heavy linered 9471LE for easy handling and lay-flat properties.	2.3	83# PCK	6.2	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
9672LE	Heavy linered 9472LE for easy handling and lay-flat properties.	5.2	83# PCK	6.2	54 in. x 180 yd.	UL	9	10	10	1	7	-40	300
300MP+ (H	High Tack Acrylic)												
9772WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	2	96# PCK	7.0	60 in. x 360 yd.	-	7	7	4	9	-	-40 (-40)	-
9773WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	3	96# PCK	7.0	60 in. x 360 yd.	-	7	7	4	9	_	-40 (-40)	-
9774WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	4	96# PCK	7.0	60 in. x 360 yd.	-	7	7	4	9	-	-40 (-40)	-
9775WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	5	96# PCK	7.0	60 in. x 360 yd.	-	7	7	4	9	-	-40 (-40)	-
320 (High	Tenacity Acrylic)												
9447	Designed for use with 3M™ Label Component Systems.	1	55# DK	3.2	54 in. x 360 yd.	-	5	5	1	1	5	-60	250
350 (High	Performance Acrylic)												
9442	Excellent temperature and solvent resistance; high bond to low surface energy substrates.	2	55# DK	3.2	48 in. x 180 yd.	UL	9	10	10	9	8	-40	450
9445	Thicker version of 9442.	5	55# DK	3.2	48 in. x 180 yd.	UL	9	10	10	9	8	-40	450
9482PC	High tack and shear strength; excellent adhesion to plastics and foams.	2	58# PCK	4.2	48 in. x 180 yd.	UL	9	10	10	9	8	-40	450
9485EK	Thicker version of 9482PC with an extensible Kraft liner.	5	78# EK	6.0	48 in. x 180 yd.	-	9	10	10	9	8	-40	450
9485PC	A 5 mil version of 9482PC.	5	58# PCK	4.2	48 in. x 180 yd.	UL	9	10	10	9	8	-40	450
9675	Heavy linered version of 9485PC for easy handling, lay-flat properties.	5	83# PCK	6.2	48 in. x 180 yd.	-	9	10	10	9	8	-40	450

<sup>\*</sup>Manufactured using a solventless adhesive coating process.

### Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# **3M™ Adhesive Transfer Tapes**

=	292

		Adhesive	Li	iner				Adhe	sion			Temp.	Range
Product	Description/Application Ideas	Caliper (mils)	Туре	Caliper (mils)	Master Size	Specs	Metal	HSE Plastic	LSE Plastic	Foam	Chem. Resist.	Low (°F)	High (°F)
400 (Acryl	ic Adhesive)												
463	High tack and excellent adhesion to most paper stocks. For automatic dispensing.	2	60# DK	3.5	48 in. x 180 yd.	-	5	5	5	4	5	-60	250
465	Same as 463, but with easy liner release for manual or hand application.	2	60# DK	3.5	48 in. x 180 yd.	-	5	5	5	4	5	-60	250
9457	Adhesive with long term stability, excellent outdoor performance and UV resistance. Adhesive 400 is best if necessary to apply at cooler temperatures.	1	55# DK	3.2	54 in. x 360 yd.	UL	5	5	5	4	5	-60	250
9665	Thicker version of 9457.	2	58# PCK	4.2	48 in. x 180 yd.	_	5	5	5	4	5	-60	250
420 (Acryl	ic Adhesive)												
F9752PC	High tack; can be applied in temperatures as low as 32°F (0°C).	2	58# PCK	4.2	54 in. x 360 yd.	-	7	7	8	4	6	-40	300
F9755PC	Thicker version of F9752PC for textured surfaces.	5	58# PCK	4.2	54 in. x 360 yd.	_	7	7	8	4	6	-40	300
430 (Acryl	ic Adhesive)												
9497	Pink tinted high temperature splicing tape.	2	60# DK	3.5	48 in. x 360 yd.	-	6	6	5	4	5	-40	350
9499	Transparent version of 9497.	2	60# DK	3.5	48 in. x 360 yd.	-	6	6	5	4	5	-40	350
Specialty /	Acrylic												
9379	Jet fuel and hydraulic fluid resistant adhesive transfer tape.	2	PET	2	48 in. x 200 yd.	MH*	9	8	1	2	9	-40	350
9380	Thicker version of 9379.	5	PET	2	48 in. x 200 yd.	MH*	9	8	1	2	9	-40	350
F9465PC	Vinyl plasticizer resistant adhesive.	5	58# PCK	4.2	54 in. x 360 yd.	-	10	10	7	5	5	-40	200
F9467U	Vinyl plasticizer resistant adhesive.	3.5	58# PCK	4.2	54 in. x 180 yd.	-	10	10	7	5	5	-40	200
Silicone													
91022	Silicone attachment. Silicone linered for easier processing.	2	White PET	2	48 in. x 180 yd.	-	9	8	7	6	10	-40	500

<sup>\*</sup>MH meets Mil-P-19834B Type I.

### Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

# **Scotch® ATG Adhesive Transfer Tapes**

### Finger Touch Application of Pressure Sensitive Adhesive

Versatility, convenience and speed. That's what you get with Scotch® ATG Adhesive Transfer Tapes for assembly operations in businesses ranging from appliance and printing to P.O.P. and electronics. Readily bond, join, mount, or laminate materials such as paper, plastics, metal. foam and more.

With Scotch® ATG Applicators, a touch of the finger triggers a quick, controlled application of Scotch® ATG Adhesive Transfer Tape at the same time as the liner rewinds into the applicator. There is no mess and no cleanup. 3M advanced acrylic adhesive bonds on contact and is formulated with a choice of properties such as high temperature resistance, differential tack, adhesion to low surface energy plastic and more.





Save time and effort with Scotch® ATG Adhesive Transfer Tapes and Applicators. You apply a precise strip of adhesive at the same time as the liner rewinds into the applicator.



Scotch® ATG Applicator 700 with Scotch® ATG Adhesive Transfer Tape 924 makes fast work of folder assembly. Pressure sensitive adhesive bonds immediately and the folder pocket is ready to hold contents.



Scotch® ATG Applicator 700 for 3/4" and 1/2" wide tape



Scotch® ATG Applicator 714 for 1/4" wide tape



Scotch® ATG Applicator 752C for 3/4", 1/2" and 1/4" wide tape (1/4" adapter purchased separately)



Scotch® ATG Applicator 3662 for 2" wide tape

	Tape Thickness			erature tance			ntive esion		Adhesive Transfer
Product	w/o Liner mils (mm)	Description	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas	Tape Equivalent
350 (Firm	Acrylic)								
926	5 (0.13)	High adhesion, excellent shear holding power to a variety of substrates. UV resistant.	450°F (232°C)	300°F (149°C)	Very Good	High	Med- High	Nameplates on award plaques, bonding foam insulation.	_
300 (Soft /	Acrylic)								
969	5 (0.13)	Very high initial adhesion, good shear holding power to a variety of materials including plastics.	250°F (121°C)	180°F (82°C)	Med	High	Med- High	Assemble point of purchase displays, attach fabric swatches in sample books.	_
300 (High	Tack Acrylic)								
976	2 (0.05)	High tack. Excellent adhesion to most plastics.	250°F (121°C)	150°F (65°C)	Med	High	High	Attach fabric swatches in sample books.	927
400 (Gene	eral Purpose A	Adhesive)							
924	2 (0.05)	General purpose. Excellent adhesion to most paper stocks.	250°F (121°C)	180°F (82°C)	Med	Med	Low	Seal pocket in folders. Bond mat board in picture frames. Splice paper, films, foils. General purpose bindery attaching.	465
987*	1.7 (0.040)	General purpose. Excellent adhesion to most paper stocks.	250°F (121°C)	180°F (82°C)	Med	Med	Low	Seal pocket in folders. Bond mat board in picture frames. Splice paper, films, foils. General purpose bindery attaching.	9498

<sup>\*3</sup>M Brand. Relative Adhesion: HSE – High Surface Energy; LSE – Low Surface Energy

# **3M™ Extended Liner Tapes**

### Versatile Pressure Sensitive Adhesive on Easy-to-Remove Liners

3M™ Extended Liner Tapes offer the adhesive versatility of 3M tapes but with liners wider than the adhesive. This leaves an easy-to-lift edge for convenient and easy liner removal. With the variety of adhesives, you have a selection of performance characteristics such as high tack for coated papers and plastics, low tack for temporary attachment, high temperature resistance and more. Apply manually or with equipment matched to your production volume requirements.





3M<sup>™</sup> Extended Liner Tapes are available with a release liner wider than the adhesive. This provides an easy-to-grab edge for convenient liner removal.

Depending on adhesive type, 3M™ Extended Liner Tapes are applied to envelopes, polybags, boxes or tubes. User simply peels off liner to expose the adhesive for an immediate, secure closure.



3M<sup>™</sup> Extended Liner Tapes 450XL, 450EK and 465XL immediately bond product information "outserts" to polyethylene bottles. Holds tightly but can be cleanly removed.

	Tape Thickness				erature tance			itive esion	
Product	w/o liner mils (mm)	Liner Type	Description	Min Hr	Days Weeks	Solvent Resistance	HSE	LSE	Application Ideas
340									
466XL	2 (0.05)	62# DK White with Black Print	High tack; Permanent	180°F (82°C)	150°F (65°C)	Med	High	High	Coated papers and low surface energy (LSE) plastics. Overnight envelopes. Features an end-of-roll indicator tab for automated dispensing.
400									
465XL	2 (0.05)	60# DK Tan with Green Print	General purpose	250°F (121°C)	180°F (82°C)	Med	Med	Low	Seal flaps on overnight envelopes. Pressure sensitive edging on business forms. General commercial joining applications. For attaching materials that require more adhesive thickness. Larger outsert attachments.
450EK	1 (0.025)	78# Extensible Kraft White without Print	General purpose	250°F (121°C)	180°F (82°C)	Med	Med	Low	Pharmaceutical outsert attachment. For applications requiring a more tear resistant liner.
450XL	1 (0.025)	60# DK Tan with Green Print	General purpose	250°F (121°C)	180°F (82°C)	Med	Med	Low	Pharmaceutical outsert attachment. General paper attachment.
920XL	1 (0.025)	40# DK White with Red Print	General purpose	250°F (121°C)	180°F (82°C)	Med	Med	Low	Seal flaps on polybags and envelopes. Pressure sensitive edging on business forms, literature, photos, posters and labels.
9926XL	1 (0.025)	40# DK White with Red Print	General purpose	180°F (82°C)	150°F (65°C)	Med	Med	Low	Economical alternative for general paper-to-paper applications.
600									
9934XL	4 (0.10)	60# DK tan without Print	High tack to LSE materials	150°F (65°C)	120°F 49°C)	Med	High	High	P.O.P. displays. Difficult splicing applications, shelf talkers, price tags, polyethylene foam bonding. Indirect food-contact applications. High tack to LSE materials.
760									
476XL	6 (0.16)	62# DK White with Red Print	High tack, double coated film	150°F (65°C)	120°F 49°C)	Med	High	High	Heavy-duty sealing. Mounting of promotional items. Core starting. Closure of overnight boxes, tubes and envelopes. Indirect food-contact applications.
770									
9925XL*	2.5 (0.065)	43# DK White with Black Print	Tissue reinforced; High initial adhesion to a wide variety of materials	150°F (65°C)	100°F 41°C)	Low	Med	Med	General mounting. P.O.P. items. Attaching tags and labels. Core starting. Permanent bonding paper-topaper, business forms, traffic tickets, novelty items and literature. Indirect food-contact applications.

<sup>\*</sup>Non-liner side is adhesive coated full width.

Relative Adhesion: HSE – High Surface Energy LSE – Low Surface Energy

# **3M Industrial Adhesives and Tapes**

# **Specialty Technologies**

# Supporting your designs behind the seams.

# **Powerful Fastening Solutions**


Weather-resistant single coated foam tapes are practical solutions that protect against moisture, dust, vibration and impact, and remain flexible.

# 3M™ Dual Lock™ Reclosable Fasteners

# Holding Power to Replace Screws, Bolts and Rivets

Durable enough to last through repeated opening and closing. Unique mushroom-shaped heads snap shut and stay locked.

- Durable up to 1,000 openings and closings before losing 50% of original tensile strength
- Helps reduce vibration
- Temperature, moisture and UV resistant
- Strong, pressure-sensitive adhesive bonds on contact
- Interlocking mushroom-shaped heads have 5X the tensile strength of hook-and-loop products





Secure plastic signs to window glass.



Anchor vehicle accessories to dashboard.



Attach elevator control panel to interior wall.



Fasten ceiling panels to interior for future access.



Attach access panels to industrial, electronic and electrical equipment.

# **3M™ Dual Lock™ Reclosable** Fasteners and Applications (1) (2)<sub>292</sub>



Best Suggested Product Primer Recommended

A Performance Dependent on Selected Attachment Method


Product	Stem Density (per sq/in)	Adhesive	Color	3M Liner	Engaged Thickness	Temperature Resistance °F (°C)	Metals (AI & SS)	Glass	Plastics (Acrylic, PC, ABS)	Powder Coated Paints	Low Surface Energy (PP,PE)	Indoor/ Outdoor Use	Appliance & Electronics	Design & Construction	Furniture & Upholstery	General Industrial	Marine & Specialty Vehicle	POP, Display & Signage
SJ3540	250	Rubber	Black	White, 5 mil (0.13mm) Polyolefin	0.23 in (5.7mm)	120 (49)			•			Indoor			•	•		
SJ3541	400	Rubber	Black	White, 5 mil (0.13mm) Polyolefin	0.23 in (5.7mm)	120 (49)			•			Indoor						
SJ3542	170	Rubber	Black	White, 5 mil (0.13mm) Polyolefin	0.23 in (5.7mm)	120 (49)						Indoor						
SJ3550CF	250			01														
SJ3551CF	400	Clear Acrylic	Black	Clear, 4 mil (0.10mm)	0.23 in (5.7mm)	200 (93)				•	•	Indoor/ Outdoor		•				
SJ3552CF	170			Polyolefin		,												
SJ3560	250			01														
SJ3561	400	Clear Acrylic	Clear	Clear, 4 mil (0.10mm)	0.23 in (5.7mm)	200 (93)				•	•	Indoor/ Outdoor						
SJ3562	170			Polyolefin	,	(/												
SJ3870	250			Dod														
SJ3871	400	Modified Acrylic	Black	Red, 4.5 mil (0.11mm)	0.24 in (6.1mm)	140 (60)					•	Indoor/ Outdoor						
SJ3872	170			Polyolefin														
SJ3782	250	Low Surface Energy Acrylic	Black	Brown, 83# Polykraft	0.16 in (4.1mm)	120 (49)	•		•	•	•	Indoor/ Outdoor				•		•
SJ3440	250	None	Black	No Liner	0.15 in (3.86mm)	220 (104)	_	<b>A</b>	_	_	_	Indoor/ Outdoor	<b>A</b>	_	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>
SJ3441	400	None	Black	No Liner	0.15 in (3.86mm)	220 (104)	_	<b>A</b>	<b>A</b>	<b>A</b>	_	Indoor/ Outdoor	<b>A</b>	<b>A</b>	<b>A</b>	<b>^</b>	<b>A</b>	<b>A</b>
SJ3442	170	None	Black	No Liner	0.15 in (3.86mm)	220 (104)	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	Indoor/ Outdoor	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>
SJ3443	400	Non- woven	Black	No Liner	0.28 in (7.1mm)	220 (104)	<b>^</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>^</b>	Indoor/ Outdoor	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>
SJ3444	170	Backing with	Black	No Liner	0.28 in (7.1mm)	220 (104)	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	Indoor/ Outdoor	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>	lack
SJ3445	250	No Adhesive	Black	No Liner	0.28 in (7.1mm)	220 (104)	<b>^</b>	<b>A</b>	<b>A</b>	<b>A</b>	<b>^</b>	Indoor/ Outdoor	<b>A</b>	<b>A</b>	<b>^</b>	<b>A</b>	<b>^</b>	<b>A</b>
SJ3460	250	None	Clear	No Liner	0.15 in (3.86mm)	220 (104)	<b>A</b>	<b>A</b>	<b>A</b>	_	•	Indoor/ Outdoor	_	<b>A</b>	<b>A</b>	<b>A</b>		<b>A</b>
SJ3463	400	Piece Part Circle†	Black	No Liner	0.20 in** (5.1mm)	220 (104)						Indoor/ Outdoor						
SJ3481	400	Rigid Strip†	Black	No Liner	0.20 in** (5.1mm)	220 (104)	•	•	<b>A</b>	•	•	Indoor/ Outdoor	<b>A</b>	•	<b>A</b>	<b>A</b>	<b>A</b>	<b>A</b>
Low Profile																		
SJ4570	Low Profile/ Thin	Low Surface Energy Acrylic	Clear	Brown, 83# Polykraft	0.098 in (2.489mm)	158 (70)						Indoor/ Outdoor						•
SJ4575	Low Profile/ Thin	Low Surface Energy Acrylic	Black	Brown, 83# Polykraft	0.098 in (2.489mm)	158 (70)			•			Indoor/ Outdoor						•
SJ4580	Low Profile/ Thin	Clear Acrylic	Clear	Red, 4.5 mil (0.11mm) Polyolefin	0.12 in (3.0mm)	200 (93)				•	•	Indoor/ Outdoor						

<sup>\*\*</sup>Single thickness; not engaged †No adhesive

# 3M™ Hook and Loop Reclosable Fasteners

### Hooks on One Side, Loops on the Other for Secure, Repeated Closures

- Reliable PSA holds on contact with a variety of materials
- Low profile options, as much as 75% thinner than standard product
- Up to 5,000 closures for standard Hook and Loop
- Flame resistant product available
- Also available without adhesive





Attach cushioning panels in an ambulance or bus.



Sew to the fabric and leather of jackets and gloves.



Use as a replacement for string, tapes, rubber bands, wire and strapping.



Attach removable seat cushions.



Hang graphics and banners that change frequently.

# 3M<sup>™</sup> Hook and Loop Reclosable Fasteners and Applications

Best Suggested Product

 Performance Dependent on Selected Attachment Method

▲ Primer Recommended

☐ Back-to-back fastener which can wrap around any type of surface or substrate


Product Type	Adhesive	Closure Life	Product Material	Liner Description	Engaged Thickness	Temperature Resistance °F (°C)	Metals (Al & SS)	Glass	Plastics (Acrylic, PC, ABS)	Powder Coated Paints	Low Surface Energy (PP, PE)	Indoor/Outdoor Use	Aerospace & Rail	Furniture & Upholstery	General Industrial	Marine & Specialty Vehicle	POP, Display & Signage
High Performance				14/12/2000	l												
SJ3526N Hook	High Performance Rubber	5,000	Nylon	White, 3 mil (0.08mm) Polyethylene Film 3M Red Print	0.14 in. (3.6mm)	120 (49)						Indoor					
SJ3527N Loop	High Performance Rubber	5,000	Nylon	White, 3 mil (0.08mm) Polyethylene Film 3M Red Print	0.14 in. (3.6mm)	120 (49)						Indoor					
SJ3572 Hook	High Performance Acrylic	5,000	Nylon	Clear, 4 mil (0.10mm) Polypropylene Film Embossed 3M Logo	0.14 in. (3.6mm)	200 (93)				<b>A</b>	<b>A</b>	Indoor/ Outdoor					
SJ3571 Loop	High Performance Acrylic	5,000	Nylon	Clear, 4 mil (0.10mm) Polypropylene Film Embossed 3M Logo	0.14 in. (3.6mm)	200 (93)				<b>A</b>	<b>^</b>	Indoor/ Outdoor					
General Purpose	,			<u> </u>	<u>I</u>												
SJ3522 Hook	Plasticizer Resistant Acrylic	5,000	Nylon	Clear, 3.5 mil (0.08mm) Polyolefin Film, No print	0.14 in. (3.6mm)	158 (70)						Indoor/ Outdoor					_
SJ3523 Loop	Plasticizer Resistant Acrylic	5,000	Nylon	Clear, 3.5 mil (0.08mm) Polyolefin Film, No print	0.14 in. (3.6mm)	158 (70)						Indoor/ Outdoor					
SJ3530 Hook	High Tack Rubber	5,000	Nylon	Yellow, 3 mil (mm) Polyethylene Film No Print	0.14 in. (3.6mm)	90 (32)						Indoor					
SJ3531 Loop	High Tack Rubber	5,000	Nylon	Yellow, 3 mil (mm) Polyethylene Film No Print	0.14 in. (3.6mm)	90 (32)						Indoor					
No Adhesive																	
SJ3401 Loop	None	5,000	Nylon	None	0.12 in. (3.0mm)	200 (93)	•	•	•	•	•	Indoor/ Outdoor		•	•		•
SJ3402 Hook	None	5,000	Nylon	None	0.12 in. (3.0mm)	200 (93)	•	•	•	•	•	Indoor/ Outdoor		•	•		•
Low Profile/Thin																	
SJ3506 Hook	Acrylic	25	Polypropylene	Brown #83 Polykraft Green Print	0.034 in. (0.84mm)	158 (70)				•	<b>A</b>	Indoor/ Outdoor					
SJ3507 Loop	Acrylic	25	Polyester	Brown #83 Polykraft Green Print	0.034 in. (0.84mm)	158 (70)				•	•	Indoor/ Outdoor					
SJ3001 Back-to-Back Hook and Loop	None	10	Polypropylene/ Nylon	None	0.053 in. (1.3mm)	200 (93)						Indoor					
Flame Resistant																	
SJ3519FR Hook	Flame Resistant	5,000	FR Nylon	White, 3 mil (0.08mm) Polyethylene Film 3M Red Print	0.14 in. (3.6mm)	158 (70)						Indoor					
SJ3518FR Loop	Flame Resistant	5,000	FR Nylon	White, 3 mil (0.08mm) Polyethylene Film 3M Red Print	0.14 in. (3.6mm)	158 (70)						Indoor					
SJ3419FR Hook	None	5,000	FR Nylon	None	0.12 in. (3.0mm)	200 (93)	•	•	•	•	•	Indoor/ Outdoor	•	•	•		
SJ3418FR Loop					0.12 in.	200						Indoor/			$\neg$		

# **3M™ Single Coated Foam Tapes**

### Roll-on Protection Against Moisture, Dust, Noise, Vibration and Impact

3M™ Single Coated Foam Tapes are strips of foam in a roll with high strength acrylic adhesive on one side of the foam. Cut to length, they seal, damp, insulate or cushion. For die-cut shapes, 3M™ Single Coated Foam Tape Series 4100, 4300, and 4700 is protected by a liner. With 3M™ Single Coated Foam Tape Series 4500, the liner is on the non-adhesive side to minimize foam stretching while placing the gasket.

Urethane foams seal, cushion, damp sound, and absorb vibration.
Weather-resistant vinyl foams seal out light and dust when under compression and remain flexible even when exposed to variable temperatures and UV.





In a computer printer, 3M™ Urethane Foam Tape 4318 is a very soft, low density cushion that helps absorb impact and vibration.



To help prevent light leakage around a sign perimeter, 3M™ Vinyl Foam Tape 4726 attaches securely on contact.



When compressed 50%, the open cell construction of 3M™ Urethane Foam Tape 4314 provides an air barrier and cushion in electronic equipment.



In outdoor mailboxes, strips of 3M<sup>™</sup> Vinyl Foam Tape 4504 helps seal the inside from rain and dirt. Vinyl provides excellent aging characteristics and remains flexible.

				Approximate		Tensile Strength	Compression Deflection			erature rance	
Product	Color	Description	Adhesive	Thickness in. (mm)	Density lb./cu.ft (kg/cu.m)	psi (kPa)	25% psi (kPa)	Compression Set % Loss	Short- term	Long- term	
Urethane											
4104*		Firm, rigid, open cell urethane		0.250 (6)	12 (192)	115 (795)	4 (27.6)	8			
4108	Natural White	foam for cushioning. Allows air or gas vapors to pass through. Not	350 Acrylic	0.125 (3)	16 (256)	130 (895)	6 (82.8)	8	350°F (176°C)	200°F (93°C)	
4116	771110	recommended for outdoor use.	7 (6) 7116	0.062 (1.5)	18 (288)	115 (795)	12 (82.8)	12	(170 0)	(55 0)	
4314		Soft conformable, low density		0.250 (6)	2 (32)	25 (170)	0.3 (2.1)	5			
4317*	Charcoal	foam for sealing out air, dust and light when compressed 30%.	430	0.375 (9.5)	2 (32)	25 (170)	0.3 (2.1)	5	250°F	150°F	
4318	Gray	Used to help damp sound and absorb vibration in electronics.	Acrylic	0.125 (3)	2 (32)	25 (170)	0.3 (2.1)	5	(121°C)	(66°C)	
Vinyl											
4504*		Durable, flexible, closed cell vinyl foams with excellent aging		0.250 (6)	20 (320)	90 (620)	4 (27.6)	15			
4508*	Black	characteristics. Weather resistant.	430 Acrylic	0.125 (3)	20 (320)	100 (690)	4 (27.6)	15	250°F (121°C)	150°F (66°C)	
4516*		Application ideas include dust and moisture seal.		0.062 (1.5)	25 (400)	130 (895)	4 (27.6)	15	( ,		
4714*				0.250 (6)	14 (225)	75 (515)	2 (13.8)	5			
4718*	Black	Same as above except lower density and liner over PSA.	430 Acrylic	0.125 (3)	20 (320)	100 (690)	4 (27.6)	15	250°F (121°C)		
4726*		density and liner over PSA.		0.062 (1.5)	20 (320)	130 (895)	3 (20.7)	15	(121 0)	(00 C)	

<sup>\*</sup>Meets requirements of UL 94HBF.

# 3M™ Converter Markets Center

# Converting 3M Technology into Successful Applications

3M Converters match 3M technologies to customer requirements with the exact form, fit, and functionality for application success in identifying, bonding, protecting, and electrical shielding or conducting.

Converter expertise includes part design, quick prototyping, laminating adhesives to various surfaces, printing labels and durable graphics, slitting, and die-cutting.

3M technologies include the following:

- 3M™ Performance Label Materials
- 3M<sup>™</sup> Thin Attachment Tapes
- 3M<sup>™</sup> Adhesive Transfer and Double Coated Bonding Tapes such as 3M<sup>™</sup> VHB<sup>™</sup> Tapes
- 3M™ Single Coated Tapes such as crepe masking tape
- 3M™ Reclosable Fasteners
- 3M™ Bumpon™ Protective Products
- And more



For permanent attachment of die-cut durable graphics, 3M™ Low Surface Energy (LSE)
Acrylic Adhesive 300 bonds on contact and stays tight on low surface energy plastics, powder coated paints, and lightly oiled metals.



3M" Performance Label Materials with Structured Adhesive — With unique microchannels throughout the structured adhesive, air flows freely from between the label adhesive and substrate. Hand-applied large labels go on smoothly and stay that way permanently without unsightly wrinkles and bubbles.



Dimensionally-stable 3M™ Double Coated Tapes are pre-applied to foam gasketing material and die-cut to precise shape and size for fast, easy application.



3M converters can slit 3M™ Masking Tapes to specified widths and roll lengths, as well as die-cut to unique shapes for specialized applications.



For hundreds to thousands of openings and closings, 3M converters customize 3M™ Reclosable Fasteners to meet exact customer requirements for form, fit, mating strength, and liner.



For a little touch of quiet and skid resistance on a PDA or other small product, custom 3M™ Bumpon™ Protective Products are scaled for the design. Adhesive is formulated to hold even a small bonding surface.



From the 150,000 possible combinations of adhesives, facestocks, overlaminates and liners, 3M has many choices for durable labels requiring UL and/or RoHS compliance.

# **Numerical Index**

Product	Page	Product	Page	Product	Page	Product	Page
1	62	463	91	987	92	4016	82
5	54, 60	465	91	992U	89	4026	82
10	60	465XL	93	1000NF	53, 54, 55, 62	4032	82
20	60	466XL	93	1099	54, 56, 62	4052	82
24	60	467MC	88	1099L	56, 62	4056	82
27	60	467MCF	88	1300	56, 62	4085	82
30H	60	467MP	88	1300L	56, 62	4104	100
30NF	54, 60	467MPF	88	1357	62	4108	100
49	53, 60	468MC	88	1357L	62	4116	100
60 CA	59, 60	468MCF	88	1386	32	4117	100
70	53, 59, 60	468MP	88	1469	32	4200 FC	67
72	62	468MPF	88	1751 B/A	29	4224NF	62
74	59, 60	476XL	93	1838 B/A	29	4314	100
74 CA	60	490	31	1838L B/A	29	4317	100
76	62	501FL	89	2000NF	54, 60	4318	100
77	53, 55, 59	502FL	89	2084	66	4411B	80
78	62	525	66	2158 B/A	29	4411G	80
78ET	59, 62	540	66	2214	24, 32	4411N	80
78HT	62	550FC	66	2216	25	4412G	80
80	56, 62	550FC + AC63	66	2216 B/A	30	4412N	80
90	54, 56, 59, 60	551	66	2216NS B/A	30	4462	82
90 CA	60	560	66	2158 BA	29	4466	82
	54, 59, 60	560 + AC63	66	2262	56, 62	4475	62
94	79	600	35, 69	2290	32	4491	62
94 CA	54, 59, 60	600NS	35, 69	3028EK	84	4492	82
94 ET	54, 59, 60	604NS	35	3501 B/A	28	4496	82
100	29	605NS	35	3532 B/A	33	4504	100
100 Plus	30	606	66	3549	35	4508	100
100FR	29	620NS	35	3731	50	4516	100
100NF	53, 55, 60	665	86	3738	50	4611	75
100NS	29	666	86	3747	50	4618	75
105	30	730UV	66	3748	50	4622	75
110	30	740UV	66	3748 VO	50	4624	75
125	30	760UV	66	3750	50	4646	75
200	43	800	66	3756	36	4655	75
221	32	810	33	3762	50	4658F	82
270	29	810NS	33	3762LM	50	4693	56, 62
401M	85, 86	826	62	3764	50	4714	100
405	31	847	56, 62	3776LM	50	4718	100
410M	85, 86	847H	62	3779	50	4726	100
415	84	920XL	93	3789	50	4799	56, 62
420	31	924	92	3792	50	4905	75
420LH	31	926	92	3792LM	50	4910	75, 78
	31	927		3794		4914	
	84	928ATG		3797		4914-015	•
	84	936		3901		4914-020	
	93	950		4000 UV		4919F	
	93	950EK		4001		4920	
	31	969		4004		4926	
	31	976		4008		4929	
		o, o		1000		1020	1 3

# **Numerical Index**

Product	Page	Product	Page	Product	Page	Product	Page
4930	75	6038PL	90	9482PC	90	9832HL +	84
4930F	75	6101	32	9485EK	90	9913	49
4936	74	6111	50	9485PC	90	9916	49
4936F	74	6111HT	50	9496LE	83	9917	49
4941	74, 78, 79	6116	53	9497	91	9921	49
4941F	74	6501	59	9499	91	9922	49
4943F	75	7240FR	31	9500PC	84	9925XL	93
4945	75	8010	34	9501	59	9926XL	93
4946	75	8010NS	34	9502	88	9929	49
4947F	74	8405NS	33	9505	88	9934XL	93
4949	75	8407NS	33	9552	88	9940	49
4950	75	8410NS	33	9555	88	9946	49
4951	75	8425NS	33	9576	84	53382	43, 69
4955	75	8610NS	34	9579	85	87979	43, 69
4956	74, 78	8625NS		9589	85	87982	43, 69
4956F		8705NS		9653	89	91022	91
4957F	75	8710NS		9653LE		93005LE	
	75	8725NS	33	9665		93010LE	
	75	8805NS	34	9667MP		93015LE	
4979F		8810NS	34	9668MP		93020LE	
	74	8825NS	34	9668MPL		96042	
	74	8910NS	24, 34	9671		97331	
5001		9086	84	9671LE		98073	ŕ
5010		9087	84	9672		99786+	ŕ
5200		9372DKW	89	9672LE		99786NP+	
5200 FC		9372W	89	9673		250050	
5354		9375W	90	9675		650050	
	74. 76	9377	85	9725		AC09	
	74, 76	9379	91	9726			
	74, 76, 79	9380	91			AC77	
		9415PC	86	9727		AC79	
	74, 76	9416	86			AC113	
	74, 79	9425	86	9737		AC452	
5915P		9425HT		9738		AC649	
	74	9442	90	9740		AP111	
	74, 79	9443NP	85	9741		AP115	79
5925P		9445		9772WL+	90	AP596	67
	74	9447		9773WL+		B11F	
	74	9453FL		9774WL+		B16F	
	74	9453LE		9775WL+		B23F	
	74	9456		9785	49	B45F	78
5952	74, 78, 79	9457		9816H	85	B90F	77
5952P	74	9458		9816L	85	CA4	39
5952WF	74, 78			9816M	85	CA5	39
	74	9459W		9817H	85	CA7	39
5962	74, 78	9471		9817L	85	CA8	39
5962P	74	9471FL		9817M	85	CA9	38
5962WF	74	9471LE		9824	84	CA40	39
6035PC	90	9472		9828	84	CA40H	39
6035PL	90	9472FL		9828PC	84	CA50 Gel	39
6038PC	90	9472LE	90	9832+	84	CA100	39

# **Numerical Index**

Product	Page	Product	Page	Product	Page	Product	Page
CV45F	76	EZ250060	36	RP+110GP	74, 79	SJ3552CF	97
CV62F	76	EZ250120	36	RP+110GF	74	SJ3558	97
DP100	25, 29	EZ250150	36	RP+160GP	74	SJ3560	97
DP100 Plus	30	EZ250200	36	RP+160GF	75	SJ3561	97
DP100FR	29	F9460PC	88	RT09	7	SJ3562	97
DP100NS	29	F9465PC	91	RT38	41	SJ3571	99
DP105	30	F9467U	91	RT41	41	SJ3572	99
DP110	30	F9469PC	88	RT48	41	SJ3782	97
DP125	24, 25, 28, 30	F9473PC	88	RT5000B	39	SJ3870	97
DP190	30	F9752PC	91	SF20	39	SJ3871	97
DP270	25, 29	F9755PC	91	SF100	39	SJ3872	97
DP405	31	G11F	77	SI Gel	38	SJ4570	97
DP420	31	G16F	77	SI100	37	SJ4575	97
DP420NS	24, 25, 28, 31	G23F	77	SI1500	38	SJ4580	97
DP460	31	G45F	78	SJ30H	99	Super 77™	60
DP460NS	31	G45P	78	SJ30L	99	Super 77™ CA	60
DP490	31	G90F	77	SJ60H	99	TE015	35
DP600	35, 69	GM10	41	SJ60L	99	TE030	36
DP600NS	35, 69	GM18	41	SJ3001	99	TE031	36
DP604NS	35	GM74	41	SJ3401	99	TE040	36
DP605NS	35	GPH-060GF	75	SJ3402	99	TE100	36
DP620NS	35	GPH-110GF	75	SJ3418FR	99	TE200	36
DP6301NS	35	GPH-160GF	75	SJ3419FR	99	TL22	41
DP6310NS	25, 28, 35	HP45	40	SJ3440	97	TL42	41
DP6330NS	35	LO1000	38	SJ3441	97	TL43	41
DP640	34	LSB60	31	SJ3442	97	TL62	40
DP805	33	LSB60NS	31	SJ3443	97	TL71	41
DP810	32	LSB360NS	31	SJ3444	97	TL72	40
DP810NS	33	LSE-060WF	75, 78	SJ3445	97	TL77	40
DP820	33	LSE-110WF	75, 78	SJ3460	97	TL90	41
DP5001	35	LSE-160WF	75, 78	SJ3463	97	TS115 HGS	36
DP5106	69	0P591	67	SJ3481	97	TS230	25, 28, 36
DP8005	34	P592	67	SJ3506	99	UPUV	79
DP8010	24, 28, 34	PF5422	66	SJ3507	99		
DP8010NS	33	PF5423	66	SJ3518FR	99		
DP8405NS	33	PR Gel	38	SJ3519FR	99		
DP8407NS	24, 28, 33	PR40	38	SJ3522	99		
DP8410NS	24, 33	PR100	24, 28, 38	SJ3523	99		
DP8425NS	33	PR600	38	SJ3526N	99		
DP8610NS	34	PR1500	38	SJ3527N	99		
DP8625NS	34	PS65	40	SJ3530	99		
DP8705NS	33	PS67	40	SJ3531	99		
DP8710NS	24, 28, 33	PS77	40	SJ3540	97		
DP8725NS	33	QSS		SJ3541			
DP8805NS		RP+040GP	•	SJ3542			
DP8810NS		RP+040GF		SJ3550			
DP8825NS		RP+060G		SJ3550CF			
DP8910NS	ŕ	RP+060GF		SJ3551			
EZ250015		RP+080GP		SJ3551CF			
EZ250030	36	RP+080GF	74	SJ3552	97		

Product	Page	Product	Page	Product	Page	Product	Page
3M <sup>™</sup> Adhesive Sealants		9375W	89	3M™ Cleaners and Lubricant	s	2084	66
525	66	9379	91	Adhesive Remover	57	2158 B/A	29
540	66	9380	91	Adhesive Remover –		2214	24, 32
550FC	66	9442	90	Low VOC <20% Clear		2216	25
550FC + AC63	66	9445	90	Industrial Citrus Base Cleaner.	57	2216 B/A	30
551	66	9447	90	Silicone Lubricant		2216NS B/A	30
560	66	9453FL	90	Silicone Spray 60% VOC	57	2262	56, 62
560 + AC63	66	9453LE	90			2290	32
590	66	9457	91	3M™ Concrete Repair		3028EK	84
606	66	9458	89	600	35, 69	3501 B/A	28
730UV	66	9459W	89	600NS	35, 69	53382	69
740UV	66	9471	89	604NS	35	87979	69
760UV	66	9471FL	90	605NS	35	87982	69
800	66	9471LE	90	606	66	97331	69
2084	66	9472	89	620NS	35	98073	69
4000 UV	67	9472FL	90	665	86	DP600	35, 69
4200 FC	67	9472LE	90	666	86	DP600NS	35, 69
5010	66	9482PC	90	730UV	66	DP5106	69
5200	67	9485EK	90	740UV	66		
5200 FC	67	9485PC	90	760UV	66	3M™ Cylinder Spray	Adhesive
5345	66	9497	91	800	66	60 CA	
AP596	67	9499	91	810	33	70	
Marine Silicone	67	9502	88	810NS	33	74	
P591		9505	88	826	62	77	
P592	67	9552	88	847	56, 62	78 ET	
PF5422	66	9555	88	847H	62	90	
PF5423	66	9653		920XL	93	92	
		9653LE		924	92	94 CA	
3M™ Adhesive Transfer Tapes		9665		926	92	94 ET	
463	91	9667MP	88	927	89	4001	
465		9668MP	88	928ATG	86	6501	
467MC		9668MPL	88	936	92	9501	
467MCF		9671	89	950	89	250050	
467MP		9671LE	90	950EK	89	650050	
467MPF		9672LE	90	969	92	QSS	
468MC		9672	89	976	92	Q00	
468MCF		9772WL	90	987	92	3M™ Double Coated	Foom Tonos
468MP		9673		992U	89	4004	•
468MPF		9675		1000NF53,	54, 55, 62	4008	
501FL		9773WL	90	1099	54, 56, 62	4016	
502FL		9774WL	90	1099L	56, 62	4026	
927		9775WL	90	1300	56, 62	4032	
950		91022	91	1300L	56, 62		
950EK		F9460PC		1357	62	4052	
992U		F9465PC		1357L	62	4056	
6035PC		F9467U		1386	32	4085	
6035PL		F9469PC		1469	32	4462	
6038PC		F9473PC		1751 B/A	29	4466	
6038PL		F9752PC		1838 B/A	29	4492	
9372DKW		F9755PC		1838L B/A	29	4496	
9372W				2000NF	54, 60	4658F	82
JUI ZVV	09						

Product	Page	Product	Page	Product	Page	Product	Page
3M™ Double Coated Tapes		SJ3460	97	SJ3401	99	Foot Pedal Assembly	49
401M	85	SJ3463	97	SJ3402	99	Heavy-Duty Benchstand	49
410M	85	SJ3481	97	SJ3418FR	99	Hot Melt Applicator AE II	49
415	84	SJ3540	97	SJ3419FR	99	Hot Melt Applicator Pneumatic	
444	84	SJ3541	97	SJ3506	99	PG II with Speedloader	
444PC	84	SJ3542	97	SJ3507	99	Hot Melt Applicator TC	49
3028EK	84	SJ3550	97	SJ3518FR	99	Hot Melt Applicator TC with Quadrack Converter	49
9086	84	SJ3550CF	97	SJ3519FR	99	Low Melt Applicator AE II LT	
9087	84	SJ3551	97	SJ3522	99	Low Melt Applicator LT	
9377	85	SJ3551CF	97	SJ3523	99	Low Melt Applicator LT with	
9443NP	85	SJ3552	97	SJ3526N	99	Quadrack Converter	49
9496LE	83	SJ3552CF	97	SJ3527N	99	Low Melt Applicator Pneumatic	40
9456	84	SJ3558	97	SJ3530	99	PG II LT with Speedloader	
9500PC	84	SJ3560	97	SJ3531	99	Quadrack Converter	
9576	84	SJ3561	97	SJ3571	99	TC and LT Palm Trigger	
9579	85	SJ3562	97	SJ3572	99	Valve Assembly Kit	
9589	85	SJ3782	97			Variable Applicator EC	49
9731	85	SJ3870	97	3M™ Hot Melt Adhesives,			
9737	85	SJ3871	97	Applicators and Accessories		3M™ Hot Melt Spray Adhesives	
9738	85	SJ3872	97	3731		3794	
9740	85	SJ4570	97	3738	50	6111HT	50
9741	85	SJ4575	97	3747	50		
9816H	85	SJ4580	97	3748		3M™ Removable/Repositionable	Tapes
9816L	85			3750	50	401M	86
9816M	85	3M™ Extended Liner Tapes		3762	50	410M	86
9817H	85	450EK	93	3764	50	665	86
9817L	85	450XL	93	3779	50	666	86
9817M	85	465XL		3789	50	928ATG	86
9824	84	466XL	93	3792	50	9415PC	86
9828	84	476XL	93	3797	50	9416	86
9828PC	84	920XL		3748 VO	50	9425	86
9832	84	9925XL		3762LM	50	9425HT	86
9832HL	84	9926XL		3776LM	50		
93005LE	83	9934XL		3792LM	50	3M™ Scotch-Weld™	
93010LE	83			3798LM	50	Anaerobic Adhesives	
93015LE	83	3M™ Extreme Sealing Tapes		9725	49	AC649	41
93020LE	83	4411B	80	9726	49	GM10	41
96042	85	4411G		9727	49	GM18	
99786	84	4411N		9785	49	GM74	
99786NP	84	4412G		9913	49	HP45	
		4412N		9916	49	PS65	
3M™ Dual Lock™ Reclosable Fas	teners			9917	49	PS67	
SJ3440	97	284™ I I I I I		9921	49	PS77	
SJ3441		3M™ Hook and Loop Reclosable Fasteners		9922	49	RT09	
SJ3442		SJ30H	99	9929	49	RT38	
SJ3443		SJ30L	99	9940	49	RT41	
SJ3444		SJ60H	99	9946	49	RT48	
SJ3445		SJ60L	99	Bench Mount		TL22	
		SJ3001	99	Bench Nozzle Assembly	49	TL42	41

Product	Page	Product	Page	Product	Page	Product	Page
TL43	41	RT5000B	39	490	31	2290	32
TL62	40	SI Gel	38	600	35, 69	3028EK	84
TL71	41	SI100	37	600NS	35, 69	3501 B/A	28
TL72	40	SI1500	38	604NS	35	7240FR	31
TL77	40	SF20	39	605NS	35	3501 B/A	28
TL90	41	SF100	39	606	66	3532 B/A	33
		Surface Activator	40	620NS	35	3549	35
3M™ Scotch-Weld™ EPX				665	86	3901	32
Applicators and Nozzles		3M™ Scotch-Weld™ PUR		666	86	5001	35
3M™ Concrete Repair 8.4 oz. Nozzles		Adhesive Systems		730UV	66	6101	32
3M™ EPX™ 400mL Manual Ap		3M™ Scotch-Weld™ PUR Applic		740UV	66	8010	34
3M™ EPX™ Mixing Nozzle		3M™ Scotch-Weld™ PUR Prehe	ater37	760UV	66	8010NS	33
3M™ EPX™ Pneumatic Applic		3M <sup>™</sup> Scotch-Weld <sup>™</sup> PUR Repai Kits and Replacement Parts		800	66	8405NS	33
48.5/50mL		3M™ Scotch-Weld™ PUR		810	33	8407NS	33
3M™ Scotch-Weld™ Dual Driv		System Accessories		810NS	33	8410NS	33
Manual 1:1/2:1 Applicator 20		for hands-free dispensing		826	62	8425NS	33
3M <sup>™</sup> Scotch-Weld <sup>™</sup> Dual Driv Manual 10:1 Applicator		Alternate Nozzle System not for with disposable nozzles		847	56, 62	8625NS	34
3M™ Scotch-Weld™ Dual		EZ250015		847H	62	8705NS	33
Drive Pneumatic 1:1/2:1	40	EZ250030		920XL	93	8710NS	33
Applicator 200mL	43	EZ250060		924	92		33
3M™ Scotch-Weld™ Dual Drive Pneumatic 1:1/2:1		F7250120		926	92		32
Applicator 400mL	43	FZ250150	36	927	89		32
3M™ Scotch-Weld™ Dual Driv Pneumatic Applicator 490mL		EZ250200		928ATG	86	8825NS	32
3M™ Scotch-Weld™ EPX™	40	TE015		936	92	8910NS	24, 34
Mixing Nozzle	42,43	TE030		950	89		25, 29
3M™ Scotch-Weld™ EPX™		TE031		950EK	89		29
Mixing Nozzle, Low Waste	43	TE040		969	92		29
3M™ Scotch-Weld™ EPX™ Plus II Applicator	42	TE100		976	92		30
Standard Caulk Gun		TE200		987	92		30
		TS115 HGS		992U	89		30
3M™ Scotch-Weld™ Instant	Adhasivas	TS230		1000NF	53, 54, 55, 62		24, 25, 28, 30
AC09		3756	36	1099	54, 56, 62		30
AC77		TS230	25, 28, 36	1099L	56, 62		25, 29
AC79		3756	36	1300	56, 62		31
AC113				1300L	56, 62		31
AC452		3M™ Scotch-Weld™		1357	62		24, 25, 28, 31
CA4		Structural Adhesives		1357L	62		31
CA5		100	29	1386	32		31
CA7		100NS	29	1469	32		31
CA8		100FR	29	1751 B/A	29		35, 69
CA9		100 Plus	30	1838 B/A	29		35, 69
CA40		105	30	1838L B/A	29		35
CA40H		110	30	2000NF	54, 60		35
CA50 Gel		125	30	2084	66		35
CA100		221	32	2158 B/A	29		34
LO1000		270	29	2214 Hi-Temp New F	ormula32		33
PR Gel		405	31	2214 Non- Metallic F	illed32		32
PR40		420	31	2214 Regular	24, 32		33
PR100		420LH	31	2216	25		33
PR600		420NS	31	2216 B/A	30		34
PR1500		460	31	2216NS B/A	30		35
1 10 10 00	00	460NS	31	2262	56, 62	DP6310NS	25, 28, 35

Product	Page	Product	Page	Product	Page	Product	Page
DP6330NS	35	74	60	4914-020	76	B11F	77
DP8005	34	74 CA	60	4919F	74	B16F	77
DP8010	24, 28, 34	76	62	4920	75	B23F	77
DP8010NS	33	77	53, 55	4926	74	B45F	78
DP8405NS	33	78	62	4929	75	B90F	77
DP8407NS	24, 28, 33	78ET	62	4930	75	CV45F	76
DP8410NS	24, 33	78HT	62	4930F	75	CV62F	76
DP8425NS	33	80	56, 62	4936	74	G11F	77
DP8610NS	34	90	54, 56, 60	4936F	74	G16F	77
DP8625NS	34	90 CA	60	4941	74, 78, 79	G23F	77
DP8705NS	33	92	54, 60	4941F	74	G45F	78
DP8710NS	24, 28, 33	94 CA	54, 60	4943F	75	G45P	78
DP8725NS	33	94 ET	54, 60	4945	75	G90F	77
DP8805NS	34	100NF	53, 55, 60	4946	75	GPH-060GF	75
DP8810NS	34	100NF + Activator	55	4947F	74	GPH-110GF	75
DP8825NS	34	826	62	4949	75	GPH-160GF	75
DP8910NS	24, 34	847	56, 62	4979F	74	LSE-060WF	75, 78
LSB60	31	847H	62	4950	75	LSE-110WF	75, 78
LSB60NS	31	1000NF	53, 54, 55, 62	4951	75	LSE-160WF	75, 78
LSB360NS	31	1099	54, 56, 62	4955	75	RP+040GP	74, 79
				4956	74, 78	RP+040GF	74
3M™ Single Coated Foam 7	Tapes .	3M™ Solvent and Wa		4956F	74	RP+060GP	74
4104	100	Based Adhesives (cor	•	4957F	75	RP+060GF	74
4108	100	1099L	ŕ	4959	75	RP+080GP	74
4116	100	1300		4959F	75	RP+080GF	74
4314	100	1300L	•	4991	74	RP+110GP	74, 79
4317	100	1357		4991B	74	RP+110GF	74
4318	100	1357L		5906	74, 76	RP+160GP	74
4504	100	2000NF	•		74, 76	RP+160GF	74
4508	100	2262	,-	5908	74, 76, 79	UPUV	79
4516	100	4475		5909	74, 76		
4714	100	4693		5915	74, 79	Scotch® ATG Adhes	ive Transfer Tapes
4718	100	4799	,-		74	926	92
4726	100	4799 Super 77™	•		74	969	92
		Super 77™ CA			74, 79	976	92
3M™ Solvent and Water		Super // CA	00		74	924	92
Based Adhesives	00				74	987	92
1		3M™ VHB™ Tapes and			74		
5	,	94			74		
10		4611			74		
20		4618			74, 78, 79		
24		4622			74		
27		4624			74, 78		
30H		4646			74		
30NF	,	4655			74, 78		
49	,	4905			74		
60 CA		4910			74		
70	,	4914			79		
72	62	4914-015	/6	AP115	79		

Notes:	

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

3M, Bumpon, Dual Lock, Fastbond, Scotch-Seal, Scotch-Weld, Super 77, VHB and Weatherban are trademarks of 3M Company. Scotch is a registered trademark of 3M Company. All other trademarks are property of their respective owners.

LEED® is a registered trademark of the United States Green Building Council (USGBC).



Industrial Adhesives and Tapes Division 3M Center, Building 223 St. Paul, MN 55144-100 USA

Phone 800-362-3550 Fax 877-369-2923

Web 3M.com/assemblysolutions